

ISO/FDIS 1827:2022(E)

ISO TC 45/SC 2/WG 1

Date: 2022-05-12

Secretariat: JISC

Rubber, vulcanized or thermoplastic — Determination of shear modulus and adhesion to rigid plates — Quadruple-shear methods

Caoutchouc vulcanisé ou thermoplastique — Détermination du module de cisaillement et de la force d'adhérence à des plaques rigides — Méthodes du quadruple cisaillement

iTeh STANDARD PREVIEW

FDIS stage
(standards.iteh.ai)

ISO/FDIS 1827

<https://standards.iteh.ai/catalog/standards/sist/2a010d3d-ad60-4142-89b3-3b5218a754e4/iso-fdis-1827>

ISO/FDIS 1827:2022(E)

© ISO ~~2021~~2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office

CP 401 • Ch. de Blandonnet 8

CH-1214 Vernier, Geneva

Phone: +41 22 749 01 11

Email: copyright@iso.org

Website: www.iso.org~~www.iso.org~~

Published in Switzerland

ITeH STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 1827

<https://standards.iteh.ai/catalog/standards/sist/2a010d3d-ad60-4142-89b3-3b5218a754e4/iso-fdis-1827>

Contents

Foreword	5
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
4.1 Method A — Determination of the shear modulus	2
4.2 Method B — Determination of the adhesion	2
5 Apparatus	2
6 Calibration	2
7 Test piece	3
7.1 Shape and dimensions	3
7.2 Preparation	4
7.3 Number of test pieces	5
8 Time interval between vulcanization and testing	5
9 Conditioning	5
10 Temperature of test	5
11 Procedure	5
11.1 Method A	5
11.2 Method B	6
12 Expression of results	6
12.1 Method A	6
12.2 Method B	7
13 Test report	7
13.1 For method A	7
13.2 For method B	8
Annex A (normative) Calibration schedule	10
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
4.1 Method A — Determination of the shear modulus	2
4.2 Method B — Determination of the adhesion	2
5 Apparatus	2
6 Calibration	2
7 Test piece	2

ISO/FDIS 1827:2022(E)

7.1	Shape and dimensions	2
7.2	Preparation	3
7.3	Number of test pieces	3
8	Time interval between vulcanization and testing.....	4
9	Conditioning.....	4
10	Temperature of test.....	4
11	Procedure.....	4
11.1	Method A.....	4
11.2	Method B.....	4
12	Expression of results	5
12.1	Method A.....	5
12.2	Method B.....	5
13	Test report.....	6
13.1	For method A.....	6
13.2	For method B.....	7
	Annex A (normative) Calibration schedule.....	8

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 1827

<https://standards.iteh.ai/catalog/standards/sist/2a010d3d-ad60-4142-89b3-3b5218a754e4/iso-fdis-1827>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This ~~six~~sixth edition cancels and replaces the fifth edition (ISO 1827:2016), of which ~~has been technically revised~~ it constitutes a minor revision.

The ~~main~~ changes ~~compared to the previous edition~~ are as follows:

- ~~The~~the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Rubber, vulcanized or thermoplastic — Determination of shear modulus and adhesion to rigid plates — Quadruple-shear methods

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document ~~might~~ can involve the use or generation of substances, or the generation of waste, that ~~could~~ can constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies methods for the determination of the modulus in shear and the strength of bonds of rubber to metal or other rigid plates, using rubber bonded between four parallel plates.

Method A describes the determination of the modulus in shear.

Method B describes the determination of the strength of the bonds.

The methods are applicable primarily to test pieces prepared in the laboratory under standard conditions, such as can be used to provide data for the development and control of rubber compounds and methods of manufacture of bonded shear units.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5893:2020, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Specification*

ISO 18899:2013, *Rubber — Guide to the calibration of test equipment*

ISO 23529, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain ~~terminological~~terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp><https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/><https://www.electropedia.org/>

3.1

shear modulus

applied shear stress, calculated with respect to the bonded area of the rubber in a test piece, divided by the resultant shear strain in the direction of application of the stress

Note 1 to entry: The shear strain (γ) is half the measured deformation divided by the thickness of one rubber block or element. The shear stress (τ) is the applied force divided by twice the area of a bonded face of one rubber block or element.

Note 2 to entry: The form of the test piece specified ensures that there is zero applied stress in the direction normal to the bonded surfaces, so that the deformation can be regarded as simple shear.

Note 3 to entry: This definition of shear modulus is sometimes referred to as the secant modulus.

4 Principle

4.1 Method A — Determination of the shear modulus

The force required to obtain a range of predetermined shear strains of a unit of standard dimensions comprising four parallelepipeds of rubber symmetrically disposed and bonded to four parallel rigid plates is measured, the forces being parallel to the bonding surfaces and, as a rule, non-destructive, i.e. of maximum values appreciably lower than the bond strength.

4.2 Method B — Determination of the adhesion

The force required to cause the rupture of a unit as described for method A is measured.

5 Apparatus

5.1 Test machine, complying with the requirements of ISO 5893, capable of measuring force with an accuracy corresponding to class 1, as defined in ISO 5893:2020, and with a rate of traverse of the moving grip of 5 mm/min (method A) or 50 mm/min (method B).

The test machine shall include apparatus to measure the deformation of the rubber of the test piece to an accuracy of 0,02 mm.

5.2 Fixtures, for holding the test pieces in the grips, provided with a universal joint to permit accurate centring of the line of action of the applied force.

5.3 Environmental chamber, suitable for carrying out tests at the temperature chosen or specified (see Clause 10), conforming to the requirements of ISO 23529.


6 Calibration


The test apparatus shall be calibrated in accordance with the schedule given in Annex A.

7 Test piece

7.1 Shape and dimensions

The test piece shall consist of four identical parallelepipedic rubber elements $4\text{ mm} \pm 1\text{ mm}$ thick, $20\text{ mm} \pm 5\text{ mm}$ wide and $25\text{ mm} \pm 5\text{ mm}$ long, bonded on each of their two largest opposite faces to the mating faces of four rigid plates of the same width and of appropriate lengths to obtain a symmetrical double-sandwich arrangement, means being provided at the free external end of each central plate to enable it to be attached to a holding fixture. The rigid plates shall be of sufficient thickness to withstand bending. A typical arrangement is shown in Figure 1.





- Key
- 1 two external plates
 - 2 two internal plates
 - 3 pin and fixture for tensile loading

Figure 1 — Test piece arrangement

ISO/FDIS 1827

<https://standards.iteh.ai/catalog/standards/sist/2a010d3d-ad60-4142-89b3-3b5218a754e4/iso-fdis-1827>

7.2 Preparation

7.2.1 Preparation of rigid plates

Rectangular rigid plates of suitable dimensions shall be prepared and treated in accordance with the requirements of a suitable adhesive system.

7.2.2 Preparation using un moulded rubber

Prepared rigid plates and suitably sized rubber blanks shall be moulded either by compression or by transfer methods. The moulding shall be carried out using a time and temperature sequence appropriate to the rubber under test. At the conclusion of moulding, care shall be taken in removing the test pieces from the mould to avoid subjecting the adhered surfaces to undue stress.

7.2.3 Preparation using pre-moulded rubber

The four rubber elements for each test piece may be cut from a pre-moulded sheet of uniform thickness or from a rubber product. In either case, care shall be taken to ensure that all four elements are equal in all their dimensions to within $\pm 0,1$ mm.