



Designation: E 1710 – 97

Standard Test Method for Measurement of Retroreflective Pavement Marking Materials with CEN-Prescribed Geometry Using a Portable Retroreflectometer¹

This standard is issued under the fixed designation E 1710; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers measurement of the retroreflective properties of horizontal pavement marking materials containing retroreflecting beads, such as traffic stripes and surface symbols, using a portable retroreflectometer that can be placed on the road delineation to measure the retroreflection at a prescribed geometry.

NOTE 1—The restriction to bead based materials is for the purpose of ensuring a sufficiently gradual optical response function (from points of the source aperture to points of the receiver aperture) to allow generous sized instrument source and receiver apertures.

1.2 The entrance and observation angles of the retroreflectometer affect the readings. As specified by the European Committee for Standardization (CEN), the entrance and observation angles shall be 88.76° and 1.05° , respectively.

1.3 This test method is intended to be used for field measurement of pavement markings but may be used to measure the performance of materials on sample panels before placing the marking material in the field.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 4061 Test Method for Retroreflectance of Horizontal Coatings²

E 284 Terminology of Appearance²

E 809 Practice for Measuring Photometric Characteristics of Retroreflectors²

2.2 Other Standard:

CEN EN 1436 Road Marking Materials—Road Marking

¹ This test method is under the jurisdiction of ASTM Committee E-12 on Appearance and is the direct responsibility of Subcommittee E12.10 on Retroreflection.

Current edition approved Dec. 10, 1997. Published September 1998. Originally published as E 1710 – 95. Last previous edition E 1710 – 95a.

² Annual Book of ASTM Standards, Vol 06.01.

Performance for Road Users³

3. Terminology

3.1 The terminology used in this test method generally agrees with that used in Terminology E 284.

3.2 *Definitions*—The delimiting phrase “in retroreflection” applies to each of the following definitions when used outside the context of this or other retroreflection test methods:

3.2.1 *coefficient of retroreflected luminance, R_L, n* —the ratio of the luminance, L , of a projected surface to the normal illuminance, E_{\perp} , at the surface on a plane normal to the incident light, expressed in candelas per square metre per lux ($\text{cd}\cdot\text{m}^{-2}\cdot\text{lx}^{-1}$).

3.2.1.1 *Discussion*—Because of the low luminance of pavement markings, the units used commonly are millicandelas per square metre per lux ($\text{mcd}\cdot\text{m}^{-2}\cdot\text{lx}^{-1}$).

3.2.2 *co-entrance angle, β_C, n* —the complement of the entrance angle ($90^\circ - \beta$).

3.2.3 *co-viewing angle, ν_C, n* —the complement of the viewing angle ($90^\circ - \nu$).

3.2.4 *entrance angle, β, n* —the angle between the illumination axis and the retroreflector axis.

3.2.5 *observation angle, α, n* —the angle between the illumination axis and the observation axis.

3.2.6 *portable retroreflectometer, n* —a hand-held instrument that can be used in the field or laboratory for measurement of retroreflectance.

3.2.6.1 *Discussion*—In this test method, “portable retroreflectometer” refers to a hand-held instrument that can be placed over roadway delineation to measure the coefficient of retroreflected luminance with a prescribed geometry.

3.2.7 *presentation angle, γ, n* —the angle between the observation half-plane and the half-plane that originates on the illumination axis and that contains the retroreflector axis.

3.2.8 *instrument standard, n* —working standard used to standardize the portable retroreflectometer.

3.2.9 *retroreflection, n* —a reflection in which the reflected rays are returned preferentially in directions close to the

³ Available from European Committee for Standardization, Central Secretariat (CEN), rue de Stassart 36, B1050 Brussels, Belgium.

opposite of the direction of the incident rays, this property being maintained over wide variations of the direction of the incident rays.

3.2.10 *viewing angle, n* —the angle between the retroreflector axis and the observation axis.

3.2.10.1 *Discussion*—The retroreflector axis for pavement markings is normal to the marking.

4. Summary of Test Method

4.1 This test method involves the use of commercial portable retroreflectometers for determining the coefficient of retroreflected luminance of horizontal coating materials used in pavement markings.

4.2 The entrance angle is fixed at 88.76° (co-entrance angle 1.24°).

4.3 The observation angle is fixed at 1.05° .

4.4 The presentation angle shall be 0° .

4.5 The portable retroreflectometers use either a built-in reference white for standardization or use an external panel of known coefficient of retroreflected luminance, or both.

4.6 The retroreflector is placed directly over the pavement marking to be measured, ensuring that the measurement area of the retroreflector fits within the width of the stripe, and the reading displayed by the retroreflector is recorded.

4.7 The retroreflector is then moved to other positions on the pavement marking, and the readings are recorded and averaged.

4.8 Readings shall be taken and averaged in each direction of traffic for a centerline.

5. Significance and Use

5.1 The quality of the stripe is determined by the coefficient of retroreflected luminance, R_L , and depends on the materials used, age, and wear pattern. These conditions shall be observed and noted by the user.

5.2 Under the same conditions of illumination and viewing, larger values of R_L correspond to higher levels of visual performance.

5.3 Retroreflectivity of pavement (road) markings degrade with traffic wear and require periodic measurement to ensure that sufficient line visibility is provided to drivers.

5.4 For a given viewing distance, measurements of R_L made with a retroreflector having a geometry corresponding to that viewing distance are a good indicator of the visual ranking of material measured.

5.5 As specified by CEN, the measurement geometry of the instrument is based on centerline markings, a viewing distance of 30 m, an eye height of 1.2 m, and a headlight mounting height of 0.65 m.

5.6 It shall be the responsibility of the user to employ an instrument having the specified observation and entrance angles.

6. Apparatus

6.1 *Portable Retroreflector:*

6.1.1 The retroreflector shall be portable, with the capability of being placed on various horizontal pavement markings in different locations.

6.1.2 The retroreflector shall be constructed so that placement on the highway pavement markings will preclude any stray light from entering the measurement area of the instrument and affecting the reading.

6.1.3 For the convenience of the user, a marking shall be placed on the instrument to permit it to be aligned with the direction of traffic.

6.2 *Light Source Requirements:*

6.2.1 The projection optics shall be such that the distribution of the illuminance over the measurement area will be within 10 % of the average illuminance.

6.2.2 The aperture angle of the light source as determined from the center of the measurement area shall not be larger than a rectangle subtending 10 min of arc (0.17°) by 20 min of arc (0.33°).

6.2.2.1 Rectangle aperture dimensions are given with the first side parallel to the observation half plane.

NOTE 2—The maximum source aperture dimensions are in agreement with CEN EN 1436. There is experimental evidence that for this test method, using this maximum source aperture together with the maximum receiver aperture in 6.3.3 produces R_L measurements within 1.5 % of those using two 10-min circular apertures as specified in Test Method D 4061.

6.3 *Receiver Requirements:*

6.3.1 The receiver shall have sufficient sensitivity and range to accommodate coefficient of retroreflected luminance values expected in use, typically 1 to 2000 $\text{mcd}\cdot\text{m}^{-2}\cdot\text{lx}^{-1}$.

6.3.2 If the retroreflector is intended to be used for measurement of marking materials other than white, the combined spectral distribution of the light source and the spectral responsivity of the receiver shall match the combined spectral distribution of CIE Illuminant A and the $V(\lambda)$ spectral luminosity function according to the following criterion: For any choice of plano parallel colored absorptive filter mounted in front of a white retroreflective sample, the ratio of the R_L measured with the filter to the R_L measured without the filter shall be within 10 % of the Illuminant A luminous transmittance of an air-spaced pair of two such filters.

6.3.3 The aperture of the receiver as determined from the center of the measurement area shall not be larger than a square subtending 20 min of arc (0.33°) by 20 min of arc (0.33°).

NOTE 3—The maximum receiver aperture dimensions are in agreement with CEN EN 1436. There is experimental evidence that for this test method, using this maximum receiver aperture together with the maximum source aperture in 6.2.2 produces R_L measurements within 1.5 % of those using two 10-min circular apertures as specified in Test Method D 4061.

6.3.4 Instruments with annular apertures are not recommended for measuring pavement markings.

6.3.5 The combined stability of the output of the light source and receiver shall be such that readings will not change more than $\pm 1\%$ after 10 s when the retroreflector is in contact with the pavement marking and ready to measure.

6.3.6 The linearity of the retroreflector photometric scale over the range of readings expected shall be within 2 %. Correction factors may be used to ensure a linear response. A method for determining linearity is found in Annex A2 of Practice E 809.

6.4 *Measurement Geometry:*