



Designation: B584 – 13

Standard Specification for Copper Alloy Sand Castings for General Applications¹

This standard is issued under the fixed designation B584; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers requirements for copper alloy sand castings for general applications. Nominal compositions of the alloys defined by this specification are shown in [Table 1](#).² This is a composite specification replacing former documents as shown in [Table 1](#).

NOTE 1—Other copper alloy castings are included in the following ASTM specifications: [B22](#), [B61](#), [B62](#), [B66](#), [B67](#), [B148](#), [B176](#), [B271](#), [B369](#), [B427](#), [B505/B505M](#), [B763](#), [B770](#), and [B806](#).

1.2 Component part castings produced to this specification may be manufactured in advance and supplied from stock. In such cases the manufacturer shall maintain a general quality certification of all castings without specific record or date of casting for a specific casting.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards:³

[B22](#) Specification for Bronze Castings for Bridges and Turntables

[B61](#) Specification for Steam or Valve Bronze Castings

[B62](#) Specification for Composition Bronze or Ounce Metal Castings

[B66](#) Specification for Bronze Castings for Steam Locomotive Wearing Parts

[B67](#) Specification for Car and Tender Journal Bearings, Lined

[B148](#) Specification for Aluminum-Bronze Sand Castings

[B176](#) Specification for Copper-Alloy Die Castings

[B208](#) Practice for Preparing Tension Test Specimens for Copper Alloy Sand, Permanent Mold, Centrifugal, and Continuous Castings

[B271](#) Specification for Copper-Base Alloy Centrifugal Castings

[B369](#) Specification for Copper-Nickel Alloy Castings

[B427](#) Specification for Gear Bronze Alloy Castings

[B505/B505M](#) Specification for Copper Alloy Continuous Castings

[B763](#) Specification for Copper Alloy Sand Castings for Valve Applications

[B770](#) Specification for Copper-Beryllium Alloy Sand Castings for General Applications

[B806](#) Specification for Copper Alloy Permanent Mold Castings for General Applications

[B824](#) Specification for General Requirements for Copper Alloy Castings

[B846](#) Terminology for Copper and Copper Alloys

[E255](#) Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

[E527](#) Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 ASME Code:

ASME Boiler and Pressure Vessel Code⁴

3. Terminology

3.1 Definitions of terms relating to copper alloys can be found in Terminology [B846](#).

4. General Requirements

4.1 The following sections of Specification [B824](#) form a part of this specification. In the event of a conflict between this specification and Specification [B824](#), the requirements of this specification shall take precedence.

4.1.1 Terminology,

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved April 1, 2013. Published April 2013. Originally approved in 1973. Last previous edition approved in 2012 as B584 – 12a. DOI: 10.1520/B0584-13.

² The UNS system for copper and copper alloys (see Practice [E527](#)) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Nominal Compositions

Classification	Copper Alloy UNS No.	Previous Designation	Commercial Designation	Copper	Tin	Lead	Zinc	Nickel	Iron	Aluminum	Manganese	Silicon	Niobium	Bismuth
Leaded red brass	C83450	88	2½	2	6½	1
	C83600	B145-4A	85-5-5-5 or No. 1 composition	85	5	5	5
	C83800	B145-4B	commercial red brass, 83-4-6-7	83	4	6	7
Leaded semi-red brass	C84400	B145-5A	valve composition, 81-3-7-9	81	3	7	9
	C84800	B145-5B	semi-red brass, 76-2½-6½-15	76	2½	6½	15
Leaded yellow brass	C85200	B146-6A	high-copper yellow brass	72	1	3	24
	C85400	B146-6B	commercial No. 1 yellow brass	67	1	3	29
High-strength yellow brass	C85700	B146-6C	leaded naval brass	61	1	1	37
	C86200	B147-8B	high-strength manganese bronze	63	27	...	3	4	3
	C86300	B147-8C	high-strength manganese bronze	61	27	...	3	6	3
	C86400	B147-7A	leaded manganese bronze	58	1	1	38	...	1	½	½
	C86400 C86500	B 132-A B147-8A	No. 1 manganese bronze	58	39	...	1	1	1
Silicon bronze + silicon brass	C86700	B 132-B	leaded manganese bronze	58	1	1	34	...	2	2	2
	C87300	B198-12A	silicon bronze	95	1	4
	C87400	B198-13A	silicon brass	82	...	½	14	3½
	C87500	B198-13B	silicon brass	82	14	4
	C87600	B198-13C	silicon bronze	91	5	4
	C87610	B198-12A	silicon bronze	92	4	4
	C87710	...	silicon bronze	86	10	4
Bismuth selenium brass	C87845 ^A	...	silicon bronze	76	21.26	2.7
	C87850 ^B	...	silicon brass	76	20.9	3
	C89510 ^C	...	sebiloy I	87	5	...	5	1.0
	C89520 ^D	...	sebiloy II	86	5½	...	5	1.9
	C89530 ^E	86.5	4.7	...	8.0	1.5
	C89535	86.5	3.0	...	7.0	0.65	1.4
Bismuth brass	C89720 ^F	67.5	1	...	29.8	0.5	...	0.5	...	0.7
Bismuth red brass	C89833	...	bismuth brass	89	5	...	3	2.2
Bismuth bronze	C89836	...	lead-free bronze	89.5	5.5	...	3.0	2
Bismuth semi-red brass	C89844	...	bismuth brass	84½	4	...	8	3
Tin bronze + leaded tin bronze	C90300	B143-1B	modified "G" bronze, 88-8-0-4	88	8	...	4
	C90500	B143-1A	"G" bronze, 88-10-0-2	88	10	...	2
	C92200	B143-2A	steam or valve bronze-Navy "M"	88	6	1½	4½
	C92210	88	5	2	4	1
	C92300	B143-2B	87-5-1-4, Navy PC	87	8	1	4
	C92600	...	87-10-1-2	87	10	1	2
	C93200	B144-3B	83-7-7-3	83	7	7	3
High-lead tin bronze	C93500	B144-3C	85-5-9-1	85	5	9	1
	C93700	B144-3A	80-10-10	80	10	10
	C93800	B144-3D	78-7-15	78	7	15
	C94300	B144-3E	71-5-24	71	5	24
	C94700	B 292-A	nickel-tin bronze Grade "A"	88	5	...	2	5
Nickel-tin bronze + leaded nickel-tin bronze	C94800	B 292-B	leaded nickel-tin bronze Grade "B"	87	5	1	2	5
	C94900	...	leaded nickel-tin bronze Grade "C"	80	5	5	5	5
Spinodal alloy	C96800	82	8	10	0.2	...
Leaded nickel bronze	C97300	B149-10A	12 % leaded nickel silver	57	2	9	20	12
	C97600	B149-11A	20 % leaded nickel silver	64	4	4	8	20

TABLE 1 *Continued*

Classification	Copper Alloy UNS No.	Previous Designation	Commercial Designation	Copper	Tin	Lead	Zinc	Nickel	Iron	Aluminum	Manganese	Silicon	Niobium	Bismuth
	C97800	B149-11B	25 % leaded nickel silver	66	5	2	2	25

^A Phosphorus 0.04.
^B Phosphorus 0.12.
^C Selenium 0.5.
^D Selenium 0.9.
^E Selenium 0.20.
^F Antimony 0.07, Boron 0.001.

- 4.1.2 Other Requirements,
- 4.1.3 Dimensions, Mass, and Permissible Variations,
- 4.1.4 Workmanship, Finish, and Appearance,
- 4.1.5 Sampling,
- 4.1.6 Number of Tests and Retests,
- 4.1.7 Specimen Preparation,
- 4.1.8 Test Methods,
- 4.1.9 Significance of Numerical Limits,
- 4.1.10 Inspection,
- 4.1.11 Rejection and Rehearing,
- 4.1.12 Certification,
- 4.1.13 Test Report,
- 4.1.14 Product Marking,
- 4.1.15 Packaging and Package Marking, and
- 4.1.16 Supplementary Requirements.

5. Ordering Information

5.1 Orders for castings under this specification should include the following information:

- 5.1.1 Specification title, number, and year of issue,
- 5.1.2 Quantity of castings,
- 5.1.3 Copper alloy UNS Number (Table 1) and temper (as-cast, heat treated, and so forth),
- 5.1.4 Pattern or drawing number, and condition (as-cast, machined, etc.),
- 5.1.5 *ASME Boiler and Pressure Vessel Code*—compliance (Section 10),
- 5.1.6 When material is purchased for agencies of the U.S. government, the Supplementary Requirements of Specification B824 may be specified.

5.2 The following options are available and should be specified in the purchase order when required:

- 5.2.1 Chemical analysis of residual elements (7.3),
- 5.2.2 Pressure test or soundness requirements (Specification B824),
- 5.2.3 Approval of weld repair or impregnation, or both (Section 9),
- 5.2.4 Certification (Specification B824),
- 5.2.5 Foundry test report (Specification B824),
- 5.2.6 Witness inspection (Specification B824), and
- 5.2.7 Product marking (Specification B824).

6. Manufacture

6.1 Copper alloy UNS Nos. C94700 and C96800 may be supplied in the heat treated condition to obtain the higher

mechanical properties shown in Table 2. Suggested heat treatments for these alloys are given in Table 3. Actual practice may vary by manufacturer.

6.2 Separately cast test bar coupons representing castings made in copper alloy UNS Nos. C94700HT and C96800HT shall be heat treated with the castings.

7. Chemical Composition

7.1 The castings shall conform to the compositional requirements for named elements as shown in Table 4 for the copper alloy UNS numbers specified in the purchase order.

7.2 These specification limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements agreed upon between manufacturer or supplier and purchaser. Copper or zinc, when zinc is 20 % or greater, may be given as remainder and may be taken as the difference between the sum of all elements analyzed and 100 %. When all named elements in Table 4 are analyzed, their sum shall be as specified in Table 5.

7.3 It is recognized that residual elements may be present in cast copper alloys. Analysis shall be made for residual elements only when specified in the purchase order.

8. Mechanical Properties

8.1 Mechanical properties shall be determined from separately cast test bar castings, and shall meet the requirements shown in Table 2.

9. Casting Repair

9.1 The castings shall not be weld repaired without approval of the purchaser (5.2.3).

9.2 The castings shall not be impregnated without approval of the purchaser (5.2.3).

10. ASME Requirements

10.1 When specified in the purchase order to meet ASME Boiler and Pressure Vessel Code requirements, castings in copper alloy UNS Nos. C92200, C93700, and C97600 shall comply with the following:

- 10.1.1 Certification requirements of Specification B824.
- 10.1.2 Foundry test report requirements of Specification B824.
- 10.1.3 Castings shall be marked with the manufacturer's name, the copper alloy UNS number, and the casting quality

TABLE 2 Mechanical Requirements

Copper Alloy UNS No.	Tensile Strength, min		Yield Strength, ^A min		Elongation in 2 in. or 50 mm, min, %
	ksi ^B	MPa ^C	ksi ^B	MPa ^C	
C83450	30	207	14	97	25
C83600	30	207	14	97	20
C83800	30	207	13	90	20
C84400	29	200	13	90	18
C84800	28	193	12	83	16
C85200	35	241	12	83	25
C85400	30	207	11	76	20
C85700	40	276	14	97	15
C86200	90	621	45	310	18
C86300	110	758	60	414	12
C86400	60	414	20	138	15
C86500	65	448	25	172	20
C86700	80	552	32	221	15
C87300	45	310	18	124	20
C87400	50	345	21	145	18
C87500	60	414	24	165	16
C87600	60	414	30	207	16
C87610	45	310	18	124	20
C87710	47	324	24	165	10
C87845	52	359	18	124	29
C87850	59	407	22	152	16
C89510	26	184	17	120	8
C89520	25	176	17	120	6
C89530	28	195	13 ^D	90 ^D	15
C89535	32	220	16 ^D	110 ^D	15
C89720	30	210	16	110	15
C89833	30	207	14	97	16
C89836	33	229	14	97	20
C89844	28	193	13	90	15
C90300	40	276	18	124	20
C90500	40	276	18	124	20
C92200	34	234	16	110	22
C92210	32	225	15	103	20
C92300	36	248	16	110	18
C92600	40	276	18	124	20
C93200	30	207	14	97	15
C93500	28	193	12	83	15
C93700	30	207	12	83	15
C93800	26	179	14	97	12
C94300	24	165	10
C94700	45	310	20	138	25
C94700 (HT)	75	517	50	345	5
C94800	40	276	20	138	20
C94900	38	262	15	103	15
C96800	125	862	100 ^D	689 ^D	3
C96800 (HT)	135	931	120 ^D	821 ^D	...
C97300	30	207	15	103	8
C97600	40	276	17	117	10
C97800	50	345	22	152	10

^A Yield strength shall be determined as the stress producing an elongation under load of 0.5 %, that is, 0.01 in. (0.254 mm) in a gage length of 2 in. or 50 mm.

^B ksi = 1000 psi.

^C See Appendix X1.

^D Yield strength 0.2 %, offset.

TABLE 3 Suggested Heat Treatments

Copper Alloy UNS No.	Solution Treatment (not less than 1 h followed by water quench)	Annealing Treatment (not less than 2 h followed by air cool)
C96800	1500°F (815°C)	(Age to develop properties) 660°F (350°C)
	Solution treatment (not less than 2 h followed by water quench)	Precipitation hardening (5 h)
C94700	1425–1475°F (775–800°C)	580–620°F (305–325°C)

factor. In addition, heat numbers or serial numbers that are traceable to heat numbers shall be marked on all pressure-containing castings individually weighing 50 lbs (22.7 kg) or more. Pressure-containing castings weighing less than 50 lbs (22.7 kg) shall be marked with either the heat number or a serial number that will identify the casting as to the month in which it was poured. Marking shall be in such a position as to not impair the usefulness of the casting.

10.2 The castings shall not be repaired, plugged, welded, or “burned in” unless permission from the purchaser has been previously secured. This will be given only when the defects are such that after the approved repair the usefulness and strength of the castings has not been impaired.

10.3 Alloys in this specification are generally weldable. Preparation for repair welding shall include inspection to ensure complete removal of the defect. Repairs shall be made utilizing welding procedures qualified in accordance with Section IX if the ASME code and repair welding shall be done by welders or welding operators meeting the qualification requirements of ASME Section IX. The following records shall be maintained:

10.3.1 A sketch or drawing showing the dimensions, depth, and location of excavations,

10.3.2 Postweld heat treatment, when applicable,

10.3.3 Weld repair inspection results,

10.3.4 Casting identification number,

10.3.5 Weld procedure identification number,

10.3.6 Welder identification, and

10.3.7 Name of inspector.

11. Sampling

11.1 Test bar castings for copper alloy UNS Nos. C86200, C86300, C86400, C86500, and C86700 shall be cast to the form and dimensions shown in Figs. 1 or 2 of Practice B208. Test bar castings for all other alloys listed in this specification shall be cast to the form and dimensions shown in Figs. 2, 3, or 4 of Practice B208.

11.2 When castings are specified to meet the requirements of the ASME Boiler and Pressure Vessel Code, for small remelts the lot size shall not exceed 1000 lbs (455 kg) of castings and shall consist of all of the metal from a single master heat poured from an individual melting unit or group of melting units operating during the course of one-half shift, not to exceed 5 h.

12. Test Methods

12.1 Analytical chemical methods are given in Specification B824.

13. Keywords

13.1 copper alloy castings; copper-base alloy castings; sand castings