



Designation: **D4332 – 01 (Reapproved 2006) D4332 – 13**

Standard Practice for Conditioning Containers, Packages, or Packaging Components for Testing¹

This standard is issued under the fixed designation D4332; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice provides for standard and special conditioning and testing atmospheres that may be used to simulate particular field conditions that a container, package, or packaging component may encounter during its life or testing cycle.

1.2 This practice describes procedures for conditioning these containers, packages, or packaging components so that they may reach equilibrium with the atmosphere to which they may be exposed.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D685 Practice for Conditioning Paper and Paper Products for Testing](#)

[D996 Terminology of Packaging and Distribution Environments](#)

[E41 Terminology Relating To Conditioning](#)

[E171 Practice for Conditioning and Testing Flexible Barrier Packaging](#)

[E337 Test Method for Measuring Humidity with a Psychrometer \(the Measurement of Wet- and Dry-Bulb Temperatures\)](#)

2.2 *ISO Standard:*

[2233 Packaging—Complete, Filled Transport Packages: Conditioning for Testing](#)³

~~2.3 *Forest Products Laboratory:*~~

~~[Moisture Content vs. Relative Humidity Chart](#) [Content vs. Relative Humidity Chart](#)⁴~~

3. Terminology

3.1 Terms and definitions used in this practice may be found in Terminology [D996](#), Terminology [E41](#), or Specification [E171](#).

4. Significance and Use

4.1 Many materials from which containers and packages are made, especially cellulosic materials, undergo changes in physical properties as the temperature and the relative humidity (RH) to which they are exposed are varied. Therefore, the package should be placed and kept in a specified atmosphere for a length of time such that subsequent measurements of physical properties will be meaningful and reproducible.

4.2 The conditions described in this practice are either historically accepted standard conditions or special laboratory conditions chosen to represent particular phases of the distribution environment. These special conditions do not necessarily duplicate actual field conditions, but tend to simulate them and have effects on packages and materials which may be related to their field performance.

¹ This practice is under the jurisdiction of ASTM Committee [D10](#) on Packaging and is the direct responsibility of Subcommittee [D10.21](#) on Shipping Containers and Systems - Application of Performance Test Methods.

Current edition approved Nov. 1, 2006 March 15, 2013. Published November 2006 April 2013. Originally approved in 1984. Last previous edition approved in 2004 2006 as D4332 – 01 (2006) ϵ ; DOI: [10.1520/D4332-01R06](#); [10.1520/D4332-13](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, [http://www.ansi.org](#).