
**Textile glass — Chopped-strand
and continuous-filament mats —
Determination of average thickness,
thickness under load and recovery
after compression**

*Verre textile — Mats à fils coupés et mats à fils continus —
Détermination de l'épaisseur moyenne, de l'épaisseur sous charge et
de la recouvrance après compression*

ISO/PRF 3616

<https://standards.iteh.ai/catalog/standards/sist/e7015bbd-0b96-4c62-8674-59653145cdb7/iso-prf-3616>

PROOF/ÉPREUVE



Reference number
ISO 3616:2022(E)

© ISO 2022

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/PRF 3616

<https://standards.iteh.ai/catalog/standards/sist/e7015bbd-0b96-4c62-8674-59653145cdb7/iso-prf-3616>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Apparatus	2
6 Preparation of test specimens	4
7 Conditioning of test specimens	4
8 Procedure	4
9 Calculation and expression of results	5
9.1 Average thickness.....	5
9.2 Thickness under load.....	5
9.3 Recovery after compression.....	6
10 Test report	6

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/PRF 3616

<https://standards.iteh.ai/catalog/standards/sist/e7015bbd-0b96-4c62-8674-59653145cdb7/iso-prf-3616>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

ISO/PRF 3616

This third edition cancels and replaces the second edition (ISO 3616:2001), which has been technically revised. It also incorporates the Amendment ISO 3616:2001/Amd. 1:2017.

The main changes are as follows:

- an “Introduction” has been added;
- the sampling method (former Clause 6) has been deleted and subsequent clauses have been renumbered;
- the duration for conditioning test specimens has been changed to from at least 16 h to at least 2 h.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Chopped-strand and continuous-filament mats are mainly used as reinforcement materials for polymer matrix composites. The average thickness, thickness under load and recovery after compression of the mat are the most basic parameters provided for the composites process design and the final product structure and size design.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/PRF 3616

<https://standards.iteh.ai/catalog/standards/sist/e7015bbd-0b96-4c62-8674-59653145cdb7/iso-prf-3616>

Textile glass — Chopped-strand and continuous-filament mats — Determination of average thickness, thickness under load and recovery after compression

1 Scope

This document specifies a method for the determination of the average thickness, the thickness under load and the recovery after compression of chopped-strand and continuous-filament textile-glass mats.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 3374, *Reinforcement products — Mats and fabrics — Determination of mass per unit area*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1 average thickness

thickness of a mat, in millimetres, measured in accordance with the specified method, under a specified nominal light pressure

Note 1 to entry: The average thickness determined by this method does not necessarily bear a direct relation to the thickness of a single layer. The regularity of thickness of a mat must be measured on a single layer and with apparatus with a much smaller contact area than that specified in this document.

3.2 thickness under load

thickness of a mat, measured in accordance with the specified method, under a specified heavy pressure applied for a specified time, expressed as a percentage of the initial *average thickness* (3.1)

3.3 recovery after compression

thickness to which the mat recovers after a specified interval following removal of the specified heavy pressure, expressed as a percentage of the initial *average thickness* (3.1)

4 Principle

The distance between the outer surfaces of a pile of superimposed layers of mats, having a total thickness of at least 5 mm, is measured under a specified light pressure. The average thickness is calculated by dividing the value obtained by the number of layers in the pile.

The distance between the outer surfaces of the pile is measured both during the application of a specified high pressure and again after a specified interval following removal of the pressure. The thickness under pressure and the recovery after compression, respectively, are calculated by dividing the two values obtained by the number of layers in the pile and expressing the results as a percentage of the average thickness.


5 Apparatus

5.1 Sharp knife.

5.2 Template for cutting out test samples, of dimensions 316 mm × 316 mm or 400 mm × 250 mm (see [Clause 7](#)).

5.3 Template for cutting out test specimens, of dimensions 158 mm × 158 mm or 200 mm × 125 mm (see [Clause 7](#)).

5.4 Stand, having a plane base-plate for supporting the test specimens and a suitable support for a dial-gauge micrometer (see [Figure 1](#)).



Key

- 1 support for dial-gauge micrometer
- 2 positioning jig
- 3 dial-gauge micrometer
- 4 micrometer stem
- 5 base-plate

Figure 1 — Example of stand for test specimens and dial-gauge micrometer

5.5 Dial micrometer thickness gauge, readable to 0,01 mm and with a stem of length at least 70 mm.

5.6 Positioning jig, to ensure that the test specimens and steel plates A and B (see [5.7](#) and [5.8](#)) are placed with their centres directly under the foot of the micrometer, and of such thickness that plate B rests on the mats (and not on the jig).

5.7 Polished steel plate, plate A (see [Figure 2](#)), of dimensions 158 mm × 158 mm × 1,3 mm (plate A₁) or 200 mm × 125 mm × 1,3 mm (plate A₂), having a mass of about 255 g and exerting a pressure of 100 Pa on the test specimens). Other dimensions or details of construction may be varied as long as it conforms to the values given for area and pressure.

The surfaces of the plate shall be plane and parallel.

A hydraulic system may be used in place of the plate provided that the same pressure is produced.

5.8 Polished steel plate, plate B (see [Figure 3](#)), of dimensions either 158 mm × 158 mm × 65,5 mm (plate B₁) or 200 mm × 125 mm × 65,5 mm (plate B₂), having a mass of about 12,25 kg and exerting a pressure of 5 kPa on the test specimens when used together with plate A. Plate B has a cut-out as shown in [Figure 3](#). Other dimensions or details of construction may be varied as long as it conforms to the values given for area and pressure.

The surfaces of the plate shall be plane and parallel.

A hydraulic system may be used in place of the plate provided that the same pressure is produced.





Figure 2 — Light mild-steel plate (density of steel 7,84 Mg/m³) for determination of average thickness

Dimensions in millimetres

**Key**

1 weld

Figure 3 — Examples of heavy mild-steel plate (density of steel 7,84 Mg/m³) for determination of thickness under load and recovery after compression

6 Preparation of test specimens

Using the template (5.2) and sharp knife (5.1), cut out three test samples, evenly distributed across the mat, of dimensions 316 mm × 316 mm or 400 mm × 250 mm, following the procedure specified in ISO 3374.

Using the template (5.3) and sharp knife, cut each test sample into four test specimens of dimensions 158 mm × 158 mm or 200 mm × 125 mm.

7 Conditioning of test specimens

Condition the test specimens for at least 2 h in one of the standard atmospheres specified in ISO 291.

The atmosphere during the test shall be the same as that used for conditioning.

8 Procedure

8.1 Place steel plate A (5.7) on the base-plate of the stand (5.4), under the foot of the dial-gauge micrometer (5.5). Ensure that the axis of the micrometer foot is perpendicular to plate A.

8.2 Record the dial-gauge reading, h_1 , in millimetres, to the nearest 0,1 mm.