



Designation: **E1993 – 98 (Reapproved 2008) E1993/E1993M – 98 (Reapproved 2013)^{ε1}**

Standard Specification for Bituminous Water Vapor Retarders Used in Contact with Soil or Granular Fill Under Concrete Slabs¹

This standard is issued under the fixed designation E1993;E1993/E1993M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

ϵ^1 NOTE—Units information was editorially corrected in May 2013.

1. Scope

1.1 This specification covers bituminous water vapor retarders for use in contact or granular fill under concrete slabs.

1.2 The specified tests are conducted on new materials and materials that have been conditioned or exposed to simulate potential service conditions.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values given in parentheses are provided for information only and are not considered—stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C168 Terminology Relating to Thermal Insulation

D828 Test Method for Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus (Withdrawn 2009)³

D1790 Test Method for Brittleness Temperature of Plastic Sheeting by Impact

~~D5147~~**D5147/D5147M** Test Methods for Sampling and Testing Modified Bituminous Sheet Material

E96/E96M Test Methods for Water Vapor Transmission of Materials

~~E154~~**E154/E154M** Test Methods for Water Vapor Retarders Used in Contact with Earth Under Concrete Slabs, on Walls, or as Ground Cover

E631 Terminology of Building Constructions

3. Terminology

3.1 ~~Definitions:~~*Definitions*—For definitions of terms used in this specification, see Terminologies **C168** and **E631**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *perm, n*—the time rate of water vapor migration through a material or a construction of one grain per hour, square foot, inch of mercury pressure difference.

¹ This specification is under the jurisdiction of ASTM Committee **E06** on Performance of Buildings and are the direct responsibility of Subcommittee **E06.21** on Serviceability.

Current edition approved Oct. 1, 2008; April 1, 2013. Published November 2008; May 2013. Originally approved in 1998. Last previous edition approved in 2002 as **E1993 – 98 (2002)** (2008). DOI: 10.1520/E1993-98R08; 10.1520/E1993_E1993M-98R13E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

3.2.1.1 *Discussion*—