



Designation: B70 – 90 (Reapproved 2013)

# Standard Test Method for Change of Resistance With Temperature of Metallic Materials for Electrical Heating<sup>1</sup>

This standard is issued under the fixed designation B70; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the change of resistance with temperature of metallic materials for electrical heating, and is applicable over the range of service temperatures.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

## 2. Significance and Use

2.1 The change in resistance with temperature for heating element materials is a major design factor and may influence material selection. The measurement of this change is essential to ensure that heating elements perform as designed. This test method was designed to minimize the effect different manufacturing processes have on resistance change, thereby yielding results that are reproducible.

## 3. Test Specimen and Leads

3.1 The test specimen shall be prepared from material as left by the manufacturing process, and in a form suitable for measuring its resistance in an electric furnace. When the resistance is to be measured with a Kelvin bridge, potentiometer, digital ohmmeter, or equivalent, a current lead shall be welded to each end of the specimen in such a manner that there will be no change of current distribution in the specimen during measurements. Potential leads, one at each

end, shall be attached by welding, at a distance from the corresponding current lead not less than one tenth of the length of the specimen between the potential leads.

3.2 When the resistance is to be measured with a Wheatstone bridge, only the current leads are required. The resistance of the leads in this case shall not exceed 1 % of the resistance of the specimen and the leads shall be made of the same type of alloy as the test specimen. For both methods of measurement, the leads shall have a length within the heated zone of the furnace of at least 50 times their minimum transverse dimension, in order to avoid disturbance of the temperature of the specimen by conduction of heat to the colder parts of the furnace.

## 4. Electric Furnace

4.1 The furnace for heating the specimen shall be of such a type that the temperature can be controlled over the range from room temperature to the maximum desired. It shall be so constructed that the specimens and the thermocouples can be maintained at a uniform and constant temperature at desired points within the working range. The specimen and thermocouples shall be so shielded as to prevent direct radiation from hotter, or to colder, parts of the furnace.

4.2 In order to test the uniformity of the temperature in the region to be occupied by the test specimen, a typical specimen and thermocouple shall be prepared and mounted in the center of this region. The furnace shall then be heated to its maximum temperature and maintained at this temperature until equilibrium is reached. The specimen shall then be moved in the furnace in the direction of the maximum temperature gradient through a distance equal to the maximum dimension of the largest specimen and thermocouple assembly which is to be used in this furnace. The temperature of the typical specimen in this position shall not differ from that in the normal position by more than 10°C.

## 5. Resistance Measurements

5.1 A Kelvin bridge, potentiometer, digital ohmmeter, or equivalent shall be used when measuring specimens having resistances less than 10  $\Omega$ . A Wheatstone bridge may be used with specimens having resistances greater than 10  $\Omega$ . The resistance of the specimen shall be measured with an accuracy

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.10 on Thermostat Metals and Electrical Resistance Heating Materials.

Current edition approved May 1, 2013. Published May 2013. Originally approved in 1927. Last previous edition approved in 2007 as B70 – 90 (2007). DOI: 10.1520/B0070-90R13.