



Designation: **F925–02 (Reapproved 2008) F925 – 13**

Standard Test Method for Resistance to Chemicals of Resilient Flooring¹

This standard is issued under the fixed designation F925; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method provides a procedure for determining the resistance of resilient floor covering to surface deterioration when exposed to various chemical reagents. This test method is not intended as a staining test nor as a method to judge surface and appearance restoration of the sample after exposure to the chemical reagent.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only. ~~mathematical conversions to SI units that are provided for information only and are not considered standard.~~

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific hazard information is provided in Section 56 of this test method.

2. Referenced Documents

2.1 *ASTM Standards:*²

[D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates](#)

[F141 Terminology Relating to Resilient Floor Coverings](#)

[F142 Test Method for Indentation of Resilient Floor Tiles \(McBurney Test\) \(Withdrawn 2007\)](#)³

[F386 Test Method for Thickness of Resilient Flooring Materials Having Flat Surfaces](#)

[F1914 Test Methods for Short-Term Indentation and Residual Indentation of Resilient Floor Covering](#)

3. Terminology

3.1 For terminology relating to Resilient Floor Coverings, see Terminology [F141](#).

4. Significance and Use

4.1 Resilient flooring products are designed and formulated to have good resistance to most common chemicals encountered in typical use. High performance wear layers can also be used to enhance cleanability and chemical resistance. Resilient flooring used in residential and commercial environments may be subjected to a variety of chemicals through accidental spillage or as ingredients used for hygienic purposes. Performance is dependent upon the flooring formulation and that of the maintenance products used on the flooring. This test method provides a means of estimating the relative susceptibility of resilient floor covering to change when exposed to chemical reagents.

5. Apparatus

5.1 *Gloves*, impervious vinyl or rubber,

5.2 *Tweezers*, or forceps,

5.3 *Medicine Dropper*, 3 in. straight glass with rubber bulb or pipette having a point opening diameter not less than $\frac{1}{16}$ in. (1.6 mm) or greater than $\frac{5}{64}$ in. (1.8 mm),

¹ This test method is under the jurisdiction of ASTM Committee F06 on Resilient Floor Coverings and is the direct responsibility of Subcommittee F06.30 on Test Methods - Performance.

Current edition approved Jan. 1, 2008; May 1, 2013. Published March 2008; May 2013. Originally approved in 1985. Last previous edition approved in 2002 as F925-02(2008)-02. DOI: 10.1520/F0925-02R08; 10.1520/F0925-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

5.4 *White Facial Tissue.*

5.5 *Watch Glass.*

5.6 *Timer.*

5.7 *Filter Paper.*

5.8 *Small Laboratory Spatula*, approximately ¼ –½ in.-wide blade, rounded bottom, not sharpened,

5.9 *Suitable Spectrophotometer or Colorimeter*, with a minimum ¼ in. (6.35 mm) diameter opening having a cool white fluorescent (CWF) or daylight (D-65) light source, or both, that measures color in CIE L*, a*, b* using CIE 10° standard observer and specular included (see Test Method **D2244**).

5.10 *Indentation Tester*, see Test Methods **F142** and **F1914**.

5.11 *Thickness Tester*, see Test Method **F386**.

5.12 *Conditioning Room or Cabinet*, equipped with automatic temperature and humidity controls that will maintain 73.4 ± 3.6°F (23 ± 2°C) and 50 ± 5 % relative humidity.

6. Hazards

6.1 A new medicine dropper or pipette should be used for each test reagent. If the same reagent dispenser apparatus is to be reused, it shall be thoroughly cleaned in hot soapy water and alcohol, or both, prior to applying each different test reagent.

6.2 Check to be sure the colorimeter is properly warmed up and calibrated prior to use.

6.3 Be sure specimens are held flat when measuring color.

6.4 Be sure each specimen is marked in the corner on the back for easy identification.

6.5 Dispose of chemical test reagents properly. Refer to Material Safety Data Sheets (MSDS) or precautions on the label for proper disposal. (**Warning**—Observe all necessary precautions when handling test reagents known to be flammable or potentially hazardous.)

7. Test Specimen

7.1 The specimen shall consist of a portion of the test unit at least 6 by 6 in. (153.4 by 153.4 mm) for each reagent (chemical) to be tested.

7.2 Specimens shall be selected with minimal changes in surface texture.

7.3 Specimens should be of a color to show potential effect of reagent.

8. Procedure

8.1 Unless otherwise specified, condition the specimens and the test reagents (chemicals) for at least 24 h prior to testing. The environment for conditioning and testing is 73.4 ± 3.6°F (23 ± 2°C) and 50 ± 5 % relative humidity.

8.2 Lay the specimens face up on a firm, flat surface.

8.3 Select a test area on the specimen having the flattest area and color appropriate to show the effect of the reagent and draw a square approximately 1½ by 1½ in. (38 by 38 mm) centered on that desired test location.

8.4 If using test equipment such as an indentation tester, thickness tester or color spectrophotometer to help quantify specimen change, take initial readings on the unexposed specimen and record values as indicated in **Fig. 1**. All measurements should be taken on a relatively flat spot, corresponding as closely as possible to the center of the test square.

	Reagent	Overall thickness, mils			Indentation, mils			Color; L, a, b						Sample:	
		Initial	Difference after exposure	Difference 24 h after exposure	Initial	Difference after exposure	Difference 24 h after exposure	Initial			After exposure			Comments	
								L	a	b	L	a	b		ΔE
1															
2															
3															
4															
5															
6															
7															
8															
9															
10															
Average															

FIG. 1 Resistance to Chemicals Measurement Form