



Designation: **C1728—12 C1728 – 13**

Standard Specification for Flexible Aerogel Insulation¹

This standard is issued under the fixed designation C1728; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This specification covers the classification and performance of flexible aerogel thermal insulation. This will cover the range of continuous exposure operating temperatures from -321°F (-196°C) up to 1200°F (649°C).

1.2 For satisfactory performance, properly installed protective vapor retarders or barriers shall be used on below ambient temperature applications to reduce movement of moisture through or around the insulation to the colder surface. Failure to use a vapor retarder or barrier could lead to insulation and system non-performance.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The following safety hazards caveat pertains only to the test methods described in this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C165 Test Method for Measuring Compressive Properties of Thermal Insulations](#)

[C167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations](#)

[C168 Terminology Relating to Thermal Insulation](#)

[C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus](#)

[C303 Test Method for Dimensions and Density of Preformed Block and Board-Type Thermal Insulation](#)

[C335 Test Method for Steady-State Heat Transfer Properties of Pipe Insulation](#)

[C356 Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat](#)

[C390 Practice for Sampling and Acceptance of Thermal Insulation Lots](#)

[C411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation](#)

[C447 Practice for Estimating the Maximum Use Temperature of Thermal Insulations](#)

[C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus](#)

~~[E665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing](#)~~

[G795 Specification for Thermal Insulation for Use in Contact with Austenitic Stainless Steel](#)

[C1045 Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions](#)

[C1058 Practice for Selecting Temperatures for Evaluating and Reporting Thermal Properties of Thermal Insulation](#)

[C1101/C1101M Test Methods for Classifying the Flexibility or Rigidity of Mineral Fiber Blanket and Board Insulation](#)

[C1104/C1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation](#)

[C1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus](#)

[C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings](#)

[C1511 Test Method for Determining the Water Retention \(Repellency\) Characteristics of Fibrous Glass Insulation \(Aircraft Type\)](#)

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved Jan. 15, 2012; May 1, 2013. Published January 2012; May 2013. Originally approved in 2012. Last previous edition approved in 2012 as C1728-12. DOI: [10.1520/C1728-12](#); [10.1520/C1728-13](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[C1617 Practice for Quantitative Accelerated Laboratory Evaluation of Extraction Solutions Containing Ions Leached from Thermal Insulation on Aqueous Corrosion of Metals](#)

[E84 Test Method for Surface Burning Characteristics of Building Materials](#)

[E2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics](#)

2.2 *Other Standards*:³

[CAN/ULC-S102 Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies](#)

3. Terminology

3.1 *Definitions*: For definitions used in this specification, see Terminology A3.

3.2 *flexible aerogel insulation, n*—a flexible insulation containing a composite of aerogel, fibrous carrying media, or reinforcements, or a combination thereof.

³ Available from Underwriters Laboratories (UL), 2600 N.W. Lake Rd., Camas, WA 98607-8542, <http://www.ul.com>.

3.2.1 *Discussion*—

Opacifiers are sometimes added as either fibers or powders.

4. Classification

4.1 Flexible ½ aerogel insulation shall be classified into three Types based on the maximum use temperature:

4.1.1 Type I — 257°F (125°C)

4.1.2 Type II — 390°F (200°C)

4.1.3 Type III — 1200° F (649°C)

4.2 Types I and II are subdivided as Grade 1 (tested in flat configuration) and Categories A or B by thermal conductivity.

4.3 Type III is subdivided into two Grades 1 and 2 whereby Grade 1 is tested in a flat configuration using Test Method [C177](#) and Grade 2 is tested only in a pipe configuration using Test Method [C335](#).

5. Ordering Information

5.1 The Type, Grade, Category, dimensions, and thickness shall be specified by the purchaser. A product certification (if required) shall be specified in the purchase order.

6. Materials and Manufacture

6.1 *Composition*—Flexible aerogel insulation is a composite of an amorphous silica-based aerogel, a fibrous carrying media, or reinforcements, or a combination thereof, that allow the construct to be flexible.

6.1.1 A fibrous carrying media or reinforcement, or both, consists of the following: fibers, batts, strips, sheets, or some combination thereof.

6.1.1.1 This fibrous carrying media or reinforcement material, or both, is either organic, such as polyester, or inorganic, such as glass fibers. Additionally, some flexible aerogel insulation contains additives such as a water resistant treatment or opacifiers, or both.

7. Physical, Mechanical and Chemical Property Requirements

NOTE 1—Performance requirements for flexible aerogel insulation (Type I Grade 1 Category A, Type I Grade 1 Category B, Type II Grade 1 Category A, Type II Grade 1 Category B, and Type III Grade 1 Category A and Type III Grade 2 Category A) are given in [Table 1](#).

7.1 *Maximum Use Temperature*—When tested in accordance with Test Method [C411](#) in a flat configuration and the hot surface performance of Practice [C447](#) in a flat configuration at the insulation's maximum use temperature at a thickness of 80 mm or manufacturer's maximum recommended thickness, the flexible aerogel insulation shall not warp, flame, or glow during hot surface exposure. No evidence of melting or fiber degradation shall be evident upon post-test inspection.

7.2 *Thickness and Density*—The thickness and density shall be determined and reported in accordance with Test Methods [C167](#) or [C303](#).

7.3 *Apparent Thermal Conductivity*:

7.3.1 Determine the thermal conductivity as a function of temperature for the representative specimens with data obtained from a series of thermal tests utilizing Test Methods [C177](#), [C518](#), [C1114](#), or [C335](#) as appropriate for the material under study. Specimen shall be tested unfaced and, for Type III, Grade 2 (pipe configuration per Test Method [C335](#)), test at a minimum of 4 layers. Each layer shall have a minimum thickness of 0.2 in (5 mm). The test report shall state the barometric pressure at the time of the tests. See [Note 2](#) below.