



Designation: **C1410—12 C1410 – 13**

# Standard Specification for Cellular Melamine Thermal and Sound-Absorbing Insulation<sup>1</sup>

This standard is issued under the fixed designation C1410; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the type, physical properties, and dimensions of open-cell melamine foam intended for use as thermal and sound-absorbing insulation for temperatures from  $-40$  to  $+350^{\circ}\text{F}$  ( $-40$  to  $+177^{\circ}\text{C}$ ) in industrial environments.

1.2 Some uses of thermal insulation materials covered by this specification are governed by building codes that address fire performance.

1.3 The use of an appropriate vapor retarder is required on cold surface applications where water vapor condense and cause a decrease in thermal performance. Refer to Practice **C755** for selection of vapor retarders. Facings shall be agreed upon between the purchaser and the manufacturer or supplier.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**C168** Terminology Relating to Thermal Insulation

**C177** Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus

**C335** Test Method for Steady-State Heat Transfer Properties of Pipe Insulation

**C356** Test Method for Linear Shrinkage of Preformed High-Temperature Thermal Insulation Subjected to Soaking Heat

**C390** Practice for Sampling and Acceptance of Thermal Insulation Lots

**C423** Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method **10-13**

**C518** Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus

**C585** Practice for Inner and Outer Diameters of Thermal Insulation for Nominal Sizes of Pipe and Tubing

**C755** Practice for Selection of Water Vapor Retarders for Thermal Insulation

**C1045** Practice for Calculating Thermal Transmission Properties Under Steady-State Conditions

**C1104/C1104M** Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation

**C1363** Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus

**D2863** Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics (Oxygen Index)

**D3574** Test Methods for Flexible Cellular Materials—Slab, Bonded, and Molded Urethane Foams

**E84** Test Method for Surface Burning Characteristics of Building Materials

**E176** Terminology of Fire Standards

**E662** Test Method for Specific Optical Density of Smoke Generated by Solid Materials

**E795** Practices for Mounting Test Specimens During Sound Absorption Tests

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **C16** on Thermal Insulation and is the direct responsibility of Subcommittee **C16.22** on Organic and Nonhomogeneous Inorganic Thermal Insulations.

Current edition approved ~~Sept. 1, 2012~~ May 15, 2013. Published ~~October 2012~~ May 2013. Originally approved in 1998. Last previous edition approved in ~~2010~~ 2012 as ~~C1014~~ **C1410-10-12**. DOI: ~~10.1520/C1410-12~~ 10.1520/C1410-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Common Dimensions**

	Type I	Type II
Width, in. (mm)	12 to 50 (305 to 1270)	N/A
Length, in. (mm)	48 to 100 (1219 to 2540)	36 or 48 (914 or 1219)
Thickness, in. (mm)	¼ to 20 (6.4 to 508)	½ to 5 (12.7 to 127)

## E2231 Practice for Specimen Preparation and Mounting of Pipe and Duct Insulation Materials to Assess Surface Burning Characteristics

### 2.2 Boeing Standards:

Boeing Specification Support Standard 72396<sup>3</sup>

### 2.3 International Maritime Organization:

Resolution MSC.41(64) Interim Standard for Measuring Smoke and Toxic Products of Combustion Interim Standard for Measuring Smoke and Toxic Products of Combustion<sup>4</sup>

## 3. Terminology

3.1 *Definitions*—Terms used in this specification are defined in Terminology C168 and also in Terminology E176 as appropriate

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *melamine foam*—a low-density, semirigid, flexible cellular, open-cell foam made from the polymerization and foaming of melamine-formaldehyde resins.

3.2.2 *flexible cellular*—a cellular organic polymeric material that will not rupture within 60 s when a specimen 8 by 1 by 1 in. (200 by 25 by 25 mm) is bent around a 1-in. (25-mm) diameter mandrel at a uniform rate of one lap in 5 s in the form of a helix at a temperature between 65 and 85°F (18 and 29°C).

## 4. Classification

4.1 Melamine thermal insulation are furnished in the following types and grades:

4.1.1 *Type I*—Flat slab:

4.1.1.1 *Grade 1*—Regular (core foam with no facing).

4.1.1.2 *Grade 2*—Faced foam.

4.1.2 *Type II*—Pipe and tubing insulation:

4.1.2.1 *Grade 1*—Regular (core foam with no facing).

4.1.2.2 *Grade 2*—Faced foam.

4.1.3 *Type III*—Special shapes.

4.1.4 Special Facings.

## 5. Ordering Information

5.1 Purchase orders for melamine thermal insulation shall specify any or all of the following:

5.1.1 Title, number, and year of this specification.

5.1.2 Type and grade designation (see 4.1).

5.1.3 Length, width and thickness required (see Table 1).

5.1.4 Tolerance, if other than specified (see Table 2).

5.1.5 Quantity of material.

5.1.6 Special packaging or marking, when required.

5.1.7 Special requirements for inspection and for testing.

5.1.8 Thermal conductivity at mean temperature of flat stock.

5.1.9 Manufacturers name, address, and telephone number.

5.1.10 Jacket facing type.

## 6. Materials and Manufacture

6.1 Typically a hydrocarbon blowing agent is used to foam melamine formaldehyde resins. The result is an open-cell melamine foam. The blowing agent is drawn off in the manufacturing process and is not residual in the foam.

6.2 Facing materials incorporated into the design of pipe insulation or flat slab shall be agreed upon between the purchaser and the manufacturer or seller. Typical materials are as follows:

6.2.1 *Aluminum Foil*—Aluminum foil laminated to a supporting membrane.

6.2.2 *Aluminized Mylar*—Aluminized mylar film laminated to a supporting membrane.

<sup>3</sup> The Boeing Company, Boeing Technology Services, Seattle, WA, <http://www.boeing.com>.

<sup>4</sup> International Maritime Organization, 4 Albert Embankment, London, United Kingdom, <http://www.imo.org>.