



Designation: B221M – 13

Standard Specification for Aluminum and Aluminum-Alloy Extruded Bars, Rods, Wire, Profiles, and Tubes (Metric)¹

This standard is issued under the fixed designation B221M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers aluminum and aluminum-alloy extruded bars, rods, wires, profiles, and tubes in the aluminum alloys (Note 1) and tempers shown in Table 2.

NOTE 1—Throughout this specification the use of the term *alloy* in the general sense includes aluminum as well as aluminum alloy.

NOTE 2—For rolled or cold-finished bars and rods refer to Specification B211M, for drawn seamless tube used in pressure applications, Specification B210M, for structural pipe and tube, Specification B429/B429M, and for seamless pipe and tube used in pressure applications, Specification B241/B241M.

NOTE 3—Pipe and tube products listed in this specification are intended for general purpose applications. This specification may not address the

manufacturing processes, integrity testing, and verification required for fluid-carrying applications involving pressure. See Specifications B210M and/or B241/B241M, as appropriate, for seamless pipe and tube used in fluid-carrying applications involving pressure. See Specification B234, as appropriate, for use in surface condensers, evaporators, and heat exchangers.

1.2 Alloy and temper designations are in accordance with ANSI H35.1/H35.1M. The equivalent Unified Numbering System alloy designations are those of Table 1 preceded by A9, for example, A91100 for Aluminum 1100 in accordance with Practice E527.

1.3 For acceptance criteria for inclusion of new aluminum and aluminum alloys in this specification, see Annex A2.

1.4 This specification is the metric counterpart of Specification B221.

1.5 The values stated in SI are to be regarded as standard. No other units of measurement are included in this specification.

¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.03 on Aluminum Alloy Wrought Products.

Current edition approved April 1, 2013. Published May 2013. Originally approved in 1979. Last previous edition approved in 2012 as B221M–12a. DOI: 10.1520/B0221M-13.

ASTM B221M-13

<https://standards.iteh.ai/catalog/standards/sist/2299ccbc-b5e6-4279-a399-d002468400e2/astm-b221m-13>

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Composition Limits^{A,B,C}

NOTE 1—In case of a discrepancy between the values listed in **Table 1** and those listed in the “International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys”(known as the “Teal Sheets”), the composition limits registered with the Aluminum Association and published in the “Teal Sheets” should be considered the controlling composition. The “Teal Sheets” are available at <http://www.aluminum.org/tealsheets>.

Alloy	Silicon	Iron	Copper	Manganese	Magnesium	Chromium	Zinc	Titanium	Vanadium	Other Elements ^D	Aluminum
										Each	Total ^E
1060	0.25	0.35	0.05	0.03	0.03	...	0.05	0.03	0.05	0.03	...
1100	0.95 Si + Fe	0.05–0.20	0.05	0.10	0.05 ^G	0.15	99.00 min ^F
2014	0.50–1.2	0.7	3.9–5.0	0.40–1.2	0.20–0.8	0.10	0.25	0.15 ^H	...	0.05 ^H	0.15
2024	0.50	0.50	3.8–4.9	0.30–0.9	1.2–1.8	0.10	0.25	0.15 ^H	...	0.05 ^H	0.15 remainder
2219	0.20	0.30	5.8–6.8	0.20–0.40	0.02	...	0.10	0.02–0.10	0.05–0.15	0.05 ^I	0.15 ^I remainder
3003	0.6	0.7	0.05–0.20	1.0–1.5	0.10	0.05	0.15 remainder
Alclad 3003	...	3003 Clad with 7072 alloy			
3004	0.30	0.7	0.25	1.0–1.5	0.8–1.3	...	0.25	0.05	0.15 remainder
3102	0.40	0.7	0.10	0.05–0.40	0.30	0.10	...	0.05	0.15 remainder
5052	0.25	0.40	0.10	0.10	2.2–2.8	0.15–0.35	0.10	0.05	0.15 remainder
5083	0.40	0.40	0.10	0.40–1.0	4.0–4.9	0.05–0.25	0.25	0.15	...	0.05	0.15 remainder
5086	0.40	0.50	0.10	0.20–0.7	3.5–4.5	0.05–0.25	0.25	0.15	...	0.05	0.15 remainder
5154	0.25	0.40	0.10	0.10	3.1–3.9	0.15–0.35	0.20	0.20	...	0.05	0.15 remainder
5454	0.25	0.40	0.10	0.50–1.0	2.4–3.0	0.05–0.20	0.25	0.20	...	0.05	0.15 remainder
5456	0.25	0.40	0.10	0.50–1.0	4.7–5.5	0.05–0.20	0.25	0.20	...	0.05	0.15 remainder
6005	0.6–0.9	0.35	0.10	0.10	0.40–0.6	0.10	0.10	0.10	...	0.05	0.15 remainder
6005A	0.50–0.9	0.35	0.30	0.50 ^J	0.40–0.7	0.30 ^J	0.20	0.10	...	0.05	0.15 remainder
6013	0.6–1.0	0.50	0.6–1.1	0.20–0.8	0.8–1.2	0.10	0.25	0.10	...	0.05	0.15 remainder
6020 ^K	0.40–0.9	0.50	0.30–0.9	0.35	0.6–1.2	0.15	0.20	0.15	...	0.05	0.15 remainder
6041 ^L	0.50–0.9	0.15–0.7	0.15–0.6	0.05–0.20	0.8–1.2	0.05–0.15	0.25	0.15	...	0.05	0.15 remainder
6042 ^M	0.50–1.2	0.7	0.20–0.6	0.40	0.7–1.2	0.04–0.35	0.25	0.15	...	0.05	0.15 remainder
6060	0.30–0.6	0.10–0.30	0.10	0.10	0.35–0.6	0.5	0.15	0.10	...	0.05	0.15 remainder
6061 ^N	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.35	0.25	0.15	...	0.05	0.15 remainder
6063	0.20–0.6	0.35	0.10	0.10	0.45–0.9	0.10	0.10	0.10	...	0.05	0.15 remainder
6064 ^O	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.05–0.14	0.25	0.15	...	0.05	0.15 remainder
6066	0.9–1.8	0.50	0.7–1.2	0.6–1.1	0.8–1.4	0.40	0.25	0.20	...	0.05	0.15 remainder
6070	1.0–1.7	0.50	0.15–0.40	0.40–1.0	0.50–1.2	0.10	0.25	0.15	...	0.05	0.15 remainder
6082	0.7–1.3	0.50	0.10	0.40–1.0	0.6–1.2	0.25	0.20	0.10	...	0.05	0.15 remainder
6105	0.6–1.0	0.35	0.10	0.15	0.45–0.8	0.10	0.10	0.10	...	0.05	0.15 remainder
6162	0.40–0.8	0.50	0.20	0.10	0.7–1.1	0.10	0.25	0.10	...	0.05	0.15 remainder
6262	0.40–0.8	0.7	0.15–0.40	0.15	0.8–1.2	0.04–0.14	0.25	0.15	...	0.05 ^P	0.15 ^P remainder
6351	0.7–1.3	0.50	0.10	0.40–0.8	0.40–0.8	...	0.20	0.20	...	0.05	0.15 remainder
6360	0.35–0.8	0.10–0.30	0.15	0.02–0.15	0.25–0.45	0.05	0.10	0.10	...	0.05	0.15 remainder
6463	0.20–0.6	0.15	0.20	0.05	0.45–0.9	...	0.05	0.05	0.15 remainder
6560	0.30–0.7	0.10–0.30	0.05–0.20	0.20	0.20–0.6	0.05	0.15	0.10	...	0.05	0.15 remainder
7005	0.35	0.40	0.10	0.20–0.7	1.0–1.8	0.06–0.20	4.0–5.0	0.01–0.06	...	0.05 ^Q	0.15 ^Q remainder
7072 ^R	0.7 Si + Fe	0.10	0.10	0.10	...	0.8–1.3	remainder
7075	0.40	0.50	1.2–2.0	0.30	2.1–2.9	0.18–0.28	5.1–6.1	0.20 ^S	0.05 ^S	0.15	remainder
7116	0.15	0.30	0.50–1.1	0.05	0.8–1.4	...	4.2–5.2	0.05	0.05	0.05 ^T	0.15 remainder
7129	0.15	0.30	0.50–0.9	0.10	1.3–2.0	0.10	4.2–5.2	0.05	0.05	0.05 ^T	0.15 remainder
7178	0.40	0.50	1.6–2.4	0.30	2.4–3.1	0.18–0.28	6.3–7.3	0.20	...	0.05	0.15 remainder

^A Limits are in weight percent maximum unless shown as a range, or stated otherwise.

^B Analysis shall be made for the elements for which limits are shown in this table.

^C For the purpose of determining conformance to these limits, an observed value or a calculated value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of the figures used in expressing the specified limit, in accordance with the rounding-off method of Practice E29.

^D *Others* includes listed elements for which no specific limit is shown as well as unlisted metallic elements. The producer may analyze samples for trace elements not specified in the specification. However, such analysis is not required and may not cover all metallic *Others* elements. Should any analysis by the producer or the purchaser establish that an *Others* element exceeds the limit of *Each* or that the aggregate of several *Others* elements exceeds the limit of *Total*, the material shall be considered nonconforming.

^E *Other Elements*—Total shall be the sum of unspecified metallic elements 0.010 % or more, rounded to the second decimal before determining the sum.

^F The aluminum content shall be calculated by subtracting from 100.00 % the sum of all metallic elements present in amounts of 0.010 % or more each, rounded to the second decimal before determining the sum.

^G Be 0.0003 max for welding electrode, welding rod, and filler wire.

^H Upon agreement between the purchaser and the producer or supplier, a Zr + Ti limit of 0.20 % max is permitted. Properties in Specification (**Table 2**) are not based on the Zirconium and Titanium algorithm.

^I Zirconium, 0.10–0.25 %. The total for other elements does not include zirconium.

^J Manganese plus chromium shall total 0.12–0.50.

^K Lead 0.05 % max, Tin 0.9–1.5 %.

^L Bismuth 0.30–0.9 %, Tin 0.35–1.2 %.

^M Bismuth 0.20–0.8 % Lead 0.15–0.40 %.

^N In 1965 the requirements for 6062 were combined with those for 6061 by revising the minimum chromium from “0.15 %” to “0.04 %.” This action cancelled alloy 6062.

^O Bismuth 0.50–0.7 %, Lead 0.20–0.40 %,

^P Bismuth and lead shall be 0.40–0.7 % each.

^Q Zirconium 0.08–0.20 %. The total for other elements does not include zirconium.

^R Composition of cladding alloy applied during the course of manufacture. Samples from finished tube shall not be required to conform to these limits.

^S Upon agreement between the purchaser and the producer or supplier, a Zr + Ti limit of 0.25 % max is permitted. Properties in Specification (**Table 2**) are not based on the Zirconium and Titanium algorithm.

^T Gallium 0.03 % max.

TABLE 2 Tensile Property Limits^{A,B}

Temper	Specified Section or Wall Thickness, mm		Area, mm ²		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, ^C %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 \sqrt{A})
Aluminum 1060										
O	all	all			60	95	15	...	25	22
H112	all	all			60	...	15	...	25	22
F ^D	all	all		
Aluminum 1100										
O	all	all			75	105	20	...	25	22
H112	all	all			75	...	20	...	25	22
F ^D	all	all		
Alloy 2014										
O	all	all			...	205	...	125	12	10
T4	all	all			345	...	240	...	12	10
T4510 ^E	{	}								
T4511 ^E										
T42 ^F	all	all			345	...	200	...	12	10
T6	...	12.50	all		415	...	365	...	7	6
T6510 ^E	12.50	18.00	all		440	...	400	6
T6511 ^E	18.00	16 000	470	...	415	6
T62 ^F	18.00	...	16 000	20 000	470	...	400	5
	...	18.00	all	...	415	...	365	...	7	6
	18.00	...	16 000	16 000	415	...	365	6
	18.00	...	16 000	20 000	415	...	365	5
F ^D	all	all
Alloy 2024										
O	all	all	240	...	130	12	10	
T3	...	6.30	all		395	...	290	...	12 ^G	...
T3510 ^E	6.30	18.00	all		415	...	305	...	12 ^G	10 ^G
T3511 ^E	18.00	35.00	all		450	...	315	9
	35.00	16 000	485	...	360 ^H	9
	35.00	...	16 000	20 000	470	...	330 ^I	7
T42 ^F	...	18.00	all	...	395	...	260	...	12	10
	18.00	35.00	all	...	395	...	260	9
	35.00	16 000	395	...	260	9
	35.00	...	16 000	20 000	395	...	260	7
T81	1.20	6.30	all		440	...	385	...	4	...
T8510 ^E	6.30	35.00	all		455	...	400	...	5	4
T8511 ^E	35.00	20 000	455	...	400	4
F ^D	all	all
Alloy 2219										
O	all	all	220	...	125	12	10	
T31	...	12.50	...	16 000	290	...	180	...	14	12
T3510 ^E	12.50	80.00		16 000	310	...	185	12
T62 ^F	...	25.00	...	16 000	370	...	250	...	6	5
	25.00	...	20 000	370	...	250	5
T81	...	80.00	...	16 000	400	...	290	...	6	5
F ^D	all	all
Alloy 3003										
O	all	all	95	130	35	...	25	22
H112	all	all	95	...	35	...	25	22
F ^D	all	all
Alclad Alloy 3003										

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm				Area, mm ²		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, ^C %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 \sqrt{A})		
O H112	all	all	all		90	125	30	...	25	...		
	all				90	...	30 ^J	...	25	...		
					Alloy 3004							
O F ^D	all		all		160	200	60	
	all		all		
					Alloy 3102							
H112 ^K	0.70	1.30	all		75	125	30	...	25	...		
					Alloy 5052							
O	all		all		170	240	70	
					Alloy 5083							
O	...	130.00 ^L	...	20 000	270	350	110	...	14	12		
H111	...	130.00 ^L	...	20 000	275	...	165	...	12	10		
H112	...	130.00 ^L	...	20 000	270	...	110	...	12	10		
F ^D	all		all		
					Alloy 5086							
O	...	130.00 ^L	...	20 000	240	315	95	...	14	12		
H111	...	130.00 ^L	...	20 000	250	...	145	...	12	10		
H112	...	130.00 ^L	...	20 000	240	...	95	...	12	10		
F ^D	all		all		
					Alloy 5154							
O	all		all	205	285	75	
H112	all		all	205	...	75	
					Alloy 5454							
O	...	130.00 ^L	...	20 000	215	285	85	...	14	12		
H111	...	130.00 ^L	...	20 000	230	...	130	...	12	10		
H112	...	130.00 ^L	...	20 000	215	...	85	...	12	10		
F ^D	all		all		
					Alloy 5456							
O	...	130.00 ^L	...	20 000	285	365	130	...	14	12		
H111	...	130.00 ^L	...	20 000	290	...	180	...	12	10		
H112	...	130.00 ^L	...	20 000	285	...	130	...	12	10		
F ^D	all		all		
					Alloy 6005							
T1	...	12.50	all	170	...	105	...	16	14			
T5	...	3.20	all	260	...	240	...	8	...			
	{ 3.20	25.00	all	260	...	240	...	10	9			
					Alloy 6005A13							
T1	...	6.30	all	170	...	100	...	15	...			
T5	...	6.30	all	260	...	215	...	7	...			
	6.30	25.00	all	260	...	215	...	9	8			
T61	...	6.30	all	260	...	240	...	8	...			
	6.30	25.00	all	260	...	240	...	10	9			
					Alloy 6013							
T6	5.00	12.50	all	340	...	315	...	8	...			
	12.50	20.00	all	340	...	315	7			
	20.00	50.00	all	340	...	310	7			
T6511	5.00	12.50	all	340	...	315	...	8	...			
	12.50	20.00	all	340	...	315	7			
	20.00	50.00	all	340	...	310	7			
					Alloy 6020							
T6511	80.00	160.00	all	260	...	240	9			
					Alloy 6041							
T6 ^M	10.00	50.00	all	310	...	275	...	10	9			
T6511 ^M	10.00	50.00	all	310	...	275	...	10	9			
					Alloy 6042							
T5	10.00	12.50	all	260	...	240	...	10	...			
	12.50	50.00	all	290	...	240	9			
T551	10.00	12.50	all	260	...	240	...	10	...			
	12.50	50.00	all	290	...	240	9			
					Alloy 6060							
T51	...	3.20	all	150	...	110	...	8	...			
T61	...	3.20	all	205	...	170	...	8	...			
	3.20	25.00	all	205	...	170	...	10	9			
					Alloy 6061							
O	all		all	...	150	...	110	16	14			
T1	...	16.00	all	180	...	95	...	16	14			

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm ²		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, ^C %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 \sqrt{A})
T4			all		180	...	110	...	16	14
T4510 ^E	all									
T4511 ^E										
T42 ^F	all		all		180	...	85	...	16	14
T51	...	16.00	all		240	...	205	...	8	7
T6, T62 ^F	...	6.30	all		260	...	240	...	8	...
T6510 ^E	6.30	...	all		260	...	240	...	10	9
T6511 ^E										
F ^D	all		all	
					Alloy 6063					
O	all		all		...	130	18	16
T1	12.50	25.00	all	...	115	...	60	...	12	10
T4, T42 ^F	12.50	12.50	all	...	130	...	70	...	14	12
	12.50	25.00	all		125	...	60	12
T5	12.50	25.00	all		150	...	110	...	8	7
T52	...	25.00	all		150	205	110	170	8	7
T54	...	3.20	all		225	...	205	...	8	...
T6,	...	3.20	12.50	all	225	...	205	...	10	...
T62 ^{K,F}	3.20	25.00	all		205	...	170	...	8	...
T65	...	5.00	all		205	...	170	...	10	9
					250	...	230	...	7	...
					Alloy 6064					
T6	5.00	80.00	all		290	...	260	...	10	9
T6511	5.00	80.00	all		290	...	260	...	10	9
					Alloy 6066					
O	all		all		...	200	...	125	16	14
T4			all		275	...	170	...	14	12
T4510 ^E	all									
T4511 ^E										
T42 ^F	all		all		275	...	165	...	14	12
T6			all		345	...	310	...	8	7
T6510 ^E	all									
T6511 ^E										
T62 ^F	all		all		345	...	290	...	8	7
					Alloy 6070					
T6, T62 ^F	...	80.00	...	20 000	330	...	310	...	6	5
					Alloy 6082					
T6	5.00	20.00	all		310	...	260	...	6	8
T6511	20.00	150.00	all		310	...	260	...	8	8
	150.00	200.00	all		280	...	240	...	8	8
					Alloy 6105					
T1	...	12.5	all		170	...	105	...	16	14
T5	...	3.20	all		250	...	240	...	8	...
	3.20	25.00	all		250	...	240	...	10	9
					Alloy 6162					
T5,	...	25.00	all		255	...	235.	...	7	6
T5510 ^E										
T5511 ^E	...	6.30	all							
T6,					260	...	240	...	8	...
T6510 ^E	6.30	12.50	all		260	...	240	...	10	9
T6511 ^E										
					Alloy 6262					

TABLE 2 *Continued*

Temper	Specified Section or Wall Thickness, mm		Area, mm ²		Tensile Strength, MPa		Yield Strength (0.2 % offset), MPa		Elongation, ^C %, min	
	over	incl	over	incl	min	max	min	max	in 50 mm	in 5 × Diameter (5.65 \sqrt{A})
T6										
T6510 ^E	all		all		260	...	240	...	10	9
T6511 ^E										
	Alloy 6351									
T1	...	12.50	...	13 000	180	...	90	...	15	13
T11	...	20.00	all		180	...	110	...	16	14
T4	...	20.00	all		220	...	130	...	16	14
T5	...	6.30	all		260	...	240	...	8	...
	6.30	25.00	all		260	...	240	...	10	9
T51	3.20	25.00	...	13 000	250	...	230	...	10	7
T54	...	12.50	...	13 000	205	...	140	...	10	9
T6	...	3.20	all		290	...	255	...	8	...
	3.20	20.00	all		290	...	255	...	10	9
	Alloy 6360									
T5	...	6.30	all		150	...	110	...	8	...
T6	...	3.20	all		205	...	170	...	8	...
	3.20	6.30	all		205	...	170	...	10	...
	Alloy 6463									
T1	...	12.50	...	13 000	115	...	60	...	12	10
T5	...	12.50	...	13 000	150	...	110	...	8	7
T6,T62 ^F	...	3.20	...	13 000	205	...	170	...	8	...
	3.20	12.50	...	13 000	205	...	170	...	10	9
	Alloy 6560									
T5	2.50	3.20	all		150	...	110	...	8	...
T6	2.50	3.20	all		205	...	170	...	8	...
	Alloy 7005									
T53		20.00	all		345	...	305	...	10	9
	Alloy 7116									
T5	3.20	12.50	all		330	...	290	...	8	7
	Alloy 7129									
T5, T6	...	12.50	all		380	...	340	...	9	8
	Alloy 7075									
O	all	all			275	...	165	10	9	
T6										
T62 ^F	6.30	12.50	all		540	...	485	...	7	...
T6510 ^E		70.00	all		560	...	505	...	7	6
T6511 ^E	70.00	110.00	...	13 000	560	...	495	6
	70.00	110.00 ^L	13 000		560	...	490	6
	110.00	130.00 ^L	...	20 000	540	...	470	5
T73	1.60	6.30	...	13 000	470	...	400	...	7	...
T73510 ^E	6.30	35.00	...	16 000	485	...	420	...	8	7
T73511 ^E		35.00	70.00	...	16 000	475	...	405	...	7
	70.00	110.00 ^L	...	13 000	470	...	395	6
	70.00	110.00 ^L	13 000	20 000	450	...	380	6
T76										
T76510 ^E	1.25	3.20	all		500	...	435	...	7	...
T76511 ^E		3.20	6.30	...	510	...	440	...	7	...
	3.20	6.30	...	13 000	510	...	440	...	7	...
	6.30	12.50	...	13 000	515	...	450	...	7	6
	12.50	25.00	...	13 000	515	...	450	6
	25.00	50.00	...	13 000	515	...	450	6
	50.00	75.00	...	13 000	510	...	440	6
	75.00	100.00	...	13 000	510	...	435	6
F ^D	all	all		
O	all	...	20 000		275	...	165	10	9	