



## Designation: **D5178 – 98 (Reapproved 2008) D5178 – 13**

# Standard Test Method for Mar Resistance of Organic Coatings<sup>1</sup>

This standard is issued under the fixed designation D5178; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers the determination of the mar resistance on smooth, flat surfaces. Results are expressed in terms of force-to-mar films of organic coatings such as paint, varnish, and lacquer when applied to smooth, flat planar panel surfaces.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D609 Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products](#)

[D823 Practices for Producing Films of Uniform Thickness of Paint, Varnish, and Related Products on Test Panels](#)

[D1005 Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers](#)

[D1186 Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base \(Withdrawn 2006\)](#)<sup>3</sup>

[D1400 Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base \(Withdrawn 2006\)](#)<sup>3</sup>

[D2691 Method for Microscopical Measurement of Dry Film Thickness of Coatings on Wood Products \(Withdrawn 1992\)](#)<sup>3</sup>

## 3. Terminology

3.1 *Definitions:*

3.1.1 *mar resistance, n*—the ability of a coating to resist damage caused by light abrasion. As just defined, it is a resistance of the surface of the coating to permanent deformation, resulting from the application of a dynamic mechanical force.

## 4. Summary of Test Method

4.1 The materials under test are applied at uniform thickness to flat panels of uniform surface texture. After drying/curing, the mar resistance is determined by pushing the panels beneath a rounded stylus or loop that is loaded in increasing amounts until the coating is marred.

## 5. Significance and Use

5.1 In some situations, marring of coatings applied to substrates under typical use conditions is unacceptable. This test method has been found useful in differentiating the degree of marring of coatings on substrates. It is most useful in providing relative ratings for a series of coated panels exhibiting significant differences in marring.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.23 on Physical Properties of Applied Paint Films.

Current edition approved July 1, 2008; May 15, 2013. Published July 2008; May 2013. Originally approved in 1991. Last previous edition approved in 2002; 2008 D5178 – 98 (2002); (2008). DOI: 10.1520/D5178-98R08; 10.1520/D5178-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).