



Designation: D5726 – 98 (Reapproved 2013)

# Standard Specification for Thermoplastic Fabrics Used in Hot-Applied Roofing and Waterproofing<sup>1</sup>

This standard is issued under the fixed designation D5726; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers thermoplastic fabrics such as polyester, polyester/polyamide bicomponent, or composites with fiber glass or polyester scrims that can be used during the construction of hot-applied roofing and waterproofing.

1.2 This specification is intended as a material specification. Issues regarding the suitability of specific roof constructions or application techniques are beyond the scope of this specification.

1.3 The specified tests and property values used to characterize the respective fabrics are intended to establish minimum properties. In-place system design criteria or performance attributes are factors beyond the scope of this material specification.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D123 Terminology Relating to Textiles](#)

[D1079 Terminology Relating to Roofing and Waterproofing](#)

[D1117 Guide for Evaluating Nonwoven Fabrics](#) (Withdrawn 2009)<sup>3</sup>

[D1776 Practice for Conditioning and Testing Textiles](#)

[D1777 Test Method for Thickness of Textile Materials](#)

[D4830 Test Methods for Characterizing Thermoplastic Fabrics Used in Roofing and Waterproofing](#)

[D5035 Test Method for Breaking Force and Elongation of Textile Fabrics \(Strip Method\)](#)

[D5733 Test Method for Tearing Strength of Nonwoven Fabrics by the Trapezoid Procedure](#) (Withdrawn 2008)<sup>3</sup>

[E1 Specification for ASTM Liquid-in-Glass Thermometers](#)

2.2 *Other Standard:*

[AATCC Test Set No. 128, Wrinkle Recovery Test](#)<sup>4</sup>

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminologies [D1079](#) and [D123](#).

## 4. Classification

4.1 The thermoplastic fabrics covered by this specification are of the following general constructions and compositions. Each is a separate class or type, differentiated by polymer type, a combination of polymers, or the manufacturing process, or some combination thereof:

4.1.1 *Type I*—Polyester spunbonded with resin, unneeded;

4.1.2 *Type II*—Polyester spunbonded with resin, needed;

4.1.3 *Type III*—Polyester mat plus fiber glass scrim and resin; and

4.1.4 *Type IV*—Polyester core/polyamide sheath bicomponent spunbonded.

## 5. Materials and Manufacture

5.1 The fabric shall be a uniform, thin, porous mat of the primary thermoplastic polymer, with or without the addition of reinforcing stranded glass or thermoplastic yarns. Chemically bonding with a water-resistant resin or thermally bonding with other thermoplastic polymers shall be permitted.

## 6. Physical Properties, Thickness, and Mass

6.1 Fabrics shall conform to the thickness, mass, and physical properties presented in [Table 1](#).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.04 on Felts, Fabrics and Bituminous Sheet Materials.

Current edition approved May 1, 2013. Published May 2013. Originally approved in 1995. Last previous edition approved in 2005 as D5726 – 98 (2005). DOI: 10.1520/D5726-98R13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American Association of Textile Chemists and Colorists (AATCC), One Davis Dr., P.O. Box 12215, Research Triangle Park, NC 27709-2215.

**TABLE 1 Physical Properties of Thermoplastic Fabrics for Use in Hot-Applied Roofing and Waterproofing**

Properties	Types			
	I	II	III	IV
Unit mass, nominal, g/m <sup>2</sup> (oz/yd <sup>2</sup> ) (lb/100 ft <sup>2</sup> )	155 (4.6) (3.2)	140 (4.1) (2.8)	125 (3.7) (2.6)	327 (9.6) (6.7)
Thickness, mm (mils), min	0.42 (16)	0.51 (20)	0.41 (16)	0.92 (36)
Breaking load, kN/m (lbf/in.), min, MD and CD	8.8 (50)	5.2 (30)	20.5 (117)	14.9 (85)
Elongation, % min, MD and CD	46	25	3.3	34
Trapezoid tearing strength, N (lbf), min, MD and CD	155 (35)	107 (24)	31 (7)	256 (57)
Puncture strength, N (lbf), min	231 (52)	169 (38)	53 (12)	316 (71)
Appearance rating (AATCC Test Set No. 128), pass (4 and 5) and fail (1 to 3)	Pass	Pass	Pass	Pass
Heat distortion stability, % change max, MD and CD	2	2	0.2	2

## 7. Unit Mass

7.1 Determine the unit mass of the fabric using the procedures described in Test Methods **D1117**.

## 8. Workmanship, Finish, and Appearance

8.1 The finished material shall be free of visible defects such as ragged or untrue edges, folds, creases, wrinkles, tears, and holes.

## 9. Sampling

9.1 Sample the material and determine the properties enumerated in this specification in accordance with the test procedures referenced and presented herein.

## 10. Thickness

10.1 Determine the thickness of the fabric using the procedures described in Test Method **D1777**.

## 11. Breaking Load and Elongation

11.1 Determine the breaking load and elongation by the cut strip method described in Test Methods **D4830** and **D5035**. The preferred SI unit for breaking load is kN/m.

## 12. Trapezoid Tearing Strength

12.1 Determine the trapezoid tearing strength using the procedures described in Test Method **D5733**.

## 13. Puncture Strength

13.1 Determine the puncture strength using the procedures described in Test Methods **D4830**.

## 14. Heat Distortion/Stability

14.1 *Scope*—This test method, which uses hot silicone oil, is a procedure for simulating the distortion that may occur with the laying of a fabric roofing ply into hot bitumen during the construction of a hot-applied built-up roofing membrane.

14.2 *Summary of Test Method*—Fabric specimens are laid into hot silicone oil at 260°C (500°F), allowed to cool to room temperature, and then removed and measured for percent shrinkage and rated visually for distortion.

14.3 *Significance and Use*—Not all thermoplastic fabrics are suitable for hot-applied built-up roofing. This test procedure is designed to simulate hot-applied built-up application

and to identify those thermoplastic fabrics that are suitable and not susceptible to excessive shrinkage or distortion, or both.

### 14.4 Apparatus and Materials:

14.4.1 *Stainless Steel Container*, appropriately sized, used to heat the silicone oil.

14.4.2 *Heating Mantle*, used in conjunction with the container and capable of heating the silicone oil adequately.

14.4.3 *Thermometer*, graduated in 1°C (2°F) intervals and including the range of 260 to 288°C (500 to 550°F) on its scale, such as ASTM No. 2F-86 (see Specification **E1**).

14.4.4 *Stainless Steel Ladle*, with a capacity of 0.09 L (3 oz).

14.4.5 *Aluminum Baking Pans*, measuring approximately 273-mm long by 178-wide by 25-mm deep (10.75 by 7 by 1 in.).

14.4.6 *Silicone Oil*, Dow Corning 710 Fluid<sup>5</sup> or an equivalent.

14.4.7 *Safety Equipment*, which includes long arm rubber gloves or hot gloves, an apron, and face shield, which are recommended to help prevent possible injury.

14.4.8 *Insulation Board*, a minimum 25-mm (1-in.) thickness, to be used beneath the metal pans as a method of reducing excessive heat loss when pouring the hot silicone oil just prior to introduction of the fabric sample.

14.4.9 The *AATCC Test Set No. 128, Wrinkle Recovery Test*, used to visually evaluate and rate the fabric distortion after testing.

### 14.5 Preparation of Specimens:

14.5.1 Each test specimen shall be 254-mm (10-in.) long and 152-mm (6-in.) wide, with the length dimension taken parallel to the machine direction of the fabric.

14.5.2 Cut five specimens spaced uniformly across the fabric sample. No specimen shall be taken within 51 mm (2 in.) of any selvage edge of the fabric.

14.5.3 Using an indelible marker, mark a 25-mm (1-in.) border from each outside edge, forming a block that will be used for measurement purposes.

14.6 *Conditioning*—Condition the test specimens using the procedures described in Practice **D1776**.

### 14.7 Procedure:

<sup>5</sup> Silicone oil, available from Dow Corning Corp., South Saginaw Road, Midland, MI 48686, has been found suitable for this purpose.