



# Standard Specification for Polyethylene (PE) Gas Pressure Pipe, Tubing, and Fittings<sup>1</sup>

This standard is issued under the fixed designation D2513; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers requirements and test methods for material dimensions and tolerances, hydrostatic burst strength, chemical resistance, and rapid crack resistance of polyethylene pipe, tubing, and fittings for use in fuel gas mains and services for direct burial and reliner applications. The pipe and fittings covered by this specification are intended for use in the distribution of natural gas. Requirements for the qualifying of polyethylene systems for use with liquefied petroleum gas are also covered.

1.1.1 This specification does not cover threaded pipe. Design considerations are discussed in [Appendix X1](#). In-plant quality control programs are specified in [Annex A1](#) and [Annex A2](#).

1.1.2 See Specification [F2619/F2619M](#) for polyethylene piping for pressure or non-pressure oil and gas producing applications to convey fluids such as oil, dry or wet gas, multiphase fluids, and non-potable oilfield water.

1.2 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 The following is an index of the annexes and appendix in this specification:

Annex	Subject
<a href="#">Annex A1</a>	In-Plant Quality Control for all materials up to 12 in.
<a href="#">Annex A2</a>	In-Plant Quality Control for PE materials 14 in. and larger.
Appendixes	Subject
<a href="#">Appendix X1</a>	Design Consideration

1.5 The following precautionary caveat pertains only to the test method portion, Section 6, of this specification. *This standard does not purport to address all of the safety concerns,*

*if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

2.1.1 *Terminology:*

[D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

[F412 Terminology Relating to Plastic Piping Systems](#)

2.1.2 *Test Methods for:*

[D638 Test Method for Tensile Properties of Plastics](#)

[D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer](#)

[D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure](#)

[D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings](#)

[D2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings](#)

[D2290 Test Method for Apparent Hoop Tensile Strength of Plastic or Reinforced Plastic Pipe](#)

[D2837 Test Method for Obtaining Hydrostatic Design Basis for Thermoplastic Pipe Materials or Pressure Design Basis for Thermoplastic Pipe Products](#)

[F1473 Test Method for Notch Tensile Test to Measure the Resistance to Slow Crack Growth of Polyethylene Pipes and Resins](#)

2.1.3 *Practices for:*

[D543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents](#)

[D618 Practice for Conditioning Plastics for Testing](#)

[D1435 Practice for Outdoor Weathering of Plastics](#)

[D1898 Practice for Sampling of Plastics \(Withdrawn 1998\)](#)<sup>3</sup>

[D2774 Practice for Underground Installation of Thermoplastic Pressure Piping](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.60 on Gas.

Current edition approved Feb. 1, 2013. Published June 2013. Originally approved in 1966. Last previous edition approved in 2012 as D2513 – 12a<sup>ε1</sup>. DOI: 10.1520/D2513-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

- D2565** Practice for Xenon-Arc Exposure of Plastics Intended for Outdoor Applications
- F2620** Practice for Heat Fusion Joining of Polyethylene Pipe and Fittings
- G155** Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials
- 2.1.4 *Specification for:*
- D2683** Specification for Socket-Type Polyethylene Fittings for Outside Diameter-Controlled Polyethylene Pipe and Tubing
- D3261** Specification for Butt Heat Fusion Polyethylene (PE) Plastic Fittings for Polyethylene (PE) Plastic Pipe and Tubing
- D3350** Specification for Polyethylene Plastics Pipe and Fittings Materials
- F1055** Specification for Electrofusion Type Polyethylene Fittings for Outside Diameter Controlled Polyethylene and Crosslinked Polyethylene (PEX) Pipe and Tubing
- F1563** Specification for Tools to Squeeze-off Polyethylene (PE) Gas Pipe or Tubing
- F2138** Specification for Excess Flow Valves for Natural Gas Service
- F2619/F2619M** Specification for High-Density Polyethylene (PE) Line Pipe
- F2897** Specification for Tracking and Traceability Encoding System of Natural Gas Distribution Components (Pipe, Tubing, Fittings, Valves, and Appurtenances)
- 2.2 *ANSI Standards:*
- B 16.40** Manually Operated Thermoplastic Gas Shutoffs and Valves in Gas Distribution Systems<sup>4</sup>
- B 31.8** Gas Transmission and Distribution Piping Systems<sup>4</sup>
- 2.3 *Federal Specifications:*
- Fed. Std. No. 123** Marking for Shipment (Civil Agencies)<sup>5</sup>
- OPS 49 CFR Part 192** Title 49, Code of Federal Regulations<sup>5</sup>
- 2.4 *Military Standards:*
- MIL-STD-129** Marking for Shipment and Storage<sup>5</sup>
- MIL-STD-1235** (ORD) Single- and Multi-Level Continuous Sampling Procedures and Tables for Inspection by Attributes
- 2.5 *ISO Standards*<sup>6</sup>:
- ISO 4437** Buried polyethylene (PE) pipes for the supply of gaseous fuels—Metric series—Specifications
- ISO 9080** Thermoplastics Pipes for the Transport of Fluids—Methods of Extrapolation of Hydrostatic Stress Rupture Data to Determine Long-Term Hydrostatic Strength of Thermoplastic Pipe Materials
- ISO 12162** Thermoplastic Materials for Pipes and Fittings for Pressure Applications—Classification and Designation—Overall Service (Design) Coefficient

- ISO 13477** Thermoplastics pipes for the conveyance of fluids – Determination of resistance to rapid crack propagation (RCP) – Small scale steady-state test (S4 test)
- ISO 13478** Thermoplastics pipe for the conveyance of fluids – Determination of resistance to rapid crack propagation (RCP) – Full-scale test (FST)
- 2.6 *Plastic Pipe Institute*<sup>7</sup>
- PPI TR-3** HDB/HDS /PDB/ SDB/MRS Policies
- PPI TR-4** HDB/HDS/SDB/PDB/MRS Listed Materials
- PPI TR-33** Generic Butt Fusion Joining for Polyethylene Gas Pipe
- PPI TR-41** Generic Saddle Fusion Joining Procedure for Polyethylene Gas Piping<sup>7</sup>
- PPI TN-30/2006** Requirements for the Use of Rework Materials in Polyethylene Gas Pipe<sup>7</sup>
- PPI TR-9** Recommended Design Factors and Design Coefficients for Thermoplastic Pressure pipe
- 2.7 *Other Documents:*<sup>8</sup>
- National Fire Protection Association: NFPA 58** Storage and Handling Liquefied Petroleum Gases

### 3. Terminology

- 3.1 *Definitions*—Definitions are in accordance with Terminology **F412**, and abbreviations are in accordance with Terminology **D1600**, unless otherwise specified.
- 3.2 The gas industry terminology used in this specification is in accordance with ANSI B31.8 or OPS 49 CFR Part 192, unless otherwise indicated.
- 3.3 The term *pipe* used herein refers to both pipe and tubing unless specifically stated otherwise.
- 3.4 *re-rounding equipment*—equipment used to reform the pipe and permanently reduce ovality to 5 % or less.
- 3.5 *rounding equipment*—equipment, devices, clamps, and so forth, used to temporarily hold the pipe round while out-of-roundness measurements are made, or a joining procedure (heat fusion, electrofusion, or mechanical) is performed.
- 3.6 *pipe material designated code*—the pipe material designation code shall consist of the abbreviation for the type of plastic (PE) followed by Arabic numerals which describe the short term properties in accordance with applicable Specification **D3350**, the hydrostatic design stress for water at 73.4°F (23°C) in units of 100 psi with any decimal figures dropped. Where the hydrostatic design stress code contains less than two figures, a zero is used before the number. Thus, a complete material designation code shall consist of PE and four figures for PE materials. For example, PE2708 is a grade PE27 polyethylene with an 800psi design stress for water at 73.4°F (23°C). The hydrostatic design stresses for gas are not used in this designation code.
- 3.7 *dimension ratio (DR)*—the ratio of pipe diameter to wall thickness. It is calculated by dividing the specified outside diameter of the pipe, in inches (mm), by the minimum specified

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

<sup>5</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

<sup>6</sup> Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, Case postale 56, CH-1211, Geneva 20, Switzerland, <http://www.iso.ch>.

<sup>7</sup> Available from Plastics Pipe Institute (PPI), 105 Decker Court, Suite 825, Irving, TX 75062, <http://www.plasticpipe.org>.

<sup>8</sup> Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

wall thickness, in inches (mm). The standard dimension ratio (SDR) is a common numbering system which is derived from the ANSI preferred number series R 10.

3.8 *toe-in*—a small reduction of the outside diameter at the cut end of a length of thermoplastic pipe.

**4. Materials**

4.1 *General*—The PE used to make pipe and fittings shall be PE or reworked PE (see 4.2 and 4.4) and shall have a Plastics Pipe Institute (PPI) long-term hydrostatic design stress and hydrostatic design basis rating.

4.2 *Rework Material*—Clean rework material of the same commercial designation, generated from the manufacturer’s own pipe and fitting production shall not be used unless the pipe and fitting produced meet all the requirements of this specification. The use of these rework materials shall be governed by the requirements of 4.3 and PPI TN-30/2006. In pipe, rework materials shall be limited to a maximum of 30 % by weight.

NOTE 1—The requirements for rework materials herein are intended to incorporate prudent specifications to ensure that the potential for contamination in gas piping products, that meet this specification, is reduced to the extent possible. It is imperative to emphasize that rework materials have not been identified as the cause of any field failures. The requirements for rework materials were developed by the consensus of interested parties including product manufacturers, gas utility companies, and regulatory agencies.

4.3 *Documentation*—A documentation system to allow for traceability of raw materials including percentage and material classification (or designation, if applicable) of rework materials used in the manufacture of the pipe product meeting the requirements of this specification shall exist and be supplied to the purchaser, if requested.

4.4 *Classification*—Polyethylene materials suitable for use in the manufacture of pipe and fittings under this specification shall meet Table 1 requirements for the applicable pipe material designation code.

NOTE 2—References and material descriptions for PE 2306, PE 2406, PE 2606, PE 3306, PE 3406, PE 3408, PE 3608, PE 3710, and PE 4608 have been removed from D2513. Elimination of these materials does not affect the pipelines that are in service. They can still be used for gas distribution. The main reason for removing these materials from this

standard is to reflect the current state of the art in PE gas distribution piping.

4.5 *Slow Crack Growth Resistance*—Use Test Method F1473 on compression molded plaques at a stress of 2.4 MPa based on the unnotched area and a test temperature of 80°C. Notch depth shall be in accordance with Table 1 in Test Method F1473. Materials shall meet the Slow Crack Growth Resistance requirements in Table 1.

4.6 *Additive Classes*—Polyethylene material compounds shall meet Specification D3350 code C or E. Code C material compounds shall have 2 to 3 percent carbon black. Code E material compounds shall be yellow with UV stabilizer.

4.7 *Thermal Stability*—The PE material shall contain sufficient antioxidant so that the minimum induction temperature shall be 428°F (220°C) when tested in accordance with Specification D3350. The sample shall be representative of the cross section of the pipe or fittings.

4.8 *Hydrostatic Design Basis (HDB) Substantiation* —The HDB for PE materials at 73°F (23°C) shall be substantiated to be linear to 50 years as per Test Method D2837, Section 5.7.

NOTE 3—The long-term hydrostatic strength at 50 years in accordance with Test Method D2837 is not to be used for any pressure rating calculations. The MAOP is still calculated using the HDB obtained from Test Method D2837 long-term hydrostatic strength at 100 000 h. PE compounds with a thermoplastic pipe material designation code of PE 2708 and PE 4710 as well as those compounds denoted in PPI TR-4 with an asterisk (\*) meet the substantiation requirement of Test Method D2837.

4.9 *Resistance to Rapid Crack Propagation (RCP) for Material*—The PE material classification (formulation) used in the manufacture of pipe and fittings under this specification shall be tested for resistance to failure by RCP in accordance with the procedures set forth in ISO 13477 (S4 Test) or ISO 13478 (Full Scale Test (FST)). The data obtained shall be made available upon request without limitations on disclosure, and shall not subsequently be subject to disclosure limitations when used by others. The values obtained are applicable to all pipes with the wall thickness of the pipe tested and all thinner wall pipes. In case of conflict, the RCP results of ISO 13478 shall apply.

NOTE 4—While S4 or FST testing of any combination of outside diameter and SDR is permitted in fulfillment of the requirement for testing

**TABLE 1 Polyethylene Compound Requirements**

	Pipe Material Designation Code	
	PE 2708	PE 4710
Density Cell Classification per Specification D3350	2	4
SCG Resistance Cell Classification per Specification D3350	7	7
HDS for water at 73°F (23°C) per Test Method D2837 and PPI TR-3, psi (MPa)	800 (5.5)	1000 (6.9)
Color and UV Stabilizer Code per Specification D3350	C or E	C or E
Melt flow rate per Test Method D1238, g/10 min	≤0.40 Cond. 190/2.16 or ≤20 Cond. 190/21.6	≤0.15 Cond. 190/2.16 or ≤20 Cond. 190/21.6
HDB at 73°F (23°C) per Test Method D2837 and PPI TR-3, psi (MPa)	1250 (8.6)	1600 (11.0)
Minimum HDB at 140°F (60°C) per Test Method D2837 and PPI TR-3, psi (MPa)	800 (5.5)	800 (5.5)

PE material resistance to RCP, S4 testing of SDR 9 or SDR 11 PE pipe specimens is currently the most common industry practice.

NOTE 5—Caution should be exercised in applying the RCP test results obtained on one SDR or DR of pipe across a series of pipe SDR's or DR's produced from the same PE material classification (formulation). Industrial research to clarify the relationships between FST and S4 testing is ongoing at this time, particularly as it relates to the applicability of RCP test results obtained on one SDR or DR of pipe to other SDR's or DR's of pipe produced from the same PE material classification (formulation). Consult the resin manufacturer regarding the applicability of RCP test results across diameters or SDR's, or both. Additional information regarding the use of RCP data is presented in ISO 4437.

4.10 *UV Resistance*—PE materials shall be Code C or E as defined in Specification **D3350**. Code C material shall contain 2 to 3 percent well dispersed carbon black, and due to the absorptive properties of the carbon black, is considered to be stabilized against deterioration from unprotected exposure to UV for not less than 10 years. Code E material shall be stabilized and protected against deterioration from unprotected UV exposure for not less than 3 years.

4.10.1 PE compounds designated as Code C containing 2 to 3% carbon black shall be considered stabilized against deterioration for not less than 10 years without the need for additional testing.

4.10.2 PE compounds designated as Code E shall be considered stabilized against deterioration from unprotected exposure to UV for not less than 3 years when meeting the following criteria following exposure to actual outdoor (natural sunlight) weathering for up to 3 years in accordance with Practice **D1435** or accelerated weathering in accordance with Practice **D2565** and Practice **G155** for the equivalent of at least 3 years natural sunlight: (a) all tensile bar specimens tested in accordance with Test Method **D638** shall have an elongation at break value greater than 400% indicating the equivalency of the PE material before and after UV exposure against the elongation at break requirement in Specification **D3350**; and (b) all tensile bar specimens tested in accordance with Test Method **D638** shall retain a minimum of 50% of their original elongation at break values. Test data shall be made available from the manufacturer upon request.

NOTE 6—Studies have shown HDPE exposed to Xenon Arc via Practice **G155**-A Cycle 1 give approximately 4.4 times the acceleration to outdoor Florida exposure. Therefore approximately 2000 hours Xenon Arc testing would equal about 1-year outdoor exposure in Florida or 2-years in southern Canada.

NOTE 7—The determination for UV resistance is often based on measuring the ductility properties of the pipe material exposed to artificial weathering. These requirements and test methods are based on expected UV exposure levels in North America. Alternate requirements and alternate determination methods may be appropriate in other regions of the world. As an example ISO 4437 standard requires a minimum resistance to an accumulation of 3.6GJ for non-black polyethylene materials.

4.11 *Qualification for LPG Service*—Materials that qualify for natural gas service and that carry a recommended HDB for 140°F in accordance with **5.6**, also qualify for LPG service without the need for further testing.

NOTE 8—The terms LPG and LPG gas are synonymous and only apply to a particular kind of fuel gas. For compositions and properties of LPG gases see NFPA 58, Appendix B.

## 5. Requirements

5.1 *General*—Pipe shall be supplied in either coils or straight lengths. Any pipe supplied in coils must meet the same requirements before and after coiling.

5.2 *Workmanship*—The pipe and fittings shall be homogeneous throughout and free of visible cracks, holes, foreign inclusion, blisters, and dents, or other injurious defects. The pipe and fittings shall be as uniform as commercially practicable in color, opacity, density, and other physical properties.

5.3 *Pipe and Tubing Dimensions and Tolerances:*

5.3.1 *Dimension*—The dimensions shall be specified by wall thickness and outside diameter.

5.3.1.1 *Diameters*—The outside diameter shall meet the requirements given in **Table 2** or **Table 3** when measured in accordance with **6.5**.

5.3.1.2 *Toe-In*—When measured in accordance with **6.5.1.1**, the outside diameter at the cut end of the pipe shall not be more than 1.5 % smaller than the undistorted outside diameter. Measurement of the undistorted outside diameter shall be made no closer than 1.5 pipe diameters or 11.8 in. (300 mm), whichever distance is less, from the cut end of the pipe. Undistorted outside diameter shall meet the requirements of **Table 2** or **Table 3**.

5.3.1.3 *Wall Thickness*—The wall thickness shall be as specified in **Table 3** or **Table 4** when measured in accordance with **6.5.1.2**. The minimum wall thickness at any point of measurement shall be not less than the minimum wall thickness specified in **Table 3** or **Table 4**.

5.3.1.4 *Wall Thickness Eccentricity Range*—The wall thickness eccentricity range shall be within 12 % when measured in accordance with **6.5.1.3**.

5.3.1.5 *Ovality*—The ovality (cross section) of 3 in. IPS (88.9 mm) and smaller pipe shall not exceed 5 % when measured in accordance with **6.5.3**. Measurements of coiled pipe shall be made on a sample cut from the coil, and in case of disagreement, conditioned per **6.3**.

NOTE 9—Other factors, that is, installation compaction, static soil loading, and dynamic vehicular loads may increase the ovality; therefore, 5 % was chosen as the limit for the amount contributed by manufacturing, packing, in-plant storage, and shipping. For further information, see **(1)**<sup>9</sup>.

(1) Before or during installation, coiled pipe larger than 3 in. IPS (88.9 mm) shall be processed by the installer through re-rounding equipment that corrects ovality to 5 % or less.

NOTE 10—Ovality is a packaging condition that occurs when roundable pipe is wound into a coil—the pipe flattens out as it is coiled. Ovality is corrected when joining equipment is applied to roundable pipe, or by field processing roundable pipe through re-rounding and straightening equipment during installation.

5.3.1.6 *Length*—The pipe shall be supplied in straight lengths or coils as agreed upon between the manufacturer and the purchaser. The length shall not be less than the minimum length agreed upon when corrected to 73°F (23°C).

5.3.1.7 When sizes other than those listed in **Table 2**, **Table 3** or **Table 5** are used, tolerances shall be: for outside diameter,

<sup>9</sup> The boldface numbers in parentheses refer to a list of references at the end of this standard.

TABLE 2 Outside Diameters and Tolerances for Plastic Pipe, in. (mm)

Nominal Pipe Size	Outside Diameter	Tolerance	Maximum Out-of-Roundness			
			SDR 32.5	SDR 26	SDR 21	SDR 17 SDR 13.5 SDR 11
½	0.840 (21.3)	±0.004 (±0.102)	...	...	0.03(0.762)	0.016(0.406)
¾	1.050 (26.7)	±0.004 (±0.102)	...	...	0.03(0.762)	0.02(0.508)
1	1.315 (33.4)	±0.005 (±0.127)	...	...	0.03(0.762)	0.02(0.508)
1¼	1.660 (42.1)	±0.005 (±0.127)	...	...	0.03(0.762)	0.024(0.61)
1½	1.900 (48.3)	±0.006 (±0.152)	...	...	0.06(1.524)	0.024(0.61)
2	2.375 (60.3)	±0.006 (±0.152)	...	...	0.06(1.524)	0.024(0.61)
2½	2.875 (73.0)	±0.007 (±0.179)	...	...	0.06(1.524)	0.03(0.762)
3	3.500 (88.9)	±0.008 (±0.203)	...	...	0.06(1.524)	0.03(0.762)
3½	4.000 (101.6)	±0.008 (±0.203)	...	...	0.1(2.5)	0.03(0.762)
4	4.500 (114.3)	±0.009 (±0.229)	...	...	0.1(2.5)	0.03(0.762)
5	5.563 (141.3)	±0.010 (±0.254)	...	...	0.1(2.5)	0.06(1.524)
6	6.625 (168.3)	±0.011 (±0.279)	0.12(3)	0.11(2.74)	0.1(2.5)	0.07(1.778)
8	8.625 (219.1)	±0.013 (±0.330)	0.24(6.1)	0.16(4.06)	0.12(3)	0.08(2.04)
10	10.750 (273.0)	±0.015 (±0.381)	0.24(6.1)	0.2(5.08)	0.14(3.58)	0.1(2.5)
12	12.750 (323.8)	±0.017 (±0.432)	0.28(7.12)	0.2(5.08)	0.14(3.58)	0.1(2.5)
14	14.000 (355.6)	±0.063 (±1.60)	0.308(7.82)	0.224(5.68)	0.154(3.91)	0.112(2.84)
16	16.000 (406.4)	±0.072 (±1.83)	0.352(8.94)	0.256(6.50)	0.176(4.47)	0.128(3.25)
18	18.000 (457.2)	±0.081 (±2.06)	0.396(10.05)	0.288(7.31)	0.198(5.02)	0.144(3.65)
20	20.000 (508.0)	±0.090 (±2.29)	0.44(11.1)	0.32(8.12)	0.22(5.58)	0.16(4.06)
22	22.000 (558.8)	±0.099 (±2.51)	0.484(12.29)	0.352(8.94)	0.242(6.14)	0.176(4.47)
24	24.000 (609.6)	±0.108 (±2.74)	0.528(13.41)	0.384(9.75)	0.264(6.70)	0.192(4.87)

TABLE 3 PE Tubing-Diameters, Wall Thicknesses, and Tolerances, in. (mm)

Nominal Tubing Size (CTS)	Outside Diameter	Tolerance	Minimum Wall Thickness	Wall Thickness Tolerance
¼	0.375 (9.52)	±0.004 (±0.10)	0.062 (1.58)	+0.006 (+0.15)
¾	0.500 (12.7)	±0.004 (±0.10)	0.062 (1.58)	+0.006 (+0.15)
½	0.625 (15.9)	±0.004 (±0.10)	0.062 (1.58)	+0.006 (+0.15)
½	0.625 (15.9)	±0.004 (±0.10)	0.090 (2.27)	+0.009 (+0.23)
½	0.625 (15.9)	±0.004 (±0.10)	0.104 (2.64)	+0.010 (+0.25)
¾	0.875 (22.2)	±0.004 (±0.10)	0.062 (1.58)	+0.006 (+0.15)
¾	0.875 (22.2)	±0.004 (±0.10)	0.077 (1.95)	+0.008 (+0.20)
¾	0.875 (22.2)	±0.004 (±0.10)	0.090 (2.27)	+0.009 (+0.23)
1	1.125 (28.6)	±0.005 (±0.13)	0.062 (1.58)	+0.007 (+0.18)
1	1.125 (28.6)	±0.005 (±0.13)	0.090 (2.27)	+0.011 (+0.28)
1	1.125 (28.6)	±0.005 (±0.13)	0.099 (2.51)	+0.012 (+0.31)
1	1.125 (28.6)	±0.005 (±0.13)	0.101 (2.56)	+0.012 (+0.31)
1	1.125 (28.6)	±0.005 (±0.13)	0.121 (3.07)	+0.015 (+0.38)
1¼	1.375 (34.9)	±0.005 (±0.13)	0.062 (1.58)	+0.007 (+0.18)
1¼	1.375 (34.9)	±0.005 (±0.13)	0.090 (2.27)	+0.011 (+0.28)
1¼	1.375 (34.9)	±0.005 (±0.13)	0.121 (3.07)	+0.015 (+0.38)
1¾	1.875 (47.6)	±0.006 (±0.15)	0.062 (1.58)	+0.007 (+0.18)

use same tolerance of next smaller size; for wall thickness, use same tolerance percentage as shown in the tables.

5.4 *Minimum Hydrostatic Burst Pressure/Apparent Tensile Strength (Quick Burst)*—The pipe or system shall fail in a ductile manner when tested in accordance with Test Method D1599. For pipe sizes above 4-in. nominal diameter, the testing lab shall be allowed to replace the quick burst test (Test Method D1599) by the apparent ring tensile strength test (Test Method D2290). The minimum apparent tensile strength at yield when determined in accordance with 6.8 shall be 2520 psi (17.4 MPa) for PE 2708 pipe or 2900 psi (20.0 MPa) for PE 4710 pipe.

NOTE 11—The requirements in 5.3.1.1 and 5.3.1.3 are for laboratory proof testing only and should not be interpreted as applicable to on-site testing for acceptance of installed systems larger than 12 in. See

appropriate installation standards or manufacturer’s recommendations for field test procedures.

5.5 *Chemical Resistance*—The pipe and fittings shall not increase in weight more than 0.5 % (1.0 % for toluene in methanol). Where the test specimen is a pipe ring, the material shall not change more than ±12 % in apparent tensile yield strength when measured in accordance with 6.9. Where the test specimen is a plaque, the material shall not change more than ±12 % in tensile strength at yield when measured in accordance with Test Method D638.

NOTE 12—This pipe test is only an indication of what will happen as a result of short term exposure to these chemicals. For longterm results, additional testing is required.

5.6 *Melt Index*—Melt index is the flow rate of PE material when measured in accordance with Test Method D1238, condition 190/2.16 (formerly Condition E). Materials that record zero flow under condition 190/2.16 shall be measured in accordance with condition 190/21.6 (formerly condition F). The melt index of pipe/fitting shall meet the designated category in Table 5. The sample shall be representative of the cross section of the pipe or fitting and diced to an appropriate size by a method not producing heat.

5.7 *Sustained Pressure 73°F (23°C)*—Fittings shall not fail in less than 1000 h when tested in accordance with Test Method D1598. For PE 2708 materials, the stress shall be 1320 psi, for PE 4710 materials, the stress shall be 1600 psi.

5.8 *Elevated Temperature Service*—piping materials intended for use at temperatures above 100°F (38°C) shall have the PPI hydrostatic design basis (HDB) determined at the specific temperature in accordance with Test Method D2837. The 100 000-h intercept (long-term strength) shall be categorized in accordance with Table 5 and be listed as the “hydrostatic design basis of XXX psi at XXX °F (C°) for (compound name).”

**TABLE 4 Wall Thicknesses and Tolerances for Plastic Pipe, in (mm)<sup>A,B</sup>**

Nominal Pipe Size (IPS)	DR <sup>C</sup>	Minimum	Tolerance
1/2	<i>D</i>	0.062 (1.58)	+0.007 (+0.178)
	11.0	0.076 (1.93)	+0.009 (+0.229)
	9.33	0.090 (2.29)	+0.011 (+0.279)
3/4	<i>D</i>	0.090 (2.29)	+0.011 (+0.279)
	11.0	0.095 (2.41)	+0.011 (+0.279)
	Sch 40	0.113 (2.87)	+0.014 (+0.356)
1	<i>D</i>	0.090 (2.29)	+0.011 (+0.279)
	13.5	0.097 (2.46)	+0.012 (+0.305)
	11.0	0.120 (3.05)	+0.014 (+0.356)
	9.9	0.133 (3.38)	+0.016 (+0.406)
	9.33	0.140 (3.56)	+0.017 (+0.432)
1 1/4	<i>D</i>	0.090 (2.29)	+0.011 (+0.279)
	17.0	0.098 (2.49)	+0.012 (+0.305)
	13.5	0.123 (3.12)	+0.015 (+0.381)
	Sch 40	0.140 (3.56)	+0.017 (+0.432)
	11.0	0.151 (3.84)	+0.018 (+0.457)
	10.0	0.166 (4.22)	+0.020 (+0.508)
	9.33	0.178 (4.52)	+0.021 (+0.533)
	6.0	0.277 (7.04)	+0.033 (+0.838)
1 1/2	<i>D</i>	0.090 (2.29)	+0.011 (+0.279)
	17	0.112 (2.85)	+0.013 (+0.330)
	13.5	0.141 (3.58)	+0.017 (+0.432)
	Sch 40	0.145 (3.68)	+0.017 (+0.432)
	11	0.173 (4.39)	+0.021 (+0.533)
2	21	0.113 (2.87)	+0.014 (+0.356)
	17	0.140 (3.56)	+0.017 (+0.432)
	Sch 40	0.154 (3.91)	+0.018 (+0.457)
	13.5	0.176 (4.47)	+0.021 (+0.533)
	11	0.216 (5.49)	+0.026 (+0.660)
	9.33	0.255 (6.48)	+0.031 (+0.787)
2 1/2	21	0.137 (3.48)	+0.016 (+0.406)
	17	0.169 (4.29)	+0.020 (+0.508)
	13.5	0.213 (5.41)	+0.026 (+0.660)
	11	0.261 (6.63)	+0.031 (+0.787)
3	21	0.167 (4.24)	+0.020 (+0.508)
	17	0.206 (5.23)	+0.025 (+0.635)
	Sch 40	0.216 (5.49)	+0.026 (+0.660)
	13.5	0.259 (6.58)	+0.031 (+0.787)
	11.5	0.304 (7.72)	+0.036 (+0.914)
	11	0.318 (8.08)	+0.038 (+0.965)
	9.33	0.375 (9.53)	+0.045 (+1.143)
3 1/2	21	0.190 (4.83)	+0.023 (+0.584)
	17	0.236 (5.99)	+0.028 (+0.711)
	13.5	0.296 (7.52)	+0.036 (+0.914)
	11	0.363 (9.22)	+0.044 (+1.118)
4	21	0.214 (5.44)	+0.026 (+0.660)
	19	0.237 (6.02)	+0.028 (+0.711)
	17	0.265 (6.73)	+0.032 (+0.813)
	13.5	0.333 (8.46)	+0.040 (+1.016)
	11.5	0.391 (9.93)	+0.047 (+1.194)
	11.0	0.409 (10.39)	+0.049 (+1.246)
	9.33	0.482 (12.24)	+0.058 (+1.473)
5	21.6	0.258 (6.55)	+0.031 (+0.787)
	21	0.265 (6.73)	+0.032 (+0.813)
	17	0.327 (8.31)	+0.039 (+0.991)
	13.5	0.412 (10.46)	+0.050 (+1.270)
	11	0.506 (12.85)	+0.061 (+1.549)
6	32.5	0.204 (5.18)	+0.024 (+0.610)
	26	0.255 (6.48)	+0.031 (+0.787)
	23.7	0.280 (7.11)	+0.034 (+0.864)
	21	0.315 (8.00)	+0.038 (+0.965)
	17	0.390 (9.91)	+0.047 (+1.194)
	13.5	0.491 (12.47)	+0.059 (+1.499)