



Designation: C1029 – 13

Standard Specification for Spray-Applied Rigid Cellular Polyurethane Thermal Insulation¹

This standard is issued under the fixed designation C1029; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers the types and physical properties of spray applied rigid cellular polyurethane intended for use as thermal insulation. The operating temperatures of the surfaces to which the insulation is applied shall not be lower than -22°F (-30°C) or greater than $+225^{\circ}\text{F}$ ($+107^{\circ}\text{C}$). For specific applications, the actual temperature limits shall be as agreed upon between the manufacturer and the purchaser.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[C165 Test Method for Measuring Compressive Properties of Thermal Insulations](#)

[C168 Terminology Relating to Thermal Insulation](#)

[C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus](#)

[C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus](#)

[C1303 Test Method for Predicting Long-Term Thermal Resistance of Closed-Cell Foam Insulation](#)

[C1363 Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus](#)

[D883 Terminology Relating to Plastics](#)

[D1621 Test Method for Compressive Properties of Rigid Cellular Plastics](#)

[D1622 Test Method for Apparent Density of Rigid Cellular Plastics](#)

[D1623 Test Method for Tensile and Tensile Adhesion Properties of Rigid Cellular Plastics](#)

[D2126 Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging](#)

[D2842 Test Method for Water Absorption of Rigid Cellular Plastics](#)

[D6226 Test Method for Open Cell Content of Rigid Cellular Plastics](#)

[E84 Test Method for Surface Burning Characteristics of Building Materials](#)

[E96/E96M Test Methods for Water Vapor Transmission of Materials](#)

3. Terminology

3.1 *Definitions:* For definitions of terms used in this specification, refer to Terminologies [C168](#) and [D883](#).

4. Classification

4.1 Spray-applied rigid-cellular polyurethane thermal insulation covered by this specification is classified into four types as follows:

4.1.1 *Type I*—Compressive strength 15 psi (104 kPa) minimum.

4.1.2 *Type II*—Compressive strength 25 psi (173 kPa) minimum.

4.1.3 *Type III*—Compressive strength 40 psi (276 kPa) minimum.

4.1.4 *Type IV*—Compressive strength 60 psi (414 kPa) minimum.

5. Ordering Information

5.1 Orders for materials purchased under this specification shall include the following:

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.22 on Organic and Nonhomogeneous Inorganic Thermal Insulations.

Current edition approved April 15, 2013. Published June 2013. Originally approved in 1985. Last previous edition approved in 2010 as C1029 – 10. DOI: 10.1520/C1029-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- 5.1.1 ASTM designation, year of issue, and title.
- 5.1.2 Type (see 4.1).
- 5.1.3 *R* value or thickness required (see 10.1).
- 5.1.4 Sampling, if different (see Section 8).
- 5.1.5 If a certificate of compliance is required (see 13.1).
- 5.1.6 If packaging is other than specified (see 14.1).
- 5.1.7 If marking is other than specified (see 14.4).

6. Materials and Manufacture

6.1 Spray-applied rigid-cellular polyurethane thermal insulation is produced by the catalyzed chemical reaction of polyisocyanates with polyhydroxyl compounds, with the addition of other compounds such as stabilizers and blowing agents.

6.2 The materials shall be capable of being mixed and applied using commercial polyurethane spray equipment.

NOTE 1—The thermal insulation shall be formed directly on the surface to be sprayed, unless agreed upon by the purchaser and the manufacturer.

7. Physical Requirements

7.1 Polyurethane thermal insulation shall have the limiting property values as shown in Table 1.

7.2 Other physical properties shall be required, as agreed upon by the purchaser and the manufacturer

NOTE 2—Density is not a requirement of this specification, but if agreed upon by the purchaser and the manufacturer shall be determined in accordance with Test Method D1622 for point-of-manufacture quality control.

8. Sampling

8.1 *Lot*—For purposes of sampling, the lot shall consist of all the polyurethane liquid components purchased at one time.

8.2 *Unit Sample*—The unit sample shall consist of approximately 50 lb (23 kg) of each of the two liquid components as required to prepare the foam test specimens specified in Section 9. Samples may be drawn from representative bulk storage or from one or more shipping containers.

8.3 Sampling for qualification tests, if required, shall be in accordance with statistically sound practice. Qualification tests will be conducted on the physical properties in Table 1.

8.4 Sampling for inspection tests, if required, shall be for properties agreed upon between the manufacturer and the purchaser.

9. Test Specimen Preparation

9.1 Finished polyurethane foam insulation test panels shall be made by spray application consistent with the manufacturer's recommendations including: temperatures of the liquid components, ambient temperature, temperature and type of substrate, type and operation of spray equipment, and thickness of foam per pass. Unless otherwise specified and reported, the ambient and substrate temperature shall be $75 \pm 5^\circ\text{F}$ ($24 \pm 3^\circ\text{C}$). The relative humidity must not exceed 80%. The test panels shall be of a sufficient quantity and size to satisfy test requirements.

NOTE 3—Specific panel sizes and thicknesses shall be based on the requirements of the individual tests.

9.2 The test panels shall be allowed to cure for at least 72 h at $73 \pm 2^\circ\text{F}$ ($23 \pm 1^\circ\text{C}$) and $50 \pm 5\%$ relative humidity prior to cutting or testing for physical properties.

9.3 Core specimens, when required, shall be obtained by removing both the external skin and the boundary skin found at the substrate/foam interface. A trim cut on each face to a depth of $\frac{1}{8}$ to $\frac{1}{4}$ in. (3 to 6 mm) is generally sufficient. Core specimens may contain one or more internal skins at spray pass boundaries.

9.4 *Sample preparation for Test Method D2126*: For Type I, II, III, and IV products the sample foams are spray applied to 2 ft. by 2 ft. (610 by 610- mm) exterior CDX Grade $\frac{3}{4}$ in. (19-mm) plywood (unfinished on both sides). The maximum height of the applied foam shall be 2 in. (50-mm) above the substrate with a minimum of two passes and a maximum of three. A 12 in. \times 12 in. (305 \times 305-mm) sample is cut from the center of the plywood/foam as the test specimen. The specimen and plywood will be cut in such a manner that it will have at least one knit line. The cut foam height will be 1 in. (25 mm) from the plywood surface. The test specimen will be cut from the field sample so as to have smooth edges free of cracks. All faces will be smooth and shall be dust free. Two specimens shall be used for test exposure per test. In addition, 2 samples of the plywood will also be cut 2 in. \times 12 in. (305 \times 305-mm) as a control.

10. Test Methods

10.1 Determine thermal resistance in accordance with Test Method C177, Test Method C1363, or Test Method C518 at a mean temperature of $75 \pm 2^\circ\text{F}$ ($24 \pm 1^\circ\text{C}$) and 40°F (22°C)

TABLE 1 Physical Properties

Property	Requirements			
	Type I	Type II	Type III	Type IV
Thermal resistance of 1.0 in. (25 mm) thickness, min, $^\circ\text{F}\cdot\text{ft}^2\cdot\text{h}/\text{Btu}$ ($\text{K}\cdot\text{m}^2/\text{W}$) at mean temperature 75°F (24°C)	6.2	6.2	6.2	6.2
Compressive strength, at yield or 10 % deformation, whichever comes first, min, psi (kPa)	15 (104)	25 (173)	40 (276)	60 (414)
Water vapor permeability, max, perm-inches (ng/Pa-s-m)	3.0 (4.4)	3.0 (4.4)	3.0 (4.4)	3.0 (4.4)
Water absorption, max, volume %	5	5	5	5
Tensile strength, min, psi (kPa)	20 (138)	32 (221)	42 (290)	56 (386)
Response to thermal and humid aging, max, linear change %	12	9	6	5
Closed cell content, min, %	90	90	90	90
Surface burning characteristics, report value