



Designation: **A322—07 A322 – 13**

Standard Specification for Steel Bars, Alloy, Standard Grades¹

This standard is issued under the fixed designation A322; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*Scope

1.1 This specification covers hot-wrought alloy steel bars. Bar applications include forging, heat treating, cold drawing, machining and many structural components (**Note 1**).

NOTE 1—A guide for the selection of steel bars is contained in Practice **A400**.

1.2 The bars shall be furnished in the grades specified in **Table 1**. Sections and sizes of bar steel available are covered in Specification **A29/A29M**. Hot-wrought alloy steel bars are produced in cut lengths and coils; the manufacturer should be consulted regarding sections and sizes available in coils, produced to a chemical composition.

1.3 Some applications may require superior surface quality, or special chemical restrictions, metallurgical characteristics, heat treatment, or surface finishes which the purchaser may obtain by designating one or more of the available Supplementary Requirements.

2. Referenced Documents

2.1 *ASTM Standards:*²

A29/A29M Specification for Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for
A304 Specification for Carbon and Alloy Steel Bars Subject to End-Quench Hardenability Requirements
A400 Practice for Steel Bars, Selection Guide, Composition, and Mechanical Properties
E112 Test Methods for Determining Average Grain Size
E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings
E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

3. Ordering Information

3.1 Orders under this specification should include the following as required to describe adequately the desired material:

- 3.1.1 Quantity (weight or number of bars),
- 3.1.2 Name of material (hot-wrought alloy steel bars),
- 3.1.3 Dimensions,
- 3.1.4 ASTM designation,
- 3.1.5 Deoxidation practice (see **5.3**),
- 3.1.6 Grade designation or chemical composition limits (see **6.1** and **Table 1**),
- 3.1.7 Grain size if required,
- 3.1.8 Test reports, if required (**Section 8**),
- 3.1.9 Additions to the specification and Supplementary Requirements, if required, and
- 3.1.10 Application.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification **A29/A29M**, unless otherwise provided herein.

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.15** on Bars.

Current edition approved ~~May 1, 2007~~ May 1, 2013. Published ~~May 2007~~ June 2013. Originally approved in 1947. Last previous edition approved in ~~2006~~ 2007 as **A322—06**; **A322—07**. DOI: [10.1520/A0322-07.10.1520/A0322-13](https://doi.org/10.1520/A0322-07.10.1520/A0322-13).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Grade Designations and Chemical Compositions of Hot-Wrought Alloy Steel Bars^{A,B}

UNS Designation ^C	Grade ^D Designations	Chemical Composition, Ranges and Limits, %							
		Carbon	Manganese	Phosphorus, max	Sulfur, ^E max	Silicon ^F	Nickel	Chromium	Molybdenum
G13300	1330	0.28-0.33	1.60-1.90	0.035	0.040	0.15-0.35
G13350	1335	0.33-0.38	1.60-1.90	0.035	0.040	0.15-0.35
G13400	1340	0.38-0.43	1.60-1.90	0.035	0.040	0.15-0.35
G13450	1345	0.43-0.48	1.60-1.90	0.035	0.040	0.15-0.35
G40230	4023	0.20-0.25	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40120	4012	0.09-0.14	0.75-1.00	0.035	0.040	0.15-0.35	0.15-0.25
G40240	4024	0.20-0.25	0.70-0.90	0.035	0.035-	0.15-0.35	0.20-0.30
G40230	4023	0.20-0.25	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40240	4024	0.20-0.25	0.70-0.90	0.035	0.035-0.050	0.15-0.35	0.20-0.30
G40270	4027	0.25-0.30	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40280	4028	0.25-0.30	0.70-0.90	0.035	0.035-	0.15-0.35	0.20-0.30
G40280	4028	0.25-0.30	0.70-0.90	0.035	0.035-0.050	0.15-0.35	0.20-0.30
G40320	4032	0.30-0.35	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40370	4037	0.35-0.40	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40370	4037	0.35-0.40	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40420	4042	0.40-0.45	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40470	4047	0.45-0.50	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G40420	4042	0.40-0.45	0.70-0.90	0.035	0.040	0.15-0.35	0.20-0.30
G41180	4118	0.18-0.23	0.70-0.90	0.035	0.040	0.15-0.35	...	0.40-0.60	0.08-0.15
G41200	4120	0.18-0.23	0.90-1.20	0.035	0.040	0.15-0.35	...	0.40-0.60	0.13-0.20
G41210	4121	0.18-0.23	0.75-1.00	0.035	0.040	0.15-0.35	...	0.45-0.65	0.20-0.30
G41300	4130	0.28-0.33	0.40-0.60	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41350	4135	0.33-0.38	0.70-0.90	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41370	4137	0.35-0.40	0.70-0.90	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41400	4140	0.38-0.43	0.75-1.00	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41420	4142	0.40-0.45	0.75-1.00	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41450	4145	0.43-0.48	0.75-1.00	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41470	4147	0.45-0.50	0.75-1.00	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41500	4150	0.48-0.53	0.75-1.00	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15-0.25
G41610	4161	0.56-0.64	0.75-1.00	0.035	0.040	0.15-0.35	...	0.70-0.90	0.25-0.35
G43200	4320	0.17-0.22	0.45-0.65	0.035	0.040	0.15-0.35	1.65-2.00	0.40-0.60	0.20-0.30
G43400	4340	0.38-0.43	0.60-0.80	0.035	0.040	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30
G43406	E4340	0.38-0.43	0.65-0.85	0.025	0.025	0.15-0.35	1.65-2.00	0.70-0.90	0.20-0.30
G44190	4419	0.18-0.23	0.45-0.65	0.035	0.040	0.15-0.35	0.45-0.60
G44220	4422	0.20-0.25	0.70-0.90	0.035	0.040	0.15-0.35	0.35-0.45
G44270	4427	0.24-0.29	0.70-0.90	0.035	0.040	0.15-0.35	0.35-0.45
G46150	4615	0.13-0.18	0.45-0.65	0.035	0.040	0.15-0.35	1.65-2.00	...	0.20-0.30
G46170	4617	0.16-0.21	0.40-0.65	0.030	0.040	0.15-0.35	1.65-2.00	...	0.20-0.30
G46200	4620	0.17-0.22	0.45-0.65	0.035	0.040	0.15-0.35	1.65-2.00	...	0.20-0.30
G46210	4621	0.18-0.23	0.70-0.90	0.035	0.040	0.15-0.35	1.65-2.00	...	0.20-0.30
G46260	4626	0.24-0.29	0.45-0.65	0.035	0.040	0.15-0.35	0.70-1.00	...	0.15-0.25
G47150	4715	0.13-0.18	0.70-0.90	0.035	0.040	0.15-0.35	0.70-1.00	0.45-0.65	0.45-0.60
G47180	4718	0.16-0.21	0.70-0.90	0.035	0.040	0.15-0.35	0.90-1.20	0.35-0.55	0.30-0.40
G47200	4720	0.17-0.22	0.50-0.70	0.035	0.040	0.15-0.35	0.90-1.20	0.35-0.55	0.15-0.25
G48150	4815	0.13-0.18	0.40-0.60	0.035	0.040	0.15-0.35	3.25-3.75	...	0.20-0.30
G48170	4817	0.13-0.20	0.40-0.60	0.035	0.040	0.15-0.35	3.25-3.75	...	0.20-0.30
G48200	4820	0.18-0.23	0.50-0.70	0.035	0.040	0.15-0.35	3.25-3.75	...	0.20-0.30
G50150	5015	0.12-0.17	0.30-0.50	0.035	0.040	0.15-0.35	...	0.30-0.50	...
G50460	5046	0.43-0.48	0.75-1.00	0.035	0.040	0.15-0.35	...	0.20-0.35	...
G51150	5115	0.13-0.18	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51170	5117	0.15-0.20	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51200	5120	0.17-0.22	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51300	5130	0.28-0.33	0.70-0.90	0.035	0.040	0.15-0.35	...	0.80-1.10	...
G51320	5132	0.30-0.35	0.60-0.80	0.035	0.040	0.15-0.35	...	0.75-1.00	...
G51350	5135	0.33-0.38	0.60-0.80	0.035	0.040	0.15-0.35	...	0.80-1.05	...
G51400	5140	0.38-0.43	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51450	5145	0.43-0.48	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51470	5147	0.46-0.51	0.70-0.95	0.035	0.040	0.15-0.35	...	0.85-1.15	...
G51500	5150	0.48-0.53	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51550	5155	0.51-0.59	0.70-0.90	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G51600	5160	0.56-0.64	0.75-1.00	0.035	0.040	0.15-0.35	...	0.70-0.90	...
G50986	E50100	0.98-1.10	0.25-0.45	0.025	0.025	0.15-0.35	...	0.40-0.60	...
G51986	E51100	0.98-1.10	0.25-0.45	0.025	0.025	0.15-0.35	...	0.90-1.15	...
G52986	E52100	0.98-1.10	0.25-0.45	0.025	0.025	0.15-0.35	...	1.30-1.60	...
G52986	E52100	0.98-1.10	0.25-0.45	0.025	0.025	0.15-0.35	...	1.30-1.60	...
G52985	52100	0.93-1.05	0.25-0.45	0.025	0.015	0.15-0.35	...	1.35-1.60	...
G61180	6118	0.16-0.21	0.50-0.70	0.035	0.040	0.15-0.35	...	0.50-0.70	Vanadium 0.10-0.15
G61500	6150	0.48-0.53	0.70-0.90	0.035	0.040	0.15-0.35	...	0.80-1.10	0.15 min Molybdenum

TABLE 1 *Continued*

UNS Designation ^C	Grade ^D Designations	Chemical Composition, Ranges and Limits, %							
		Carbon	Manganese	Phosphorus, max	Sulfur, ^E max	Silicon ^F	Nickel	Chromium	Molybdenum
G81150	8115	0.13–0.18	0.70–0.90	0.035	0.040	0.15–0.35	0.20–0.40	0.30–0.50	0.08–0.15
G86150	8615	0.13–0.18	0.70–0.90	0.035	0.04	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86170	8617	0.15–0.20	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86200	8620	0.18–0.23	0.70–0.90	0.035	0.04	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86220	8622	0.20–0.25	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86250	8625	0.23–0.28	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86270	8627	0.25–0.30	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86300	8630	0.28–0.33	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86370	8637	0.35–0.40	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86400	8640	0.38–0.43	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86420	8642	0.40–0.45	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86450	8645	0.43–0.48	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86500	8650	0.48–0.53	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86550	8655	0.51–0.59	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G86600	8660	0.56–0.64	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
G87200	8720	0.18–0.23	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30
G87400	8740	0.38–0.43	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30
G88220	8822	0.20–0.25	0.75–1.00	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.30–0.40
G92540	9254	0.51–0.59	0.60–0.80	0.035	0.040	1.20–1.60	...	0.60–0.80	...
G92550	9255	0.51–0.59	0.70–0.95	0.035	0.040	1.80–2.20
G92590	9259	0.56–0.64	0.75–1.00	0.035	0.040	0.70–1.10	...	0.45–0.65	...
G92600	9260	0.56–0.64	0.75–1.00	0.035	0.040	1.80–2.20
G92600	9260	0.56–0.64	0.75–1.00	0.035	0.040	1.80–2.20
G93100	9310	0.08–0.13	0.45–0.65	0.025	0.025	0.15–0.30	3.00–3.50	1.00–1.40	0.08–0.15
Standard Boron Steels ^G									
G50441	50B44	0.43–0.48	0.75–1.00	0.035	0.040	0.15–0.35	...	0.20–0.60	...
G50461	50B46	0.44–0.49	0.75–1.00	0.035	0.040	0.15–0.35	...	0.20–0.35	...
G50501	50B50	0.48–0.53	0.75–1.00	0.035	0.040	0.15–0.35	...	0.40–0.60	...
G50601	50B60	0.56–0.64	0.75–1.00	0.035	0.040	0.15–0.35	...	0.40–0.60	...
G51601	51B60	0.56–0.64	0.75–1.00	0.035	0.040	0.15–0.35	...	0.70–0.90	...
G81451	81B45	0.43–0.48	0.75–1.00	0.035	0.040	0.15–0.35	0.20–0.40	0.35–0.55	0.08–0.15
G94171	94B17	0.15–0.20	0.75–1.00	0.035	0.040	0.15–0.35	0.30–0.60	0.30–0.50	0.08–0.15
G94301	94B30	0.28–0.33	0.75–1.00	0.035	0.040	0.15–0.35	0.30–0.60	0.30–0.50	0.08–0.15

^A Small quantities of certain elements are present in alloy steels which are not specified or required. These elements are considered as incidental and may be present to the following maximum amounts: copper 0.35 %, nickel 0.25 %, chromium 0.20 %, and molybdenum 0.06 %.

^B Standard alloy steels can be produced with a lead range of 0.15 to 0.35 %. Such steels are identified by inserting the letter "L" between the second and third numerals of the number, that is, 41L40. A cast or heat analysis is not determinable when lead is added to the ladle stream.

^C New designation established in accordance with Practice E527.

^D Grade designations correspond to the respective AISI and SAE designations. Grade compositions correspond to the respective AISI compositions.

^E Where minimum and maximum sulfur contents are shown, it is indicative of resulfurized steel.

^F Silicon may be specified by the purchaser as 0.10 % maximum. The need for 0.10 % maximum generally relates to severely cold-formed parts.

^G These steels can be expected to contain 0.0005 to 0.003 % boron. If the usual titanium additive is not permitted, the steels can be expected to contain up to 0.005 % boron.

5. Materials and Manufacture

5.1 The steel shall be made by one or more of the following primary processes: ~~open-hearth, basic-oxygen, basic-oxygen~~ or electric-furnace. The primary melting may incorporate separate degassing or refining and may be followed by secondary melting using electro-slag remelting or vacuum arc remelting. Where secondary melting is employed, the heat shall be defined as all of the cast product remelted from a single primary heat.

5.2 The steel shall be furnished as strand cast or ingot cast, unless otherwise specified.

5.2.1 *Discard*—A sufficient discard shall be made to secure freedom from injurious piping and undue segregation.

5.3 *Deoxidation*—Killed steel is required.

5.3.1 The purchaser may designate that the steel be made to coarse or fine austenitic grain size. (See Supplementary Requirement S9 or S10.)

5.4 *Slow Cooling*—Immediately after hot forming, the bars shall be allowed to cool to a temperature below the critical range under suitable conditions to prevent imperfections caused by too rapid cooling.

5.5 *Thermal Treatment*—Various thermal treatments such as annealing, stress relief, quench and temper, normalize, etc., are available. Such treatments must be specified as a Supplementary Requirement.

6. Chemical Composition

6.1 The heat analysis shall conform to the requirements for chemical composition in Table 1 for the grade specified.