



International Standard

ISO 16840-2

Wheelchair seating —

Part 2:

Determination of physical and mechanical characteristics of seat cushions intended to manage tissue integrity

AMENDMENT 1: Updates and addition
of new Annex covering alternatively
sized cushions

Sièges de fauteuils roulants —

*Partie 2: Détermination des caractéristiques physiques et
mécaniques des coussins d'assise et dispositifs de répartition de
pression*

*AMENDEMENT 1: Mises à jour et ajout d'une nouvelle annexe
couvrant les coussins d'autres dimensions*

**Second edition
2018-01**

**AMENDMENT 1
2024-04**

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 16840-2:2018/Amd 1:2024](https://standards.iteh.ai/catalog/standards/iso/5183a588-2a74-49c6-bb27-18c688cf8d19/iso-16840-2-2018-amd-1-2024)

<https://standards.iteh.ai/catalog/standards/iso/5183a588-2a74-49c6-bb27-18c688cf8d19/iso-16840-2-2018-amd-1-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 173, *Assistive products*, Subcommittee SC 1, *Wheelchairs*.

A list of all the parts of ISO 16840 can be found on the ISO website.

[ISO 16840-2:2018/Amd 1:2024](https://standards.iteh.ai/catalog/standards/iso/5183a588-2a74-49c6-bb27-18c688cf8d19/iso-16840-2-2018-amd-1-2024)

<https://standards.iteh.ai/catalog/standards/iso/5183a588-2a74-49c6-bb27-18c688cf8d19/iso-16840-2-2018-amd-1-2024>

Wheelchair seating —

Part 2:

Determination of physical and mechanical characteristics of seat cushions intended to manage tissue integrity

AMENDMENT 1: Updates and addition of new Annex covering alternatively sized cushions

5.7

Replace list items a) and b) with the following:

- a) Two 50 mm \pm 2 mm diameter indenters, centres spaced 110 mm \pm 5 mm apart, representing ischial tuberosities.
- b) Two 25 mm \pm 1 mm diameter indenters, centres spaced 350 mm \pm 10 mm apart, representing the trochanters.

6.1

Replace the text with the following:

6.1 Choice of cushion

ISO 16840-2:2018/Amd 1:2024

Obtain an unused sample seat cushion for testing with a nominal width of 400 mm to 450 mm. If a cover is provided, ensure that it is fitted to the cushion in the orientation specified by the manufacturer.

A cushion with a 400 mm to 450 mm nominal width is the size for the RCLI indenter specified in Annex A and the LCI indenter in 5.7. Indenters for testing alternative cushion sizes are specified in Annexes D and E.

11.2

Replace list items f) to k) with the following:

- f) Apply a vertical load of 140 N \pm 5 N.
- g) Measure the vertical distance from the horizontal supporting surface to the inferior surface of the LCI after 300 s \pm 10 s to the nearest 1 mm (L_1).
- h) Increase the load on LCI to 186 N \pm 5 N.
- i) Re-measure vertical distance from the horizontal supporting surface to the inferior surface of the LCI to the nearest 1 mm (L_2) 60 s \pm 5 s after the increased load is applied.
- j) Increase the load on LCI to 232 N \pm 5 N.
- k) Re-measure vertical distance from the horizontal supporting surface to the inferior surface of the LCI to the nearest 1 mm (L_3) 60 s \pm 5 s after the increased load is applied.

11.3

Replace the text with the following:

11.3 Method of calculation

- a) Calculate loaded contour depth $L_{CD} = L_{th} - L_1$ and record to the nearest 1 mm for each trial.
- b) Calculate 33 % overload deflection $D_{0.33} = L_1 - L_2$ and record to the nearest 1 mm for each trial.
- c) Calculate 66 % overload deflection $D_{0.66} = L_1 - L_3$ and record to the nearest 1 mm for each trial.

11.4

Replace the text with the following:

11.4 Test report

In addition to the information required as specified in Clause 16, report the median values for loaded contour depth (L_{CD}), 33 % overload deflection ($D_{0.33}$), and 66 % overload deflection ($D_{0.66}$).

Annex A

Replace Table A.1 is with the following:

Table A.1 — Cone and sphere dimensions

Cushion width	Indenter width	Indenter length	Anterior - posterior location of load	Cone angle	Cone width first cut	Cone height w/o sphere	Height with sphere	Major diameter of cone	Minor diameter of cone	Length of cone edge
(nom.) mm	(W_i) mm	(L_i) mm	(l_f) mm	(\varnothing) °	(W_c) mm	(H_c) mm	(H_{cs}) mm	(D_c) mm	(d_c) mm	mm
400 – 450	360	500	127	10	180	367	494	254	124	373
NOTE 1 All tolerances (except cushion width) ± 2 mm.										
NOTE 2 The RCLI is constructed from cones and spheres machined according to Figure A.1. These components are assembled to form the required shape according to Table A.1.										

Annex D

Replace the first sentence with the following:

This document utilizes RCLIs designed to test cushions with widths of 400 mm to 450 mm.

Replace Table D.1 with the following: