



Designation: C1142 – 95 (Reapproved 2013)

Standard Specification for Extended Life Mortar for Unit Masonry¹

This standard is issued under the fixed designation C1142; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers extended life mortar as delivered for use in construction of non-reinforced or reinforced unit masonry.

1.2 This specification is a property standard.

1.3 Four types of mortar are covered: RM, RS, RN, and RO. These types of mortar can be manufactured by using one of the four mortar formulations with masonry aggregate: portland cement, portland cement-lime, masonry cement, or masonry cement with portland cements. The materials are listed in Section 5.

1.4 **Appendix X1** provides a rationale statement and commentary.

2. Referenced Documents

2.1 *ASTM Standards*:²

C91 Specification for Masonry Cement

C144 Specification for Aggregate for Masonry Mortar

C150 Specification for Portland Cement

C207 Specification for Hydrated Lime for Masonry Purposes

C270 Specification for Mortar for Unit Masonry

C780 Test Method for Preconstruction and Construction Evaluation of Mortars for Plain and Reinforced Unit Masonry

C1072 Test Methods for Measurement of Masonry Flexural Bond Strength

E447 Test Method for Compressive Strength of Laboratory Constructed Masonry Prisms (Withdrawn 1997)³

E518 Test Methods for Flexural Bond Strength of Masonry

¹ This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.03 on Specifications for Mortars.

Current edition approved June 1, 2013. Published June 2013. Originally approved in 1990. Last previous edition approved in 2007 as C1142 – 95 (2007). DOI: 10.1520/C1142-95R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

2.2 *Other Document*:

National Institute of Standards and Technology, Handbook 44, *Specifications, Tolerances, and Other Technical Requirements for Commercial Weighing and Measuring Devices*⁴

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 All terms in this specification have their conventional meaning, except as follows:

3.1.2 *extended life mortars*—mortar consisting of cementitious materials, aggregate, water and set-control admixtures which are measured and mixed at a central location, using weight-or-volume-control equipment. This mortar, as delivered to a construction site, shall be usable for a period in excess of 2½ h.

4. Ordering Information

4.1 The purchaser shall specify the following:

4.1.1 The mortar type in **Table 1**,

4.1.2 Length of workability time for the mortar, and

4.1.3 Desired consistency satisfactory for the mason's use when tested by the manufacturer in accordance with **10.2**.

4.2 At the request of the purchaser, the producer shall, prior to delivery, furnish laboratory and field performance data satisfactory to the purchaser that the materials to be used will produce mortar of the type specified.

NOTE 1—The purchase order or contract may list the mortar ingredients desired and may state a list of optional data, which are in addition to the performance requirements in Section 7. Examples of such tests are: Test Method C1072, Test Methods E518, Test Methods E447, and test data for mortar that has been re-tempered.

5. Materials

5.1 Materials used as ingredients in extended life mortar shall conform to the requirements specified in 5.1.1 through 5.1.4.2.

5.1.1 *Cementitious Materials*—Cementitious materials shall conform to the following ASTM specifications.

5.1.1.1 *Portland Cement*—Types I, II or III of Specification C150.

⁴ Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

TABLE 1 Property Specification Requirements

| Mortar Type | Avg ^A Compressive Strength at 28 days, min psi, (MPa) | Water Retention min, % | Air Content, ^B max, % |
|-------------|--|------------------------|----------------------------------|
| | Cubes | | |
| RM | 2500 (17.2) | 75 | 18 |
| RS | 1800 (12.4) | 75 | 18 |
| RN | 750 (5.2) | 75 | 18 |
| RO | 350 (2.4) | 75 | 18 |

^A Twenty-eight days old from date of casting. Refer to 10.3.1. The strength values as shown are the standard values. Intermediate values may be specified in accordance with project requirements.

^B When structural reinforcement is incorporated in mortar, the maximum air content shall be 12 %, or bond strength test data shall be provided to justify higher air content.

5.1.1.2 *Masonry Cement*—Types M, S, or N of Specification C91.

5.1.1.3 *Hydrated Lime*—Specification C207, Type S.

NOTE 2—Type N limes may be permitted if shown by test or performance record to be not detrimental by the autoclave expansion.

5.1.2 *Aggregates*—The aggregate shall comply with Specification C144.

5.1.3 *Water*—Water shall be clean and free of oils, acids, alkalies, salts, organic materials or other substances that may be deleterious to mortar or corrosive to metals in the masonry.

5.1.4 *Admixtures*—Admixtures are permitted for use only at the production plant.

5.1.4.1 Evidence satisfactory to the purchaser shall be provided to show that the admixtures do not cause nor accelerate corrosion of metal which will be in contact with mortar.

5.1.4.2 Any admixture to be used shall be subject to written certification from the manufacturer, supported by evidence that the admixture will have no adverse effect on the long-term strength, durability, or appearance of the mortar nor on any material or component in contact with the mortar, nor any assemblage of which the mortar forms a part.

6. Manufacture and Delivery

6.1 *Storage of Materials*—Cementitious materials and aggregates shall be stored in such a manner as to prevent deterioration and contamination.

6.2 *Measurement of Materials*—Measure materials in accordance with 6.2.1 through 6.2.4.

6.2.1 Cementitious materials and the aggregate shall be measured by weight or by volume. Volumetric measurement shall be calibrated by weight.

6.2.2 Scales for batching mortar ingredients shall conform to the applicable sections of the current edition of the National Institute of Standards and Technology, Handbook 44.

6.2.3 Measure water by weight or by volume.

6.2.4 Measure admixtures by weight or by volume.

6.3 *Mixing*—Mix extended life mortar ingredients at a central location using either truck mixers or stationary mixers.

6.3.1 Agitation, not mixing, is allowed during transport.

6.4 *Delivery*—Unless otherwise specified, a delivery of the mortar shall conform to 6.4.1 and 6.4.2.

6.4.1 Thoroughly mix and deliver to the construction site mortar with a satisfactory degree of workability and without segregation of ingredients.

6.4.2 Temperature of the mortar at time of delivery shall be 40 to 120°F (4 to 49°C).

7. Property Requirements

7.1 When sampled and tested in accordance with Sections 9 and 10 respectively, the mortar shall comply with the appropriate sections of Table 1.

7.2 A test for compressive strength is the average of at least three specimens from one batch.

7.3 Mortar of known higher strength shall not be indiscriminately substituted when a mortar type of anticipated lower strength is specified.

7.4 Do not change the established proportions for extended life mortar designed for a particular job, nor utilize materials with different physical characteristics in the mix unless compliance with the requirements of this specification are reestablished.

7.4.1 Alter the dosage of the admixture which controls the setting time when needed to maintain a similar time of set during seasonal temperature changes.

NOTE 3—Consistency of the mortar should be correlated with the particular masonry unit to be used because certain mortars are more compatible with certain masonry units. The specifier should consult the admixture manufacturer to evaluate the interaction of the mortar type and masonry unit specified. Masonry units having a high initial rate of absorption will have greater compatibility with mortar of high-water retentivity. Refer to the Related Items That Have an Effect on Properties section in Appendix X1 of Specification C270.

8. Field Practice

8.1 *Tempering Mortars*—Mortars that have stiffened due to loss of water by evaporation shall be re-tempered not more than one time during the working life of the mortar by adding water to restore the required consistency.

8.1.1 Do not use mortar beyond the period of time established by the manufacturer. This time period shall be documented with test data.

NOTE 4—Extended life mortar is usually designed to have a workability period between 24 to 36 h.

8.2 *Storage at the Site*—The mortar shall be protected from freezing and evaporation.

9. Sampling

9.1 *Sampling Materials*—The mortar materials for laboratory tests shall be sampled at the plant where the mortar is manufactured. Water, aggregate and cementitious material shall be sampled in accordance with Test Method C780.

9.2 *Sampling Plastic Mortar at the Plant*—Discharge from the mixer a thoroughly mixed sample of mortar not less than 4 gal (15 L) into a nonabsorptive container, from which the quantity of mortar required for a specific quality control test can be taken.

9.3 *Sampling Plastic Mortar at the Site*—Obtain a composite sample by combining at least three equal portions from