



Designation: D6904 – 03 (Reapproved 2013)

# Standard Practice for Resistance to Wind-Driven Rain for Exterior Coatings Applied on Masonry<sup>1</sup>

This standard is issued under the fixed designation D6904; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice is for the evaluation of the ability of coatings to resist the passage of water through masonry block when exposed to water spray and air pressure.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D1475 Test Method For Density of Liquid Coatings, Inks, and Related Products

D3924 Specification for Environment for Conditioning and Testing Paint, Varnish, Lacquer, and Related Materials

D3925 Practice for Sampling Liquid Paints and Related Pigmented Coatings

### 2.2 Federal Standard:

TT-C-555B Coating, Textured (For Interior and Exterior Masonry Surfaces)<sup>3</sup>

## 3. Summary of Practice

3.1 Typically 8 by 16 by 2 in. masonry blocks are coated with block filler and then coated with the masonry paint and allowed to cure. The coated blocks are then secured to a test

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.47 on Concrete, Stone and Masonry Treatments.

Current edition approved June 1, 2013. Published June 2013. Originally approved in 2003. Last previous edition approved in 2007 as D6904 – 03 (2007). DOI: 10.1520/D6904-03R13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.

apparatus and exposed for 24 h to continuous water spray and air pressure or as agreed upon between manufacturer and supplier. Upon completion of the exposure, the blocks are removed, evaluated for visible water leaks or weight gain, or both.

## 4. Significance and Use

4.1 This practice is meant to simulate the ability of a coating system applied to a masonry block to withstand exposure to continuous water spray (rain) and a dynamic pressure equivalent to a 98 mph wind velocity without exhibiting water leaks or weight gain, or both.

## 5. Apparatus

5.1 The testing box is assembled from transparent plastic panels 1/2-in. thick and typically of the dimensions as shown in Fig. 1. Three openings on the side, 6 by 12 in., are provided so that the coated side of the three blocks may be positioned for test. The openings on the top of the apparatus for the air inlet and manometer connection shall not be less than 3 in. apart to make certain that air inlet turbulence will not effect the manometer readings. A spray tube shall be constructed from 1/2-in. plastic tubing with three fish-tail nozzles.<sup>4</sup> Attachment to the testing box includes a water-filled U-tube manometer, source of compressed air, clamps and angle irons for securely fastening the test panels to the box, and a drain outlet. Also, illustrated is a simple air pressure regulator consisting of a T-tube with the leg (foot) of the tube placed in a water filled beaker at a depth of slightly greater than 5 in. This set up is also a safety device. Any sudden increase in air pressure will be vented harmlessly. The apparatus outlined above was derived from that shown in Federal Specification TT-C-555B. Apparatus and substrates of other dimensions can be used as agreed upon between manufacturer and supplier. The duration of exposure and water pressure used will also be agreed upon between manufacturer and user.

## 6. Reagents and Materials

6.1 *Three 8 by 16 by 2 in. Patio Blocks.*

6.2 *Stiff Bristle Brush.*

<sup>4</sup> Federal Specification TT-C-555B, Amendment No. 1, dated August 5, 1975, U.S. Government Printing Office.