



Designation: **B843 – 07 B843 – 13**

Standard Specification for Magnesium Alloy Anodes for Cathodic Protection¹

This standard is issued under the fixed designation B843; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. ~~Scope~~ Scope*

1.1 This specification covers magnesium alloy anodes in the form of cast and extruded shapes.

2. Referenced Documents

2.1 *ASTM Standards*:²

[B951 Practice for Codification of Unalloyed Magnesium and Magnesium-Alloys, Cast and Wrought](#)

[B953 Practice for Sampling Magnesium and Magnesium Alloys for Spectrochemical Analysis](#)

[E35B954 Test Methods/Method for Chemical Analysis of Magnesium and Magnesium Alloys by Atomic Emission Spectrometry](#)
(Withdrawn 2008)

[E55 Practice for Sampling Wrought Nonferrous Metals and Alloys for Determination of Chemical Composition](#)

[E88 Practice for Sampling Nonferrous Metals and Alloys in Cast Form for Determination of Chemical Composition](#)

[G97 Test Method for Laboratory Evaluation of Magnesium Sacrificial Anode Test Specimens for Underground Applications](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

3. Significance and Use

3.1 This specification is prescriptive and not performance in nature.

4. Ordering Information

4.1 Orders for anodes under this specification shall include the following information:

4.1.1 Grade (Section 5 and Table 1),

4.1.2 Quantity (number of pieces), and

4.1.3 Size, form, and shape as negotiated between purchaser and supplier.

5. Chemical Composition

5.1 *Limits*—The material shall conform to the chemical composition requirements prescribed in Table 1.

5.2 *Sampling*:

5.2.1 Sufficient samples shall be taken by the manufacturer to ensure conformance to the chemical composition requirements of the metal. Samples may be taken from the molten metal when the cast anode or extrusion ingot is ~~poured~~, poured following Practice B953, or from the finished anode; anode following the requirements of Specifications B954, E55, or E88. Samples shall be representative of the material.

~~5.2.2 In case of dispute, the sample for chemical analysis shall meet the requirements of Practice E55 or E88.~~

5.2.2 *Method of Analysis*—Any suitable method of chemical analysis may be used. In case of dispute, the analysis shall be made by methods given in Test Methods ~~results secured by Test Method E35B954~~; shall be the basis of acceptance.

6. Property Testing

6.1 Sufficient samples may be taken for property testing as negotiated between purchaser and supplier. Testing will be done in compliance with Test Method G97.

¹ This specification is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.04 on Magnesium Alloy Cast and Wrought Products.

Current edition approved June 1, 2007; May 1, 2013. Published July 2007; June 2013. Originally approved in 1993. Last previous edition approved in 2003; 2007 as B843 – 93; B843 – 07. (2003). DOI: 10.1520/B0843-07.10.1520/B0843-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard