



Designation: ~~D6341~~—~~10~~ D6341 – 13

Standard Test Method for Determination of the Linear Coefficient of Thermal Expansion of Plastic Lumber and Plastic Lumber Shapes Between –30 and 140°F (–34.4 and 60°C)¹

This standard is issued under the fixed designation D6341; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope-~~Scope~~*

1.1 This test method covers the determination of the coefficient of linear thermal expansion for plastic lumber and plastic lumber shapes to two significant figures. The determination is made by taking measurements with a caliper at three discrete temperatures. At the test temperatures and under the stresses imposed, the plastic lumber shall have a negligible creep or elastic strain rate, or both, insofar as these properties would significantly affect the accuracy of the measurements.

1.1.1 This test method details the determination of the linear coefficient of thermal expansion of plastic lumber and plastic lumber shapes in their “as manufactured” form. As such, this is a test method for evaluating the properties of plastic lumber or shapes as a product and not a material property test method.

1.2 The thermal expansion of plastic lumber and shapes is composed of a reversible component on which it is possible to superimpose changes in length due to changes in moisture content, curing, loss of plasticizer or solvents, release of stresses, phase changes, voids, inclusions, and other factors. This test method is intended to determine the coefficient of linear thermal expansion under the exclusion of non-linear factors as far as possible. In general, it will not be possible to exclude the effect of these factors completely. For this reason, the test method can be expected to give a reasonable approximation but not necessarily precise determination of the linear coefficient of thermal expansion.

1.3 Plastic lumber and plastic lumber shapes are currently made predominately with recycled plastics where the product is non-homogeneous in the cross-section. However, it is possible that this test method will also be applicable to similar manufactured plastic products made from virgin resins or other plastic composite materials.

1.4 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 *ASTM Standards:*²

[D618 Practice for Conditioning Plastics for Testing](#)

[D883 Terminology Relating to Plastics](#)

[D4065 Practice for Plastics: Dynamic Mechanical Properties: Determination and Report of Procedures](#)

[D5033 Guide for Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics](#) (Withdrawn 2007)³

[E831 Test Method for Linear Thermal Expansion of Solid Materials by Thermomechanical Analysis](#)

3. Terminology

3.1 *Definitions:*

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.20 on Plastic Lumber. Current edition approved Sept. 1, 2010; June 1, 2013. Published September 2010; June 2013. Originally approved in 1998. Last previous edition approved in 2005 as ~~D6341–98~~D6341 - 10.(2005). DOI: ~~10.1520/D6341-10~~10.1520/D6341-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

3.1.1 *plastic lumber, n*—a manufactured product composed of more than 50 weight percent resin, in which the product generally is rectangular in cross-section and typically supplied in board and dimensional lumber sizes, may be filled made primarily from plastic materials (filled or unfilled), typically used as a building material for purposes similar to those of traditional lumber, which is usually rectangular in cross-section. (Terminology [D883](#) or unfilled, and may be composed of single or multiple resin blends.)

3.1.1.1 Discussion—

Plastic lumber is typically supplied in sizes similar to those of traditional lumber board, timber and dimension lumber; however the tolerances for plastic lumber and for traditional lumber are not necessarily the same. (Terminology [D883](#))

3.1.2 *plastic lumber shape, n*—a plastic lumber product which is generally not rectangular in cross-section.

3.1.3 *resin, n*—a solid or pseudosolid organic material often of high molecular weight, which exhibits a tendency to flow when subjected to stress, usually has a softening or melting range, and usually fractures conchoidally. (Terminology [D883](#))—(~~D883~~)

3.1.3.1 Discussion—

In a broad sense, the term is used to designate any polymer that is a basic material for plastics. (1982)

3.2 Additional definitions of terms applying to this test method appear in Terminology [D883](#) and Practice [D5033](#).

4. Summary of Test Method

4.1 This test method is intended to provide a means of determining the coefficient of linear thermal expansion of plastic lumber and plastic lumber shapes, which have the potential to contain inclusions and voids. This test method is a product test method, and not a materials test method. Furthermore, this test method is not designed to provide more than two significant figures of accuracy in the result. The test method involves using solid, full cross-sectioned members (see [Note 2](#)), as manufactured, of approximately 12 in. (300 mm) in length. In view of the low thermal conductivity of these materials it is impractical to make dynamic temperature variations in a reasonable length of time. Therefore, measurements are taken on each sample after conditioning 48 h or more at three discrete temperatures, $-30, 73.4, \text{ and } 140^{\circ}\text{F}$, $\pm 3.6^{\circ}\text{F}$ ($-34.4, 23, \text{ and } 60^{\circ}\text{C}$, $\pm 2^{\circ}\text{C}$), no more than 1 min after removal from the temperature chamber. The measuring device used is a caliper capable of measuring to the nearest 0.001 in. (0.025 mm), and is utilized at ambient temperature.

NOTE 2—It is acceptable to evaluate hollow cross-section products with this test method provided it can be shown that negligible dimensional changes occur in the prescribed measurement time interval.

5. Significance and Use

5.1 The coefficient of linear thermal expansion, α , between temperatures T_1 and T_2 for a specimen whose length is L_0 at the reference temperature, is given by the following equation:

$$\alpha = \frac{1}{L_0} \frac{L_2 - L_1}{T_2 - T_1} = \frac{1}{L_0} \frac{\Delta L}{\Delta T} \quad (1)$$

Where L_1 and L_2 are the specimen lengths at temperatures T_1 and T_2 , respectively. α is, therefore, obtained by dividing the linear expansion per unit length by the change in temperature.

5.2 The nature of most plastics and the construction applications for which plastic lumber and plastic lumber shapes are used, make -30 to 140°F (-34.4 to 60°C) a practical temperature range for linear thermal expansion measurements. Where testing outside of this temperature range or when linear thermal expansion characteristics of a particular plastic are not known through this temperature range, particular attention shall be paid to the factors mentioned in [1.2](#) and it is possible that special preliminary investigations by thermo-mechanical analysis, such as what is prescribed in Practice [D4065](#) for the location of transition temperatures, will be required, in order to avoid excessive error. If such a transition point is located, a separate coefficient of expansion for a temperature range below and above the transition point shall be determined. For specification and comparison purposes (provided it is known that no transition exists in this range), the range from -30 to 140°F (-34.4 to 60°C) shall be used. (For reference, glass transition and melting point temperatures of typical resins used in plastic lumber products are given in [Appendix X2](#) of this test method.)

6. Apparatus

6.1 *Conditioning Chamber*, capable of conditioning test specimens at temperatures in the range of -30 to 140°F , $\pm 1.8^{\circ}\text{F}$ (-34.4 to 60°C , $\pm 1^{\circ}\text{C}$), at humidity levels of $50 \pm 5\%$.

6.2 *Caliper*, capable of measuring the length of the specimen with an accuracy of 0.001 in. (0.025 mm). For a given test or test series, the same caliper shall be used for all measurements. The calipers shall be kept and used at room temperature (73.4°F (23°C)).