



SLOVENSKI STANDARD
SIST EN 28094:1997

01-marec-1997

Trakovi tračnih transporterjev z vložkom iz jeklenih vrvi - Preskus vezalne sposobnosti med krovnim in osnovnim vložkom (ISO 8094:1984)

Steel cord conveyor belts - Adhesion strength test of the cover to the core layer (ISO 8094:1984)

Stahlseilfördergurte - Haftung zwischen der Deckplatte und der Kernschicht (ISO 8094:1984)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Courroies transporteuses a câbles d'acier - Essai d'adhérence du revêtement a la couche de câbles (ISO 8094:1984)

[SIST EN 28094:1997](#)

[https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-](https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997)

[b93b2f99c233/sist-en-28094-1997](https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997)

Ta slovenski standard je istoveten z: EN 28094:1994

ICS:

53.040.20 Deli za transporterje Components for conveyors

SIST EN 28094:1997

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 28094:1997

<https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997>

EUROPEAN STANDARD

EN 28094

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 1994

UDC 621.967.21.06:620.179.4

Descriptors: Conveyor belts, wire rope, steels, adhesion tests, adhesion, adhesive strength, coatings, equipment, procedure

English version

**Steel cord conveyor belts - Adhesion strength test
of the cover to the core layer (ISO 8094:1984)**

Courroies transporteuses à câbles d'acier - Essai d'adhérence du revêtement à la couche de câbles (ISO 8094:1984) Stahlseilfördergurte - Haftung zwischen der Deckplatte und der Kernschicht (ISO 8094:1984)

(standards.iteh.ai)SIST EN 28094:1997

<https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997>

This European Standard was approved by CEN on 1994-02-08. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
EN 28094:1994

Foreword

This European Standard has been taken over by the Technical Committee CEN/TC 188 "Conveyor belts" from the work of ISO/TC 41 "Pulleys and belts (including veebelts)" of the International Organization for Standardization (ISO).

CEN/TC 188 decided to submit this document to the Unique Acceptance Procedure (UAP).

The result of the Unique Acceptance Procedure (UAP) was positive.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 1994, and conflicting national standards shall be withdrawn at the latest by August 1994.

In accordance with the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

SIST EN 28094:1997

<https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997>

The text of the International Standard ISO 8094:1984 was approved by CEN as a European Standard without any modification.

International Standard



8094

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Steel cord conveyor belts — Adhesion strength test of the cover to the core layer

Courroies transporteuses à câbles d'acier — Essai d'adhérence du revêtement à la couche de câbles

First edition — 1984-12-15

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 28094:1997](https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997)

<https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997>

UDC 621.867.2 : 620.179.4

Ref. No. ISO 8094-1984 (E)

Descriptors : conveyor belts, tests, adhesion tests, determination, adhesive strength.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 8094 was prepared by Technical Committee ISO/TC 41, *Pulleys and belts (including veebelts)*.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 28094:1997](https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997)

<https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997>

Steel cord conveyor belts — Adhesion strength test of the cover to the core layer

1 Scope and field of application

This International Standard specifies a test method for determining the adhesion strength of the cover to the core layer.

It applies exclusively to steel cord conveyor belts.

b) Belts with metallic weft

length (in the direction of the cord layer) : 150 mm min.

width : $25 \pm 0,5$ mm

thickness : full thickness of the belt

2 References

ISO 36, *Rubber, vulcanized — Determination of adhesion strength to textile fabric.*¹⁾

ISO 471, *Rubber — Standard temperatures, humidities and times for the conditioning and testing of test pieces.*

ISO 6133, *Rubber and plastics — Analysis of multi-peak traces obtained in determinations of tear strength and adhesion strength.*

Cut the specimens parallel to the axis of the belt or transversally as the case may be and at least 50 mm from the belt edge.

Using a knife, cut the cover rubber on either side of the specimen along the upper and lower edges of the cords along a length sufficient for a safe grip in the jaws of the test machine.

6 Procedure

6.1 Carry out the test in accordance with ISO 36, at least five days after manufacture of the belt.

Unless otherwise specified, and so indicated in the test report, carry out the test at 23 ± 2 °C and 50 ± 5 % relative humidity.

6.2 From the first three specimens, fix the top cover in one jaw of the test machine, and the core layer including the cords (without the bottom cover) in the other jaw.

6.3 Start the test machine, with the gap widening speed of the jaws maintained constant at 100 ± 10 mm/min.

6.4 Record a graphical plot of the force.

6.5 From the remaining three specimens, fix the bottom cover in one jaw, and the core layer including the cords in the other jaw, and repeat the test in accordance with 6.3 and 6.4.

6.6 Carry out three tests.

6.7 If the adhesion strength of the cover to the core layer is greater than the tear strength of the core layer, the maximum force obtained is recorded together with the mode of failure.

3 Test principle

Measurement of the force required to separate the covers from the core layer by stripping.

4 Apparatus

Tensile test machine with jaws, in accordance with the equipment described in ISO 36.

5 Specimens

Take six specimens with the following dimensions :

a) Belts without weft, with or without textile reinforcement

length (in the longitudinal direction of the belt) : 150 mm min.

width : 25 mm min. and containing at least two steel cords

thickness : full thickness of the belt

1) At present at the stage of draft. (Revision of ISO/R 36-1969.)

ISO 8094-1984 (E)

7 Expression of results

7.1 From the recordings of the separating force variations, determine the median force \tilde{F} in accordance with ISO 6133.

7.2 For each test the adhesion strength T of the cover to the core layer, in newtons per millimetre, is calculated by the formula :

$$T = \frac{\tilde{F}}{b}$$

where b is the width of the specimen expressed in millimetres.

7.3 Calculate separately the mean for the top and the bottom cover by the formula :

$$\bar{T} = \frac{T_1 + T_2 + T_3}{3}$$

7.4 Round off single values T and mean values \bar{T} to 0,1 N/mm.

8 Test report

The test report shall include the following information :

- a) a reference to this International Standard;
- b) the identification of the belt tested;
- c) the width of the specimens;
- d) the adhesion strengths of the top cover and the bottom cover respectively to the core layer in accordance with clause 7;
- e) any operating details not specified in this International Standard or considered as optional, together with any events which are likely to have influenced the results.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 28094:1997](https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997)

<https://standards.iteh.ai/catalog/standards/sist/9af39462-d73e-457c-b4b2-b93b2f99c233/sist-en-28094-1997>