



SLOVENSKI STANDARD
SIST EN ISO 14890:2004
01-junij-2004

HfU_cj]'fU b] \ 'fUbgdcfHY^j 'E'NU hYj Y'nUfU bYfUbgdcfHbYfU_cj Y'n[i a Ybc'U]
d`Ugh] bc`cV`c[c`nUgd`cýbYbUa YbYfGC`%, - \$.&\$\$' Ł

Conveyor belts - Specification for rubber or plastics covered conveyor belts of textile construction for general use (ISO 14890:2003)

Fördergurte - Anforderungen an Textilfördergurte mit Gummi- oder Kunststoff-Deckplatten für allgemeine Anwendungen (ISO 14890:2003)

Courroies transporteuses - Spécification pour courroies tranporteuses a carcasse textile et revetement caoutchouc ou plastique, pour utilisation générale (ISO 14890:2003)

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004>

Ta slovenski standard je istoveten z: EN ISO 14890:2003

ICS:

53.040.20 Deli za transporterje Components for conveyors

SIST EN ISO 14890:2004 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14890:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 14890

May 2003

ICS 53.040.00

English version

**Conveyor belts - Specification for rubber or plastics covered
conveyor belts of textile construction for general use (ISO
14890:2003)**

Courroies transporteuses - Spécification pour courroies
transporteuses recouvertes de caoutchouc ou de plastique à
structure textile, d'usage général (ISO 14890:2003)

Fördergurte - Anforderungen an Textilfördergurte mit
Gummi- oder Kunststoff-Deckplatten für allgemeine
Anwendungen (ISO 14890:2003)

This European Standard was approved by CEN on 10 April 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword	3
Introduction	4
1 Scope	5
2 Normative References	5
3 Terms and definitions	6
4 Designation	7
5 Construction	10
6 Length	10
7 Width	11
8 Rubber cover (see Table 5)	12
9 Tolerances on total belt thickness and cover thickness	14
10 Transverse fabric joints in multi-ply belting	14
11 Longitudinal fabric joints in multi-ply belting and Duo-ply belting	15
12 Longitudinal fabric or carcass joints in solid woven and mono ply belting	15
13 Elongation	16
14 Full thickness tensile strength (see clause 3)	16
15 Adhesion	16
16 Troughability	17
17 Sampling	18
18 Identification	18
Annex A (informative) Items to be agreed between manufacturer and purchaser	19
Annex B (informative) Helpful information to be supplied by the purchaser	20
Annex C (informative) Lateral Drift (Straight Running)	22
Bibliography	23

SIST EN ISO 14890:2004

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004>

Foreword

This document (EN ISO 14890:2003) has been prepared by Technical Committee CEN/TC 188 "Conveyor belts", the secretariat of which is held by BSI, in collaboration with Technical Committee ISO/TC 41 "Pulleys and belts (including veebelts)".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2003, and conflicting national standards shall be withdrawn at the latest by November 2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 14890:2004](https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004)

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004>

Introduction

In the preparation of this Part of this standard, consideration has been given to the work of ISO Committee ISO/TC41/SC3, "Conveyor belts", and the following standards for conveyor belts have been followed as far as possible.

ISO 251:1987	Conveyor belts - Widths and lengths
ISO 252-1	Textile conveyor belts - Adhesive strength between constitutive elements - Part 1 : Methods of test
ISO 282:1992	Conveyor belts - Sampling
ISO 283-1	Textile conveyor belts - Full thickness tensile testing - Part 1: Determination of tensile strength, elongation at break and elongation of the reference load.
ISO 432:1989	Ply type conveyor belts - Characteristics of construction
ISO 433:1991	Conveyor belts - marking
ISO 583:1990	Conveyor belts with a textile carcass – Tolerances on total thickness and thickness of covers – Direct measurement method
ISO 703:1988	Conveyor belts - Troughability - Characteristics of transverse flexibility and test method

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 14890:2004](https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004)

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d7bc364/sist-en-iso-14890-2004>

1 Scope

This European Standard specifies requirements for rubber and/or plastics covered conveyor belting of textile construction for general surface use on flat or troughed idlers.

This standard is not suitable or valid for light conveyor belts as described in EN 873.

Items that are not requirements of this standard, but need to be agreed between the manufacturer and the purchaser, are included as an informative annex A.

A list of the details that should be supplied by the purchaser of belting with an enquiry is given in informative annex B.

2 Normative References

This European Standard incorporates by dated or undated references, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by an amendment or revision. For undated references the last edition of the publication referred to applies (including amendments).

ISO 37, *Rubber, vulcanized or thermoplastic - Determination of tensile stress-strain properties.*

ISO 188, *Rubber, vulcanized or thermoplastic - Accelerated ageing and heat-resistance tests.*

ISO 282, *Conveyor belts – Sampling.*

ISO 4649, *Rubber, vulcanized or thermoplastic - Determination of abrasion resistance using a rotating cylindrical drum device.*

ISO 10247, *Conveyor belts – Characteristics of covers – Classification.*

EN ISO 252-1, *Textile conveyor belts - Adhesion strength between constitutive elements - Part 1: Methods of test (ISO 252-1:1999).*

EN ISO 283-1, *Textile conveyor belts – Full thickness tensile testing – Part 1: Determination of tensile strength, elongation at break and elongation at the reference load (ISO 283-1:2000).*

EN ISO 583-1, *Conveyor belts with a textile carcass - Total thickness and thickness of elements - Part 1: Methods of test (ISO 583-1:1999).*

EN ISO 14890:2003 (E)

EN ISO 703-1, *Conveyor belts - Transverse flexibility and troughability - Part 1: Test method (ISO 703-1:1999)*.

EN 12882, *Conveyor belting for general purpose use - Electrical and flammability safety requirements*.

prEN ISO 16851, *Textile conveyor belts - Determination of the net length of an endless (spliced) conveyor belt (ISO/DIS 16851:1998)*.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1**tensile strength**

greatest measured force during the tensile test divided by the width of the test piece . It is expressed in N/mm

3.2**reference force (reference load)**

one-tenth of the nominal tensile strength in the longitudinal direction multiplied by the width of the test piece in mm. It is expressed in Newtons

Example:

Nominal tensile strength = 1 600 N/mm

Reference force = 160N/mm

Reference force for 25 mm test piece = 25mm × 160 N/mm = 4 000 N.

NOTE This definition does not imply that a 10:1 factor should be used in design calculations, but it is important to bear in mind that any belt with any form of joint or splice should be capable of transmitting the desired working strength.

3.3**slab belting**

conveyor belting made in wide widths and long lengths for subsequent slitting and cutting into narrower widths and shorter lengths to suit individual conveyor installations

3.4**solid woven belting**

conveyor belting consisting of a carcass of more than one ply, the plies being interlocked in the weave, or bound together by binding threads in the course of weaving

3.5**mono-ply belting**

conveyor belting with a carcass consisting of one ply of woven textile fabric

3.6**duo-ply belting**

conveyor belting with a carcass consisting of two plies of woven textile fabric bonded together by an intermediate layer of elastomer of sufficient thickness to allow the incorporation of a tension element in the joint

3.7**multi-ply belting**

Conveyor belting with a carcass of two or more plies of woven textile fabric, the adjacent plies being bonded together by an intermediate layer of elastomer

3.8**primary yarn**

load carrying yarn which contributes more than 50 % of the tensile strength

3.9**secondary yarn**

load carrying yarn which contributes less than 50 % of the tensile strength

4 Designation

iTeh STANDARD PREVIEW

4.1 Belting is designated by reference to the following conveyor belt characteristics :

- a) reference to this European Standard, i.e. EN ISO 14890;
- b) the required length in metres;
- c) the required width in millimetres (see Table 4);
- d) the fibre type of the carcass, in both the warp and weft directions, e.g. polyester (E) (warp) polyamide (P), (weft) (EP) (see Table 1);
- e) the full thickness tensile strength in N/mm of belt width (see Table 8);
- f) the number of plies or belt type (see clause 3);
- g) top cover thickness in millimetres;
- h) bottom cover thickness in mm (where relevant, see clause 5);
- j) cover classification (see Table 5), where appropriate;
- k) safety category according to EN 12882.

4.2 Examples of ordering are given below

Example 1: Multiply-ply belt

A 400 m long belt, 1 200 mm wide, textile material in the longitudinal direction of polyester (E) and in the transverse direction of polyamide (P), having a minimum full thickness tensile strength of 1 000 N/mm belt width, with 5 plies and a top cover thickness of 4 mm, a bottom cover thickness of 2 mm, a cover classification of H in accordance with Table 5, and complying with the safety requirements of category 1 of EN 12882.

Example 1 - Designation

EN ISO	Length	Width	Textile material		Tensile Strength N/mm	No of plies	Cover gauge (mm)		Cover Class	Safety category according to EN 12882
			Warp	Weft			Top	Bottom		
14890	(m)	(mm)	E	P	1 000	5	4	2	H	1

Example 2: Duo-ply belt

(standards.iteh.ai)

A 200 m long belt, 1 000 mm wide, textile material in the longitudinal direction of polyester cotton (EB) and in the transverse direction of polyamide cotton (PB), having a minimum full thickness tensile strength of 800 N/mm, with 2 plies and a top and bottom cover of 1,5mm, complying with the safety requirements of category 2A of EN 12882.

Example 2 - Designation

EN ISO	Length	Width	Textile material		Tensile Strength N/mm	No of plies	Cover gauge (mm)		Cover Class	Safety category according to EN 12882.
			Warp	Weft			Top	Bottom		
14890	(m)	(mm)	EB	PB	800	2	1,5	1,5	N/A	2A

Example 3: Mono-ply

A 150 m long, 1 200 mm wide Mono-ply belt, having a polyester warp (E) and a polyamide weft (P), a full thickness tensile strength of 630 N/mm belt width and a top cover thickness of 6 mm, a bottom cover thickness of 2 mm, and a cover classification of D in accordance with Table 5, complying with safety requirement of category 1 of EN 12882.

Example 3 - Designation

EN ISO	Length	Width	Textile material		Tensile Strength N/mm	No of plies	Cover gauge (mm)		Cover Class	Safety category according to EN 12882
			Warp	Weft			Top	Bottom		
14890	(m)	(mm)	E	P	630	1	6	2	D	1

Example 4: Solid woven belt

A 300 m long, 1 600 mm wide Solid Woven belt having a combined polyester and polyamide warp (EP) and a polyamide cotton weft (PB) and an integrally woven cotton (B) warp pile, having a minimum tensile strength of 1 250 N/mm belt width and 1,5 mm top and bottom covers, complying with safety requirement of category 3A of EN 12882.

<https://standards.iteh.ai/catalog/standards/sist/05c6b43e-df2f-4cff-8cb5-85c01d76c39c/sist-en-iso-14890-2004>

Example 4 - Designation

EN ISO	Length	Width	Textile material		Tensile Strength N/mm	No of plies	Cover gauge (mm)		cover class	Safety category according to EN 12882
			Warp	Weft			Top	Bottom		
14890	(m)	(mm)	EP(B)	PB	1250	SW(1)	1,5	1,5	N/A	3A