ISO/DIS-PRF 15614-13:2023(E)

ISO/TC 44/SC 6

Secretariat: DIN

Date: 2023-09-18

Specification and qualification of welding procedures for metallic materials — Welding procedure test—___

Part 13: Upset (resistance butt) and flash welding

Partie 13: Soudage en bout par résistance pure et soudage par étincelage

https://standards.iteh.ai/catalog/standards/sist/7d8906b6-3663-4f8f-93f2-def3ad5fb007/iso-prf-15614-13

FDIS stage

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no Part part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: + 41 22 749 01 11

Fax: +41 22 749 09 47

Email E-mail: copyright@iso.org

Website: www.iso.org

Published in Switzerland

iTeh STANDARD PREVIEW (standards.iteh.ai)

https://standards.iteh.ai/catalog/standards/sist/7d8906b6-3663-4f8f-93f2-def3ad5fb007/iso-prf-15614-13

Contents

Forew	vord	V
Introd	duction	vii
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Preliminary welding procedure specification	2
5	Welding procedure test	2
6	Test pieces and test specimens	3
6.1	General	3
6.2	Shape and dimensions of test specimens	3
6.2.1	General	3
6.2.2	Tensile test specimen	4
6.2.3	Bend test specimen	4
6.2.4	Cupping test specimen	4
6.2.5	Hardness test specimen	4
6.2.6	Bend test specimen using thin sheets	4
6.3	Welding of components, test pieces or test specimens	5
7	Testing and examination	5
7.1	Extent of testing	5
7.2	Non-destructive testing (NDT)	<u></u> 5
7.2.1	General prf-15614-13	5
7.2.2	Visual test	5
7.2.3	Penetrant test	5
7.2.4	Magnetic particle test	5
7.2.5	Eddy current test	5
7.2.6	Ultrasonic test	5
7.3	Destructive tests	5
7.3.1	Tensile test	5
7.3.2	Three-point bend test	5
7.3.3	Cupping test	6
7.3.4	Bend test	6
7.4	Macrosection	6
7.5	Hardness distribution	6
7.6	Retesting	6
8	Range of qualification	6
8.1	General	6
8.2	Related to the manufacturer	6
8.3	Related to the parent metal	6

8.4	Welding procedures	7
8.4.1	Welding process	7
8.4.2	Welding equipment	7
8.4.3	Pre- or post-weld heat treatment	7
9	Welding procedure qualification record (WPQR)	7
Annex	A (informative) Example of a welding procedure qualification record (WPQR) form	8
Riblio	granhy	13

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF_15614-13 https://standards.iteh.ai/catalog/standards/sist/7d8906b6-3663-4f8f-93f2-def3ad5fb007/iso prf-15614-13

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 6, *Resistance welding and allied mechanical joining*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This fourth edition cancels and replaces the third edition (ISO 15614-13:2021), which has been technically revised.

The main changes are as follows:

- petal test changed to bend test and bend test changed to three-point bend test;
- —scope aligned with ISO 15614-1;
- <u>Clauses 2, 3</u>— <u>Clauses 2, 3, 7, 7</u> and 88 updated;
- —clause numbering revised;
- Annex A— Annex A and Annex B were combined into a new Annex AAnnex A.
- Table 1— Table 1 modified;
- Clause 9 aligned with <u>ISO</u> 15614-1;

A list of all parts in the ISO 15614 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: https://committee.iso.org/sites/tc44/home/interpretation.html.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF 15614-13 https://standards.iteh.ai/catalog/standards/sist/7d8906b6-3663-4f8f-93f2-def3ad5fb007/iso-prf-15614-13

Introduction

It is intended that all new welding procedure qualifications be carried out in accordance with this document from the date of its publication.

However, this document does not invalidate previous welding procedure qualifications made to other standards or specifications, provided the intent of its technical requirements is satisfied and the previous welding procedure qualifications are relevant to the application and production work on which they are to be employed.

The primary purpose of welding procedure qualification is to demonstrate that the joining process proposed for construction is capable of producing joints having the required mechanical properties for the intended application.

Details of the ISO 15614 series are given in ISO 15607:2019, Annex A.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF 15614-13 https://standards.iteh.ai/catalog/standards/sist/7d8906b6-3663-4f8f-93f2-def3ad5fb007/isoprf-15614-13

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/PRF 15614-13

https://standards.iteh.ai/catalog/standards/sist/7d8906b6-3663-4f8f-93f2-def3ad5fb007/iso-prf-15614-13

Specification and qualification of welding procedures for metallic materials — Welding procedure test—___

Part 13:

Upset (resistance butt) and flash welding

1 Scope

This document specifies how a preliminary welding procedure specification (pWPS) is qualified by welding procedure tests.

This document defines the conditions for the execution of welding procedure tests and the range of qualification for welding procedures for all welding operations within the qualification of this document.

The primary purpose of welding procedure qualification is to demonstrate that the joining process proposed for construction is capable of producing joints having the required mechanical properties for the intended application.

Two classes of welding procedure tests are given in order to permit application to a wide range of welded fabrication. They are designated by classes A and B. In class A, the extent of testing is greater and the ranges of qualification are more restrictive than in class B.

Procedure tests carried out to class A automatically qualify for class B requirements, but not vice-versa.

When no class is specified in a contract or application standard, all the requirements of class A apply.

NOTE Class B corresponds to level 1 and class A corresponds to level 2 in accordance with ISO 15614-1.

This document applies to upset (resistance butt) welding and flash welding of any metallic materials in all product forms (e.g. with solid, tubular, flat or circular cross-sections). It covers the following resistance welding processes, as defined in ISO 4063:2023:

- 24_ flash welding, using direct current or alternating current with various movement sequences, constant flashing and pulsed flashing;
- 25_ resistance butt welding (upset welding), using direct current or alternating current with various current and pressure sequences.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 669, Resistance welding — Resistance welding equipment — Mechanical and electrical requirements

ISO 4136, Destructive tests on welds in metallic materials — Transverse tensile test

ISO 5173, Destructive tests on welds in metallic materials — Bend tests

ISO 6520–2, Welding and allied processes — Classification of geometric imperfections in metallic materials — Part 2: Welding with pressure

ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature

ISO 9015–2, Destructive tests on welds in metallic materials — Hardness testing — Part 2: Microhardness testing of welded joints

ISO 11666, Non-destructive testing of welds — Ultrasonic testing — Acceptance levels

ISO 14732, Welding personnel — Qualification testing of welding operators and weld setters for mechanized and automatic welding of metallic materials

ISO 15607:2019, Specification and qualification of welding procedures for metallic materials — General rules

ISO/TR 15608, Welding — Guidelines for a metallic materials grouping system

ISO 15609-_5, Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding

ISO 15614-1, Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 1: Arc and gas welding of steels and arc welding of nickel and nickel alloys

ISO 15620:2019, Welding — Friction welding of metallic materials

ISO 17638, Non-destructive testing of welds — Magnetic particle testing

ISO 17639, Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds

ISO 17640, Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment

ISO 17643, Non-destructive testing of welds—Eddy current testing of welds by complex-plane analysis

ISO 23277, Non-destructive testing of welds — Penetrant testing — Acceptance levels

ISO 23278, Non-destructive testing of welds Magnetic particle testing Acceptance levels

ISO 23279, Non-destructive testing of welds — Ultrasonic testing — Characterization of discontinuities in welds

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 669, ISO $\frac{15607}{6520-2}$ and ISO $\frac{6520-215607}{6520-2}$ apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

4 Preliminary welding procedure specification

The pWPS shall be prepared in accordance with ISO 15609-_5. It shall specify all relevant parameters and requirements.

5 Welding procedure test

The welding and testing of test pieces shall be in accordance with <u>Clauses 6 Clauses 6 and 77.</u>

Any weld setter for resistance welding who satisfactorily undertakes the welding procedure test in accordance with this document shall be qualified for the appropriate range of qualification given in ISO 14732.

6 Test pieces and test specimens

6.1 General

The welded assembly tested shall be the actual component used in production. Test specimens shall be cut from the actual component.

If not possible, comparable welds shall be performed on test specimens according to references included in $6.2\frac{6.2}{6.2}$.

6.2 Shape and dimensions of test specimens

6.2.1 General

The testing includes non-destructive testing (NDT) and/or destructive testing.

The selection of test class A or B, test types and the number of test specimens depends on the performance, safety and quality requirements of the component or assembly and shall be established before any qualification is undertaken.

Examples are given in <u>Table 1</u><u>Table 1</u>.

If not otherwise specified, test specimens of the shape and dimensions stipulated in 6.2.26.2.2 to 6.2.66.2.6 shall be used.

Table 1 — Examples for testing and examination of test specimens

	 IS	Extent of test ^a		
Work piece https://standards	Test type .iteh.ai/catalog/standa	rds/sist/7d/ Class B -3663-4f8f	93f2-def3aClass A)7/iso-	
Bars/rods	Visual test	Every weld	Every weld	
	Penetrant test ^b	Every weld	Every weld	
	Tensile test	_	Three specimens ^c	
	Three-point bend test	Two specimens ^c	Six specimens ^c	
	Macrosection ^d	_	One weld	
	Hardness test ^d	_	One measuring rowe	
Hollow profile	Visual test	Every weld	Every weld	
	Penetrant test ^b	Every weld	Every weld	
	Tensile test	Two specimens	Three specimens	
	Bend test	Two specimens ^c	Six specimens ^c	
	Macrosection ^{d,f}	_	One weld ^c	
	Hardness test ^d		One measuring rowe	
Sheet metal and	Visual test	Every weld ^g	Every weld ^g	
strips	Penetrant test ^b	_	Every weld ^g	
	Tensile test ^h	Two specimens per weld joint ^g	Three specimens per weld joint ^g	