



Designation: **D7119/D7119M—13 D7119/D7119M – 13a**

## Standard Guide for Sampling Spray Polyurethane Foam and Coating in Roofing<sup>1</sup>

This standard is issued under the fixed designation D7119/D7119M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This guide covers the removal of test specimens from spray polyurethane foam (SPF) roofing systems in the field for the purpose of examination of an existing system and/or quality assurance for new installations. It describes the types and purposes of sample cuts, visual inspection techniques, laboratory physical property tests, and repair of the core and slit sample holes.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[C1029 Specification for Spray-Applied Rigid Cellular Polyurethane Thermal Insulation](#)

[D1079 Terminology Relating to Roofing and Waterproofing](#)

[D1621 Test Method for Compressive Properties of Rigid Cellular Plastics](#)

[D1622 Test Method for Apparent Density of Rigid Cellular Plastics](#)

[D4442 Test Methods for Direct Moisture Content Measurement of Wood and Wood-Base Materials](#)

[D6705 Guide for Repair and Recoat of Spray Polyurethane Foam Roofing Systems](#)

### 3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminology [D1079](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *core samples, n*—cylindrical sections of approximately 50 to 75 mm [2 to 3 in.] in diameter. They shall be cut using a round metal template or coring tool, and they shall extend from surface down to but not through the substrate.

3.2.2 *slit samples, n*—crescent-shaped samples approximately 13 mm [ $\frac{1}{2}$  in.] wide, 19 mm [ $\frac{3}{4}$  in.] deep, and 50 to 75 mm [2 to 3 in.] long, cut with a sharp knife. Slit samples are used to examine the uppermost polyurethane foam layers and the coating system.

3.3 *lift, n*—an individual layer of polyurethane foam that results from a single pass of the spray gun.

### 4. Significance and Use

4.1 Adequate coating thickness (mil thickness) is necessary to protect polyurethane foam from the effects of ultraviolet degradation. This guide outlines general procedures for sampling and measuring the coating thickness by using slit or core samples.

4.2 Thickness of individual lifts of sprayed foam will have a bearing upon foam stability. Core samples are used to determine foam thickness. Compressive strength and core density affect resistance to foot traffic and impact. Specimens from core samples

<sup>1</sup> This guide is under the jurisdiction of ASTM Committee [D08](#) on Roofing and Waterproofing and is the direct responsibility of Subcommittee [D08.06](#) on Spray Polyurethane Foam Roof Systems.

Current edition approved ~~Jan 15, 2013~~ Aug. 1, 2013. Published ~~February 2013~~ August 2013. Originally approved in 2007. Last previous edition approved in ~~2007~~ 2013 as ~~D7119—07~~ D7119 – 13. DOI: ~~10.1520/D7119—D7119M—13~~ 10.1520/D7119\_D7119M—13A.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.