

Designation: D7835/D7835M - 13

Standard Test Method for Determining the Solvent Resistance of an Organic Coating using a Mechanical Rubbing Machine¹

This standard is issued under the fixed designation D7835/D7835M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a mechanical rub method for assessing the solvent resistance of an organic coating that chemically and/or physically changes during the curing process. This technique can be used in the laboratory, in the field, or in the fabricating shop.

1.2 This test method does not specify the solvent, number of double rubs, or expected test results.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- D4138 Practices for Measurement of Dry Film Thickness of Protective Coating Systems by Destructive, Cross-Sectioning Means
- D5402 Practice for Assessing the Solvent Resistance of Organic Coatings Using Solvent Rubs
- D5796 Test Method for Measurement of Dry Film Thickness of Thin-Film Coil-Coated Systems by Destructive Means Using a Boring Device
- D6132 Test Method for Nondestructive Measurement of Dry

Film Thickness of Applied Organic Coatings Using an Ultrasonic Coating Thickness Gage

D7091 Practice for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to Ferrous Metals and Nonmagnetic, Nonconductive Coatings Applied to Non-Ferrous Metals

3. Terminology

3.1 Definitions:

3.1.1 *double rub, n*—one complete forward and backward motion over a coated surface under specific conditions, which are characterized by the force applied normal to the surface, the length of travel, and rate of speed.

4. Summary of Test Method

4.1 An automated machine is used to test the solvent resistance of a coating by rubbing a cloth saturated with the solvent across the coating and counting the number of strokes (double rubs) to coating break-through or failure.

5. Significance and Use

5.1 Many coatings used in the coil coating and other industries achieve a degree of solvent resistance after they have experienced a bake condition characterized by exposure to elevated temperatures in an oven over time. Insufficient bake, or occasionally over bake, may affect the intended chemical bonds or physical curing of the film and result in reduced solvent resistance.

5.2 The mechanical rubbing machine provides consistent stroke length, rate, pressure, and contact area that are not subject to variables such as human fatigue (see Practice D5402).

5.3 Factors other than bake can influence degree of solvent resistance of a coated surface. Paint film chemistry and composition, surface preparation, oven dwell time, oven air velocity, ambient oven temperature, oven profiling, film thickness, etc., all are influential. The test solvent used in the rub machine has a significant effect on the number of double rubs measured. Common solvents used for these tests include Methyl Ethyl Ketone (MEK), Methyl Isobutyl Ketone (MIBK), and Isopropyl Alcohol to name a few. The specific solvent to be used and the umber of double rubs to be achieved should be

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

D740 Specification for Methyl Ethyl Ketone

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.53 on Coil Coated Metal.

Current edition approved July 1, 2013. Published August 2013. DOI: 10.1520/ $\mathsf{D7835/D7835M-13}$

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.