



Designation: C1670 – 13

Standard Specification for Adhered Manufactured Stone Masonry Veneer (AMSMV) Units¹

This standard is issued under the fixed designation C1670; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The purpose of this standard is to establish the minimum product specifications for adhered manufactured stone masonry veneer units. These units are manufactured using a wet cast concrete mixture and finished to simulate stone, rocks found in nature, and other textures.

1. Scope

1.1 This specification covers the minimum product requirements for adhered manufactured stone masonry veneer (AMSMV) units applied as an adhered veneer to exterior and interior walls and structures suitable to receive AMSMV units.

1.2 The property requirements of this specification apply at the time of delivery. This standard does not address the physical evaluation of installed AMSMV units removed from service.

1.3 The AMSMV units described by this specification are manufactured from a mixture of cement, normal or lightweight aggregates (or a combination of both), water, admixtures, other cementitious materials and other components which are wet-cast into shapes simulating the appearance of natural stone and other textures.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes shall not be considered as requirements of the standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use of AMSMV units.*

¹ This test method is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.03 on Concrete Masonry Units and Related Units.

Current edition approved June 15, 2013. Published August 2013. DOI: 10.1520/C1670-13

2. Referenced Documents

2.1 ASTM Standards:

- C31/C31M Practice for Making and Curing Concrete Test Specimens in the Field
- C33 Specification for Concrete Aggregates
- C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens
- C140 Test Methods for Sampling and Testing Concrete Masonry Units and Related Units
- C150 Specification for Portland Cement
- C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory
- C207 Specification for Hydrated Lime for Masonry Purposes
- C260 Specification for Air-Entraining Admixtures for Concrete
- C330 Specification for Lightweight Aggregates for Structural Concrete
- C331 Specification for Lightweight Aggregates for Concrete Masonry Units
- C426 Test Method for Linear Drying Shrinkage of Concrete Masonry Units
- C482 Test Method for Bond Strength of Ceramic Tile to Portland Cement Paste
- C494/C494M Specification for Chemical Admixtures for Concrete
- C595 Specification for Blended Hydraulic Cements
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C666/C666M Test Method for Resistance of Concrete to Rapid Freezing and Thawing
- C979 Specification for Pigments for Integrally Colored Concrete
- C989 Specification for Slag Cement for Use in Concrete and Mortars
- C1116/C1116M Specification for Fiber-Reinforced Concrete

[C1157 Performance Specification for Hydraulic Cement](#)
[C1232 Terminology of Masonry](#)
[C1240 Specification for Silica Fume Used in Cementitious Mixtures](#)

3. Terminology

3.1 Terminology defined in Terminology [C1232](#) shall apply for this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *adhered manufactured stone masonry veneer (AMSMV) unit, n*—a non-load bearing masonry unit that is produced by wet-cast blending of cementitious material, lightweight and other aggregates, pigments and admixtures, designed to be applied with a cementitious mortar to a backing surface.

3.2.2 *AMSMV Unit Profile, n*—the combination of AMSMV units that represent the range of shapes and sizes provided in the specified veneer.

3.2.3 *average thickness, n*—the mean of the depth measurement of the unit as measured from the back side to the face side.

3.2.4 *designated area, n*—the area of a completed wall section that is used to verify compliance.

3.2.5 *saturated density, n*—the water saturated weight of the cured specimen divided by the volume of the specimen.

3.2.6 *wet cast, adj*—manufactured from a measurable slump concrete.

4. Materials

4.1 Cementitious materials shall conform to the following applicable specifications:

- 4.1.1 *Portland Cement*—Specification [C150](#).
- 4.1.2 *Blended Hydraulic Cements*—Specification [C595](#).
- 4.1.3 *Pozzolans*—Specification [C618](#).
- 4.1.4 *Slag Cement*—Specification [C989](#).
- 4.1.5 *Hydraulic Cement*—Specification [C1157](#).
- 4.1.6 *Silica Fume*—Specification [C1240](#).
- 4.1.7 *Hydrated Lime*—Specification [C207](#).

4.2 *Aggregates*—Aggregates shall conform to the following specifications:

- 4.2.1 *Normal Weight Aggregates*—Specification [C33](#).
- 4.2.2 *Lightweight Aggregates*—Specification [C330](#) or [C331](#).
- 4.3 *Air-Entraining Admixtures*—Specification [C260](#).
- 4.4 *Concrete Admixtures*—Specification [C494/C494M](#).
- 4.5 *Coloring Pigments*—Specification [C979](#).
- 4.6 *Reinforcement Fibers*—Specification [C1116/C1116M](#).
- 4.7 *Other Constituents:*

4.7.1 Other constituent materials shall be shown by test of experience or history of performance under equivalent conditions not to be detrimental to the durability of the AMSMV unit, or AMSMV construction, or both.

5. Sampling

5.1 *Concrete Mix for AMSMV Units*—From each manufacturing location, obtain representative samples from standard production of each concrete mix used for AMSMV units in accordance with [5.2](#).

5.1.1 Sample and test the concrete mixes used for AMSMV units no more than twelve months prior to production of units. More frequent testing shall be required if there is any change in the manufacturing process including changes in cementitious materials or their sources, aggregates or their sources, volume of water, mix design, manufacturing process or curing. This does not include producing units of varying shapes, configurations or sizes of units.

5.2 Sample the concrete mix at the manufacturing facility from standard production mix in accordance with Practice [C31/C31M](#); with the following exceptions:

5.2.1 For compressive strength testing prepare five 4 in. diameter by 8 in. (100 mm by 200 mm) cylinders in accordance with Practice [C192/C192M](#) and test in accordance with [6.1](#). Do not disturb the curing cylinders for a minimum of 48 hours after casting. De-mold them at an age of seven days.

5.2.2 For freeze/thaw durability testing, prepare five 3 in. by 3 in. by 11 in. beams in accordance with Section 7 of Practice [C192/C192M](#).

5.2.2.1 The molded beams shall be de-molded 24-32 hours after casting.

5.2.2.2 The molded beams shall be air cured for 28 days.

5.3 *AMSMV Units*—From each manufacturing location, obtain a minimum of eight (8) samples totaling at least 5 ft² (0.46 m²) of AMSMV units that are representative of the AMSMV unit profile from which they are selected, using the same cementitious materials, aggregates, mix design, manufacturing process and curing.

5.3.1 Sampling and testing should be performed at least annually to meet the requirements of this standard.

6. Physical Properties and Testing Requirements of AMSMV Unit Concrete Mix

6.1 *Compressive Strength:*

6.1.1 Test specimens at an age of 28 days in accordance with Test Method [C39/C39M](#).

6.1.1.1 The average compressive strength of five specimens shall be a minimum of 2100 psi (15 MPa) with no individual specimen having a measured compressive strength less than 1800 psi (12 MPa).

6.2 *Resistance to Freezing and Thawing:*

6.2.1 No single specimen in a group of five specimens shall exhibit a mass loss greater than 1.5 % or show any fracture completely through the cross section when tested in accordance with Test Method [C666/C666M](#), Procedure A, with the following modifications:

6.2.1.1 The molded beams are subjected to 50 consecutive cycles of freezing and thawing.

6.2.2 Determine mass loss in accordance with the following procedure:

6.2.2.1 Following immersion in water for a period of 48 hours, the initial specimen mass shall be measured. Excess