



Designation: **D3995 – 02 (Reapproved 2008) D3995 – 13**

## Standard Performance Specification for Men's and Women's Knitted Career Apparel Fabrics: Dress and Vocational<sup>1</sup>

This standard is issued under the fixed designation D3995; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This performance specification covers the minimum performance requirements for men's and women's knitted fabrics for dress and vocational career apparel composed of any textile fiber or mixtures of textile fibers.

1.2 This performance specification is not applicable to career apparel fabrics such as those used in protective clothing, that do not patently fit the categories in Career 3.1.1 and Apparel or 3.1.2. Career Apparel, Dress (see Terminology D7022 for these terms). Minimum performance specifications for such fabrics should be as agreed between the purchaser and the seller.

1.3 These requirements apply to the length and width directions for those factors where each fabric direction is pertinent.

1.4 The following precautionary statement pertains only to the test methods portion, Section 7, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

[D123 Terminology Relating to Textiles](#)

[D2724 Test Methods for Bonded, Fused, and Laminated Apparel Fabrics](#)

[D2905 Practice for Statements on Number of Specimens for Textiles \(Withdrawn 2008\)<sup>3</sup>](#)

[D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method](#)

[D3787 Test Method for Bursting Strength of Textiles—Constant-Rate-of-Traverse \(CRT\) Ball Burst Test](#)

[D7022 \(Withdrawn 2013\)<sup>3</sup>](#)

#### 2.2 AATCC Methods:<sup>4</sup>

[AATCC 8 Colorfastness to Crocking: AATCC-Crockmeter Method](#)

[AATCC 15 Colorfastness to Perspiration](#)

[AATCC 16.3 Colorfastness to Light](#)

[AATCC 23 Colorfastness to Burnt Gas Fumes](#)

[AATCC 61 Colorfastness to Washing, Domestic Laundering, Commercial Laundering: Accelerated](#)

[AATCC 116 Colorfastness to Crocking, Rotary Vertical Crockmeter Method](#)

[AATCC 124 Smoothness Appearance of Durable Press Fabrics After Repeated Home Launderings](#)

[AATCC 132 Colorfastness to Drycleaning](#)

[AATCC 135 Dimensional Change in Automatic Home Laundering of Durable Press Woven or Knit Fabrics Changes of Fabrics After Home Laundering](#)

[AATCC 172 Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering](#)

[AATCC 188 Colorfastness to Sodium Hypochlorite Bleach in Home Laundering](#)

[Evaluation Procedure 1 Gray Scale for Color Change](#)

[Evaluation Procedure 2 Gray Scale for Staining](#)

<sup>1</sup> This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel. Current edition approved Aug. 1, 2008; July 1, 2013. Published October 2008; August 2013. Originally approved in 1981. Last previous edition approved in 2002 as D3995 – 02: D3995 – 02(2008). DOI: 10.1520/D3995-02R08; 10.1520/D3995-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>4</sup> Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, http://www.aatcc.org.

Evaluation Procedure [38 Chromatic 9-Step Transference Scale](#)

2.3 Federal Standard:<sup>5</sup>

16 CFR 1610 Standard for Flammability of Clothing Textiles

NOTE 1—The specific dated editions of ASTM test methods that prevail in this standard are referenced in Section 7 on Test Methods.

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *career apparel, n*—garments which are manufactured for a variety of end uses and for which performance requirements vary.

<sup>5</sup> Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

#### 3.1.1.1 Discussion—

The two major end uses for career apparel are dress apparel and vocational apparel.

3.1.2 *career apparel, dress, n*—a category of tailored uniform in which abusive wear is not common and in which appearance is much more important than durability (see also *career apparel, vocational career apparel*).

3.1.3 *career apparel, vocational, n*—a type of garment worn as a uniform in which abusive wear is common and durability is generally more important than appearance (see also *career apparel, dress career apparel*).

3.1.4 *dimensional change in pressing and finishing, n*—the change in dimensions undergone by a fabric subjected to pressing and finishing during garment manufacturing.

3.1.5 For definitions of other terms used in this specification, refer to the individual ASTM and AATCC test methods and Terminology [D123](#).

3.1 For definitions of textile terms used in this specification, refer to Terminologies [D123](#) and [D7022](#). For terms relating to chemical or colorfastness testing, refer to specific AATCC methods.

#### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *pressing and finishing, n*—this term takes into account a variety of industrial pressing and finishing treatments used in garment manufacturing.

NOTE 2—No standard method is available for reproducing on a laboratory level the results of industrial press or finishing treatments, or both, used in the manufacture of knitted apparel garments.

### 4. Specification Requirements

4.1 The properties of knitted fabric for men's and women's career apparel shall conform to the specification requirement in [Table 1](#).

### 5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the seller, fabrics intended for this end use should meet all of the requirements listed in [Table 1](#) of this specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in [Table 1](#). Therefore, one or more of the requirements listed in [Table 1](#) may be modified by mutual agreement between the purchaser and the seller.

5.2.1 In such cases, any references to the specification shall specify that: "This fabric meets ASTM Specification D3995 except for the following characteristic(s)."

5.3 Where no prepurchase agreement has been reached between the purchaser and the seller, and in case of controversy, the requirements listed in [Table 1](#) are intended to be used as a guide only. As noted in [5.2](#), ultimate consumer demands dictate varying performance parameters for any particular style of fabric.

5.4 The significance and use of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

### 6. Sampling

6.1 Tests shall be performed on the fabric as it will reach the consumer. Any "partially finished" or "post-finished" fabrics or those which will be pleated, creased, steamed, or pressed during manufacturing should be processed in accordance with the fabric manufacturer's instructions before tests are made.

6.2 Unless otherwise agreed upon, as when specified in an applicable material specification, take the number of specimens directed in each of the applicable test methods.