



Designation: F 106 – 00

Standard Specification for Brazing Filler Metals for Electron Devices¹

This standard is issued under the fixed designation F 106; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers requirements for filler metals suitable for brazing internal parts and other critical areas of electron devices in a nonoxidizing atmosphere (Note 1).

1.2 These materials are available in strip or wire or preforms made by blanking the strip or bending the wire. Powders are also available.

NOTE 1—Brazing filler metals for general applications are specified in AWS Specification A 5.8.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

2. Referenced Documents

2.1 ASTM Standards:

B 214 Test Method for Sieve Analysis of Granular Metal Powders²

E 11 Specification for Wire-Cloth Sieves for Testing Purposes³

F 19 Test Method for Tension and Vacuum Testing Metalized Ceramic Seals⁴

2.2 American Welding Society:

A 5.8 Specification for Brazing Filler Metals⁵

C 3.2 Method for Evaluating the Strength of Brazed Joints⁵

C 3.3 Recommended Practices for Design, Manufacture and Inspection of Critical Brazed Components

3. Classification

3.1 Brazing filler metals which are vacuum grade and are classified on the basis of chemical composition shown in Table

¹ This specification is under the jurisdiction of ASTM Committee F01 on Electronics and is the direct responsibility of Subcommittee F01.03 on Metallic Materials.

Current edition approved Dec. 10, 2000. Published July 2001. Originally published as F 106 – 69 T. Last previous edition F 106 – 95.

² Annual Book of ASTM Standards, Vol 02.05.

³ Annual Book of ASTM Standards, Vol 14.02.

⁴ Annual Book of ASTM Standards, Vol 10.04.

⁵ Available from American Welding Society, 2501 Northwest 7th St., Miami, FL 33125.

1. The difference between Grade 1 and 2 are the impurity limitations. Grade 1 required generally lower levels of impurities.

4. Ordering Information

4.1 Orders for material to this specification shall include the following information:

4.1.1 Quantity,

4.1.2 Dimensions and tolerances (Table 1),

4.1.3 Form (rod, bar, wire, etc.),

4.1.4 AWS classification (Table 2),

4.1.5 Grade 1,

4.1.6 Special requirements or exceptions, and

4.1.7 *Certification*— State if certification is required.

5. Materials and Manufacture

5.1 The brazing filler metals shall be vacuum grade and fabricated by any method that yields a product conforming to the requirements of this specification.

6. Chemical Composition

6.1 The finished brazing filler metal shall conform to the chemical composition shown in Table 2 for Grade 1 material.

7. Mechanical Properties

7.1 Unless otherwise specified, wire shall be furnished in soft temper most suitable for hand feeding or ring winding on mandrels. A minimum elongation of 10 % in 2 in. (50.8 mm) indicates that the wire is annealed.

7.2 Unless otherwise specified, strip shall be furnished in hard as-rolled temper to facilitate clean blanking of thin shims or preforms. A maximum elongation of 5 % in 2 in. designates the strip as hard.

8. Dimensions and Permissible Variations

8.1 These materials must conform to the dimensional limitations listed in Table 2 for strip, wire, and preforms or Table 3 for size of powdered brazing filler metals.

TABLE 1 Dimensional Tolerances (All Plus or Minus)

Width Tolerances, in. (mm)		
Thickness	8 in. (200 mm) wide and under	Over 8 in. (200 mm) wide
Less than 0.020 (0.5)	0.005 (0.125)	0.015 (0.38)
0.020 to 0.050 (0.5 to 1.25), incl	0.010 (0.250)	0.015 (0.38)

Thickness Tolerances—Strip		
Thickness, in. (mm)	8 in. (200 mm) wide and under	Over 8 in. (200 mm) wide
Up to 0.002 (0.05), incl	0.0002 (0.005)	0.0005 (0.0125)
Over 0.002 to 0.003 (0.05 to 0.075), incl	0.0003 (0.0075)	0.0006 (0.015)
Over 0.003 to 0.004 (0.075 to 0.10), incl	0.0004 (0.010)	0.0007 (0.018)
Over 0.004 to 0.006 (0.10 to 0.15), incl	0.0005 (0.0125)	0.0008 (0.02)
Over 0.006 to 0.013 (0.15 to 0.33), incl	0.0010 (0.025)	0.0013 (0.033)
Over 0.013 to 0.021 (0.33 to 0.53), incl	0.0015 (0.038)	0.0018 (0.046)
Over 0.021 to 0.026 (0.53 to 0.66), incl	0.0020 (0.05)	0.0020 (0.05)
Over 0.026 to 0.050 (0.66 to 1.25), incl	0.0020 (0.05)	0.0050 (0.125)

Camber Tolerances—Strip (Edgewise Bowl)		
0.5 in. (12.5 mm) max in 6 ft (1.8 m)		
Diameter Tolerances—Wire		
Diameter, in. (mm)	Tolerance, in. (mm)	
0.010 to 0.020 (0.250 to 0.5)	0.0003 (0.0075)	
Over 0.020 to 0.030 (0.5 to 0.75)	0.0005 (0.0125)	
Over 0.030 to 0.040 (0.75 to 1.0)	0.0007 (0.018)	
Over 0.040 to 0.050 (1.0 to 1.25)	0.0008 (0.02)	
Over 0.050 to 0.060 (1.25 to 1.5)	0.0010 (0.025)	
Over 0.060 to 0.080 (1.5 to 2.0)	0.0015 (0.038)	
Over 0.080 to 0.250 (2.0 to 6.3)	0.0020 (0.05)	

9. Finish

9.1 The surface of strip, wire, or preforms shall be as smooth and free of dirt, oxide, pits, deep scratches, seams, slivers, stains, scale, blisters, edge cracks, trimming burrs, waves, wrinkles, and other defects as best commercial practice will permit.

10. Melting Test (for Cleanness and Spatter)

10.1 *Requirements*— Since cleanness and spattering are important considerations in the use of these materials, a special melting test is used to determine their suitability. For this test, the melting temperatures required are listed in Table X1.1. The material shall also comply with the requirements of 10.2.4.

10.2 Procedure:

10.2.1 The melting test is performed on an “as-received” sample. Cut approximately 1 g (with clean, dry tools) into a clean, dense polycrystalline 99.5 % alumina crucible or clean, fused silica crucible or boat which has been precleaned by air firing at 1100°C (2012°F), min, and stored in a dry, dust-free location until required.

10.2.2 Place samples and crucible in a dense polycrystalline or fused silica combustion tube muffle or equivalent, purge with dry (−40°C) (−40°F) hydrogen, and heat to 20°C (36°F) above the liquidus, hold for 10 min, and then cool to under 65°C (149°F) before stopping the hydrogen flow and removing the sample for inspection.

NOTE 2—If the sample does not melt under these conditions, the

composition is wrong or the temperature measurement is incorrect.

10.2.3 If it is desired also to test for spattering, bridge the crucible or boat by a nickel channel whose legs are designed to allow a small clearance, 0.06 in. (1.6 mm) max. above the crucible. An additional requirement is that the bridge be no more than 0.38 in. (9.5 mm) above the metal bead.

10.2.4 Examine the metal bead at 5× magnification. Just a light smokiness with no discrete black specks is the worst that is permitted. Since this examination depends on experience and judgment, standards can be developed by running carbon determinations and comparing with the maximum carbon limitation listed in Table 2.

10.2.5 If the spatter test is run, examine the bottom side of the nickel bridge, also at 5× magnification, for evidence of any spatter.

11. Rejection

11.1 The seller’s responsibility will be limited to replacement of any filler metal that does not conform to the requirements of this specification.

12. Certification

12.1 A certification, when requested by the user, based on the manufacturer’s quality control that the material conforms to the requirements of this specification, shall be furnished upon request of the purchaser, provided the request is made at the time of cost quotation and at the time of order placement.

TABLE 2 Chemical Composition Requirements (in Wt. %) for Vacuum Grade Filler Metals for Electron Devices^{A,B,C}

NOTE 1—All finished material shall be reasonably smooth and bright and free from dirt, oil, grease, or other foreign material.
 NOTE 2—A complete designation of specified material must include the grade designation number (for example, BVAg-6b, Grade 1).
 NOTE 3—Single values shown are maximum percentages, except where otherwise specified.

AWS Classification	UNS Designation	Ag	Au	Cu	Ni	Co	Sn	Pd	In	Zn	Cd	Pb	P	C
Grade 1-Vacuum grade filler metals														
BVAg-0	P07017	99.95 min.	...	0.05	0.001	0.001	0.002	0.002	0.005
BVAg-6b	P07507	49.0–51.0	...	Remainder	0.001	0.001	0.002	0.002	0.005
BVAg-8	P07727	71.0–73.0	...	Remainder	0.001	0.001	0.002	0.002	0.005
BVAg-8b	P07728	70.5–72.5	...	Remainder	0.3–0.7	0.001	0.001	0.002	0.002	0.005
BVAg-18	P07607	59.0–61.0	...	Remainder	9.5–10.5	0.001	0.001	0.002	0.002	0.005
BVAg-29	P07627	60.5–62.5	...	Remainder	14.0–15.0	0.001	0.001	0.002	0.002	0.005
BVAg-30	P07687	67.0–69.0	...	Remainder	4.5–5.5	...	0.001	0.001	0.002	0.002	0.005
BVAg-31	P07587	57.0–59.0	...	31.0–33.0	Remainder	...	0.001	0.001	0.002	0.002	0.005
BVAg-32	P07547	53.0–55.0	...	20.0–22.0	Remainder	...	0.001	0.001	0.002	0.002	0.005
BVAu-2	P00807	...	79.5–80.5	Remainder	0.001	0.001	0.002	0.002	0.005
BVAu-3	TBD	...	34.5–35.5	Remainder	2.5–3.5	0.001	0.001	0.002	0.002	0.005
BVAu-4	P00827	...	81.5–82.5	...	Remainder	0.001	0.001	0.002	0.002	0.005
BVAu-7	P00507	...	49.5–50.5	...	24.5–25.5	0.06	...	Remainder	...	0.001	0.001	0.002	0.002	0.005
BVAu-8	P00927	...	91.0–93.0	Remainder	...	0.001	0.001	0.002	0.002	0.005
BVAu-9	TBD	...	34.5–35.5	Remainder	0.001	0.001	0.002	0.002	0.005
(65Cu-35Au)														
VBAu-10	TBD	...	49.5–50.5	Remainder	0.001	0.001	0.002	0.002	0.005
(50Au-50Cu)														
BVPd-1	P03657	0.06	Remainder	...	64.0–66.0	...	0.001	0.001	0.002	0.002	0.005
Grade 2 - Vacuum grade filler metals														
BVCu-1x	C14181	99.99 min.	0.002	0.002	0.002	0.002	0.005

^AAll vacuum grade filler metals are considered to be spatter free (refer to Melting Test, Section 10).
^BAll other elements in addition to those listed in the table above, with a vapor pressure higher than 10⁻⁷ Torr at 932°F (500°C) (such as Mg, Sb, K, Na, Li, Ti, S, Cs, Rb, Sc, Hg, Tc, Sr, and Ca) are limited to 0.001 % max each for Grade 1 vacuum grade filler metals and 0.002 % max each for Grade 2 vacuum grade filler metals. The accumulative total of all these high vapor pressure elements including zinc, cadmium, and lead is limited to 0.010 % max. The total of other impurities not included in the preceding list is limited to 0.05 % max, except for BVCu-1x, which shall be 0.01 max.
^CFor the braze alloys shown, analysis shall regularly be made only for the major alloying elements specified and the elements Zn, Cd, Pb, P, C (by Melting Test), Hg, Mg, and Sb. However, the presence of the other elements (listed above in Footnote B), with a vapor pressure higher than 10⁻⁷ Torr at 932°F (500°C), outside the limits specified shall constitute cause for rejection of the material.

TABLE 3 Standard Sieve Analyses^A

100 mesh	through No. 60 sieve—100 % min through No. 100 sieve—95 % min
140°C mesh	on No. 100 sieve—trace on No. 140 sieve—10 % max
140°F mesh	through No. 325 sieve—20 % max on No. 100 sieve—trace on No. 140 sieve—10 % max
325 mesh	through No. 325 sieve—55 % max on No. 200 sieve—trace on No. 325 sieve—10 % max through No. 325 sieve—90 % min

^A These are standard ASTM sieve sizes selected from Table 1 of Specification E 11. Sieve tests are conducted in accordance with the latest edition of Test Method B 214.

13. Packaging and Marking

13.1 *Packaging*—The brazing filler metal shall be packaged in such a way that it will arrive at its destination clean and undamaged.

13.2 *Marking*—All packages of brazing filler metal shall be marked with:

- 13.2.1 AWS specification numbers and classifications,
- 13.2.2 Seller's name and trade designation,
- 13.2.3 Size or part description in the case of preforms,
- 13.2.4 Net weight or scale count in the case of preforms, and
- 13.2.5 Lot, control or heat number.

14. Keywords

14.1 braze alloys; electron devices; melting test for cleanliness and spatter