
**Plastics — Aminoplastic moulding
materials — Determination of volatile
matter**

*Plastiques — Matières à mouler aminoplastes — Détermination des
matières volatiles*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3671:2023

<https://standards.iteh.ai/catalog/standards/sist/0edb308c-251d-442c-94f3-0b8f51b6b816/iso-3671-2023>



iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 3671:2023

<https://standards.iteh.ai/catalog/standards/sist/0edb308c-251d-442c-94f3-0b8f51b6b816/iso-3671-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Apparatus	1
5 Storage of sample	1
6 Procedure	1
7 Expression of results	2
8 Test report	2

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 3671:2023

<https://standards.iteh.ai/catalog/standards/sist/0edb308c-251d-442c-94f3-0b8f51b6b816/iso-3671-2023>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 3671:1976), which has been technically revised.

The main changes are as follows:

- added the mandatory [Clauses 2](#) and [3](#) (Normative references and Terms and definitions, respectively) and renumbered the subsequent clauses;
- added procedure to record the weight of the empty weighing bottle under [Clause 6](#) (former Clause 4);
- Changed the formula in [Clause 7](#) (former Clause 5).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plastics — Aminoplastic moulding materials — Determination of volatile matter

1 Scope

This document specifies a method for the determination of volatile matter (predominantly water) in aminoplastic moulding materials, by drying in an oven.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Apparatus

4.1 Two wide-mouthed weighing bottles, of internal diameter 45 mm and depth 35 mm, provided with tight-fitting covers.

4.2 Well-ventilated oven, capable of being controlled at (55 ± 1) °C.

4.3 Balance, with an accuracy of 0,001 g.

5 Storage of sample

Store the sample in an airtight container prior to testing, to prevent the loss or gain of water or other volatile matter.

6 Procedure

6.1 Record the weight, to the nearest 0,001 g, of a clean dried empty weighing bottle (4.1).

6.2 Weigh $(5 \pm 0,1)$ g of the sample to the nearest 0,001 g into the weighing bottle and spread evenly over the bottom of the bottle. Conduct the test in duplicate.

6.3 Place the bottles, with covers removed, in the oven (4.2), controlled at (55 ± 1) °C. After a period of 3 h, close the weighing bottles, remove from the oven and place in a desiccator at room temperature. After a period of at least 1 h, ease the covers of the weighing bottles to equalize pressure, and reweigh the bottles.

7 Expression of results

The volatile matter, w_{VM} , is given, as a percentage by mass, by [Formula \(1\)](#).

$$w_{VM} = \frac{m_1 - m_2}{m_1 - m_0} \times 100 \quad (1)$$

where

m_0 is the mass of empty weighing bottle;

m_1 is the mass of sample and weighing bottle before heating;

m_2 is the mass of sample and weighing bottle after heating.

Calculate the arithmetic mean of the two determinations.

8 Test report

The test report shall include at least the following information:

- a) a reference to this document, i.e. ISO 3671:2023;
- b) complete identification of the product tested;
- c) the volatile matter content as the arithmetic mean of the two determinations;
- d) the individual results of the two determinations;
- e) any deviations from the procedure;
- f) any unusual features observed;
- g) the date of the test.

