

FINAL DRAFT International Standard

ISO/FDIS 13402

ISO/TC 170

Secretariat: DIN

Voting begins on: 2024-12-05

Voting terminates on: 2025-01-30

Surgical and dental hand instruments — Determination of resistance against autoclaving, corrosion and thermal exposure

Instruments chirurgicaux et dentaires à main — Détermination de la résistance au passage à l'autoclave, à la corrosion et à l'exposition à la chaleur

Document Preview

ISO/FDIS 13402

https://standards.iteh.ai/catalog/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

ISO/CEN PARALLEL PROCESSING

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNO-LOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/FDIS 13402

https://standards.iteh.ai/catalog/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org Published in Switzerland

Contents

Forew	ord	iv	
Intro	uction	v	
1	Scope		
2	Normative references		
3	Terms and definitions	1	
4	Test methods4.1General4.2Sampling plan4.3Overview of test methods and applicability	1 1 1 2	
5	Test report	2	
Annex A (normative) Boiling test in deionized water			
Annex	B (normative) Boiling test in 0,9 % NaCl solution	6	
Annex	C (normative) Copper sulfate test for steels with equal or greater than 16 % chromium		
Annex	D (normative) Copper sulfate test for martensitic steels with less than 16 % chromium		
Annex	E (informative) Test in 0,3 % sodium chloride solution of austenitic steels		
Annex F (informative) Test with citric acid solution for austenitic steels			
Annex	G (informative) Thermal test		
Annex H (informative) Autoclave test Len Standardis			
Biblio	graphy (https://standards.itch.ai)		

ISO/FDIS 13402

https://standards.iteh.ai/catalog/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 170, *Surgical instruments*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 55, *Dentistry*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 13402:1995), which has been technically revised.

<u>ISO/FDIS 13402</u>

The main changes are as follows: /standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

- restructuring of the document;
- update of <u>Clause 2</u>;
- addition of <u>Clause 3</u>;
- addition of <u>Clause 4</u> including a table with an overview of test methods;
- addition of <u>Clause 5</u>;
- addition of <u>Annexes A</u> to <u>H</u> including test methods.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

Introduction

The procedures described in this document form a harmonized series of tests that can be referred to, individually or in combination, in other separate product standards. The requirements for such tests are defined and stated within the body of the product standard along with the number of cycles for each test procedure. The tests apply to dental and surgical instruments and are already standardized in relevant product standards (e.g. ISO 7151, ISO 9173-1). However, the test procedures as stated in the product standards differ in minor details. An alignment and a compilation were established.

The most important test methods for dental and surgical instruments have been compiled in this document.

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/FDIS 13402

https://standards.iteh.ai/catalog/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/FDIS 13402

https://standards.iteh.ai/catalog/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

Surgical and dental hand instruments — Determination of resistance against autoclaving, corrosion and thermal exposure

1 Scope

This document describes test methods to determine the resistance of stainless steel surgical and dental hand instruments against autoclaving, corrosion and thermal exposure.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, Water for analytical laboratory use — Specification and test methods

ISO 7554-3, Surgical instruments — Terms, measuring methods and tests — Part 3: Test methods

EN 13018, Non-destructive testing — Visual testing — General principles

3 Terms and definitions tps://standards.iteh.ai)

No terms and definitions are listed in this document. TPreview

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at <u>https://www.electropedia.org/</u>

4 Test methods

4.1 General

All tests are type tests.

4.2 Sampling plan

- a) Each instrument manufacturer shall define an appropriate sampling plan for ensuring instrument safety and quality. The sampling shall be done according to ISO/DIS 7554-3¹).
- b) Rejected lots are often re-passivated and re-tested, typically using an increased sample size of instruments. If the lot is rejected a second time, the cause of the repeat failure should be evaluated before proceeding.

¹⁾ Under preparation.

4.3 Overview of test methods and applicability

<u>Table 1</u> enlists several methods for testing. The tests applicable should be chosen according to the materials of the instrument and be performed using the procedure described in respective annex.

When placing an order, the purchaser states whether both tests are to be carried out or which of the two tests. If the purchaser does not so indicate, the choice is left to the discretion of the manufacturer.

Test method	Applicability	Annex
Boiling test in deion- ized water	Martensitic, austenitic, ferritic material with less than 16 % chromium, and precipitation hardening materials and austenitic materials, precipitation hardening materials shall use the boiling test.	<u>Annex A</u> (normative)
	Instruments containing stainless steel materials that are exclusively to the following shall use the boil test and copper sulfate test: austenitic materials, precipitation hardening materials, and ferritic materials containing equal or greater than 16 % chromium.	
	The boiling test allows to detect surface imperfections, free iron, or other anodic surface contaminations on stainless steel.	
Boiling test in 0,9 % NaCl solution	Instruments made from stainless steel materials such as austenitic ma- terials, precipitation hardening materials and ferritic materials with a chromium content of 16 % or more should be tested with the boiling test in 0,9 % NaCl.	<u>Annex B</u> (informative)
Copper sulfate test for steels with equal or greater than 16 % chromium.	Instruments containing stainless steel materials that are exclusively to the following shall use the copper sulfate test and boiling test: austenitic materials, precipitation hardening materials, and ferritic materials containing equal or greater than 16 % chromium.	<u>Annex C</u> (normative)
Copper sulfate test for steels with less than 16 % chromi- um	Instruments made from martensitic with less than 16 % chromium, and precipitation hardening materials to improper heat treatment shall be tested with copper sulfate test.	<u>Annex D</u> (normative)
Test in 0,3 % NaCl solution	Instruments made from Austenitic steel should be tested with 0,3 % NaCl solution.	<u>Annex E</u> (informative)
https://standards.i	Corrosion test exclusively for austenitic steels.	/ <u>iso-fdis-13402</u>
solution	Instruments made from austenitic steel should be tested with citric acid solution.	<u>Annex F</u> (informative)
	Corrosion test exclusively for austenitic steels.	
Thermal test	The resistance to thermal stress of instruments made from martensitic or austenitic steel should be tested with the thermal test	<u>Annex G</u> (informative)
Autoclave test	Instruments made from martensitic or austenitic steel should be tested with the autoclave test.	<u>Annex H</u> (informative)
	The sterilization test should simulate normal operating conditions.	

Table 1 — Overview of test methods and applicability

5 Test report

The test report for each determination shall include at least the following information:

- a) identification of the sample including description;
- b) a reference to this document, i.e. ISO/FDIS 13402:--;
- c) identification of used method;
- d) any unusual features observed during the determination;
- e) any deviations from the procedure;
- f) starting and completion dates of test;

- g) identification of laboratory carrying out the analysis;
- h) signature and name of (an) authorized person(s).

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO/FDIS 13402

https://standards.iteh.ai/catalog/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

© ISO 2024 – All rights reserved

Annex A (normative)

Boiling test in deionized water

A.1 General

The boiling test is suitable for martensitic, austenitic, ferritic materials with less than 16 % chromium and precipitation hardening materials to detect surface defects, free iron or other anodic surface impurities on stainless steel.

Instruments containing stainless steel materials that are exclusively to the following shall use both the boiling test and copper sulfate test: austenitic materials, precipitation hardening materials, and ferritic materials containing equal or greater than 16 % chromium.

A.2 Reagents

A.2.1 Deionized water according to ISO 3696, quality 3.

A.3 Apparatus

iTeh Standards

- A.3.1 Chemically non-reacting vessel, e.g. made of glass or ceramic.
- A.3.2 Energy source to emit heat (e.g. hob).
- A.3.3 Lint-free disposable cloth.

ISO/FDIS 13402

A.3.4 Magnifying lens (×10). g/standards/iso/6459ca9a-4a68-4cce-8e05-40ab2d4b6913/iso-fdis-13402

A.4 Preparation

Instruments shall be free of oil before test. If necessary, scrub the instrument using soap and warm water. Rinse thoroughly in water (A.2.1) and dry with medical compressed air or a lint-free disposable cloth.

A.5 Procedure

Fill glass vessel (A.3.1) with the required amount of $\geq 2\,000$ ml of saline solution for the test and heat to boiling point.

The volume of the saline solution may be adjusted, if more or less solution is needed to fully immerse the instrument.

Place the instrument in the vessel with boiling water for 30 min \pm 1 min. The instrument shall be completely covered with water.

Remove the vessel with the instrument from the heat source and allow to cool for $60 \text{ min} \pm 2 \text{ min}$.

Remove the instrument and allow it to react in room air for at least 120 min.

Remove residual moisture with dried compressed air or nitrogen.