

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
17710

ISO/TC 61/SC 12

Secretariat: JISC

Voting begins on:
2023-04-03

Voting terminates on:
2023-05-29

**Plastics — Polyols for use in the
production of polyurethanes
— Determination of degree of
unsaturation by microtitration**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 17710

<https://standards.iteh.ai/catalog/standards/sist/3766b0e7-16a6-4d62-a0a5-b0284be992af/iso-fdis-17710>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 17710:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 17710

<https://standards.iteh.ai/catalog/standards/sist/3766b0e7-16a6-4d62-a0a5-b0284be992af/iso-fdis-17710>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Application.....	2
6 Interferences.....	2
7 Reagents.....	2
8 Apparatus.....	3
9 Sampling.....	3
10 Procedure.....	3
11 Expression of results.....	4
12 Precision and bias.....	5
12.1 Precision.....	5
12.2 Bias.....	5
13 Test report.....	6
Bibliography.....	7

ISO/FDIS 17710

<https://standards.iteh.ai/catalog/standards/sist/3766b0e7-16a6-4d62-a0a5-b0284be992af/iso-fdis-17710>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 12, *Thermosetting materials*.

This second edition cancels and replaces the first edition (ISO17710:2002), of which it constitutes a minor revision.

The changes are as follows:

- the title has been changed to plural form to read: "Plastics — Polyols for use in the production of polyurethanes — Determination of degree of unsaturation by microtitration"

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

Standards have been published which deal with the measurement of the degree of unsaturation in polyols used for the production of polyurethane plastics (ASTM D 4671, JIS K 1557, part 6.7). These standards are based on the reaction of mercuric acetate with the unsaturation present in the molecule. The method described in this document relies on the same chemistry, but is a microtitration method which uses less reagent and therefore reduces the disposal problems associated with mercury compounds. It is based primarily on ASTM D 4671.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 17710

<https://standards.iteh.ai/catalog/standards/sist/3766b0e7-16a6-4d62-a0a5-b0284be992af/iso-fdis-17710>

Plastics — Polyols for use in the production of polyurethanes — Determination of degree of unsaturation by microtitration

WARNING — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices, and to determine applicable national regulatory conditions prior to the application of this document.

1 Scope

This document specifies a microtitration method to measure the degree of unsaturation in polyether polyols used in the production of polyurethanes. It is based on the reaction of mercuric acetate with double bonds in the polyol. It does not apply to compounds in which the unsaturation is conjugated with carbonyl, carboxyl or nitrile groups.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4787, *Laboratory glassware — Volumetric glassware — Methods for use and testing of capacity*

ISO 6353-1, *Reagents for chemical analysis — Part 1: General test methods*

ISO 6353-2, *Reagents for chemical analysis — Part 2: Specifications — First series*

ISO 6353-3, *Reagents for chemical analysis — Part 3: Specifications — Second series*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

3.1

unsaturation

property of a compound or polymer distinguished by the presence of a carbon-to-carbon double bond

3.2

polyol

organic compound which contains two or more hydroxyl groups capable of reacting with isocyanates to form polyurethanes

3.3 polyurethane
polymer prepared from the reaction of an organic di- or polyisocyanate with compounds containing two or more hydroxyl groups

4 Principle

Carbon-to-carbon unsaturated compounds in the sample are reacted with mercuric acetate and methanol in a methanolic solution to produce acetoxymercuricmethoxy compounds and acetic acid. The amount of acetic acid released is determined by microtitration with standard alcoholic potassium hydroxide and the result used to calculate the amount of unsaturation originally present. Because the acid cannot be titrated in the presence of excess mercuric acetate, sodium bromide is added to convert the mercuric acetate to the corresponding bromide, which does not interfere with the titration. A suitable correction shall be applied if the sample is not neutral to phenolphthalein indicator. Carbon dioxide shall be excluded from the reaction.

5 Application

Side reactions in polymerizations based on propylene oxide produce small amounts of polymers with only one hydroxyl group per chain. These unsaturated polymers lower functionality and molecular mass, thus changing the overall molecular mass distribution. This test method is suitable for quality control, as a specification test, and for research.

6 Interferences

This test method does not apply to compounds in which the unsaturation is conjugated with carbonyl, carboxyl or nitrile groups. The system shall be essentially free of water and inorganic salts, especially halides. The product being measured shall be essentially dry and free of inorganic salts, especially halides. Acetone in low concentrations does not interfere significantly, although its presence may make the end point less distinct.

7 Reagents

Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of ISO 6353-1, ISO 6353-2 and ISO 6353-3. Other grades may be used, provided that it is first determined that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

Unless otherwise indicated, references to water shall be understood to mean grade 2 reagent water as defined by ISO 3696.

7.1 Methanolic mercuric acetate solution, $C = 0,05$ mol/l.

Dissolve 16 g of mercuric acetate $[\text{Hg}(\text{C}_2\text{H}_3\text{O}_2)_2]$ into 1 l of reagent grade methanol and add sufficient glacial acetic acid to require a blank titration of 0,5 ml to 1 ml of 0,05 mol/l methanolic KOH for a 2 ml aliquot. Usually several drops of acid are required. Prepare the reagent fresh weekly and filter before using.

WARNING — Mercury compounds are highly toxic. Handle all mercury-containing reagents and waste solutions with care. Handle waste solutions as hazardous materials, and dispose of wastes in accordance with good laboratory practice. Determine any applicable regulations.

7.2 Methanolic potassium hydroxide solution, $C = 0,05$ mol/l.

Prepare and standardize in accordance with good practice, using potassium acid phthalate as a primary standard.

7.3 Methanolic hydrochloric acid solution, $C = 0,05$ mol/l.

Prepare by successively diluting concentrated hydrochloric acid with methanol. This will introduce less than 0,5 % water into the titration reagent. Standardize by titrating against 0,05 mol/l methanolic KOH (7.2).

7.4 Sodium bromide (NaBr).**7.5 Methanol.****8 Apparatus**

8.1 Autotitrator, capable of determining acidimetric end points, and equipped with a pair of electrodes or a combination glass/calomel electrode, a 5 ml burette and a recorder.

8.2 Analytical balance, capable of weighing samples to 0,1 mg.

8.3 Pipette, 2 ml capacity, conforming to ISO 4787.

8.4 Titration vessel, capable 50 ml to 100 ml capacity.

9 Sampling

Samples shall be drawn from a well-mixed vessel into a thoroughly cleaned and dry borosilicate glass container (soft-glass containers are not acceptable). If drawing from a line or valve, flush the line thoroughly with the product before starting to draw the sample. Seal the sample until taking a test portion for analysis. Care shall be taken to exclude excess moisture and carbon dioxide.

<https://standards.iteh.ai/catalog/standards/sist/3766b0e7-16a6-4d62-a0a5-b0284be992af/iso-fdis-17710>

10 Procedure

10.1 This method requires at least a two-fold molar excess of mercury reagent for quantitative reaction of the unsaturated species. If the test portion is too large, the method will give inaccurate (low) results as well as reduced precision. Use no more than 0,033 milli-equivalents (meq) of unsaturated species for the analysis therefore. For samples having 0,033 meq or less of unsaturation per gram of sample, weigh approximately 1 g of sample (weighed to 0,1 mg) into a 100 ml titration flask. If the unsaturation value is not known, determine an approximate value by using a 1 g test portion. Use this approximate value to calculate a correct test portion size that will contain no more than 0,033 meq of unsaturation using [Formula \(1\)](#):

$$m = \frac{0,033}{U_A} \quad (1)$$

where

m is the mass of the test portion, in g;

U_A is the approximate sample unsaturation, in meq/g.

10.2 Add 2 ml of mercuric acetate solution (7.1) and swirl to dissolve the test portion completely. Cover with a watch glass and allow the solution to stand for 30 min. Add 50 ml of methanol (7.5) followed by 0,25 g of sodium bromide crystals (7.4).

10.3 Titrate using 0,05 mol/l methanolic KOH (7.2) to the end point using an automatic titrator (8.1).

10.4 Titrate a blank using the same procedure, but without adding a test portion.

10.5 To determine the acidity or basicity of the polyol in order to correct the results, prepare a test portion exactly as above, but omit the mercuric acetate. Titrate, as above, with 0,05 mol/l methanolic KOH to the potentiometric end point. If the solution is determined to be already past the end point, repeat this procedure, but titrate with 0,05 mol/l methanolic HCl (7.3).

11 Expression of results

11.1 Calculate the acidity of the sample as shown in [Formula \(2\)](#):

$$A = V_A \times c(\text{KOH}) / m \quad (2)$$

where

A is the acidity, in meq/g;

V_A is the volume of 0,05 mol/l KOH required to neutralize the test portion, in ml;

$c(\text{KOH})$ is the concentration of the methanolic KOH solution, in meq/ml;

m is the mass of the test portion, in g.

11.2 Calculate the basicity of the sample as shown in [Formula \(3\)](#):

$$B = V_B \times c(\text{HCl}) / m \quad (3)$$

where

B is the basicity, in meq/g; <https://standards.iteh.ai/catalog/standards/sist/3766b0e7-16a6-4d62-a0a5-b0284be992af/iso-fdis-17710>

V_B is the volume of 0,05 mol/l HCl required to neutralize the test portion, in ml;

$c(\text{HCl})$ is the concentration of the methanolic HCl solution, in meq/ml;

m is the mass of the test portion, in g.

11.3 Calculate the degree of unsaturation of the sample, in meq/g, as shown in [Formula \(4\)](#):

$$U = [(V_S - V_B) \times c(\text{KOH}) / m] - A + B \quad (4)$$

where

U is the degree of unsaturation, in meq/g;

V_S is the volume of 0,05 mol/l KOH required for the test portion, in ml;

V_B is the volume of 0,05 mol/l KOH required for the blank, in ml;

$c(\text{KOH})$ is the concentration of the methanolic KOH solution, in meq/ml;

m is the mass of the test portion, in g;

B is the basicity, in meq/g;

A is the acidity, in meq/g.