

# SLOVENSKI STANDARD SIST EN ISO 10319:1999

01-marec-1999





# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 10319:1999 https://standards.iteh.ai/catalog/standards/sist/dc0ab663-026f-4170-a5f9-001241fcdc5e/sist-en-iso-10319-1999

#### SIST EN ISO 10319:1999

# EUROPEAN STANDARD

### EN ISO 10319

# NORME EUROPÉENNE

### EUROPÄISCHE NORM

May 1996

ICS 59.080.70

Descriptors:

textiles, filter fabrics, tests, tension tests, determination, tensile properties, test specimens, wide strips

English version

### Geotextiles - Wide-width tensile test (ISO 10319:1993)

# Géotextiles - Essai de traction des bandes DARD PRE Geotextilien - Zugversuch am breiten Streifen Larges (ISO 10319:1993) (standards.iteh.ai)

<u>SIST EN ISO 10319:1999</u> https://standards.iteh.ai/catalog/standards/sist/dc0ab663-026f-4170-a5f9-001241fcdc5e/sist-en-iso-10319-1999

This European Standard was approved by CEN on 1995-12-14. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

# CEN

European Committee for Standardization Comité Européen de Normalisation Europäisches Komitee für Normung

Central Secretariat: rue de Stassart,36 B-1050 Brussels

© 1996 Copyright reserved to CEN members

Ref. No. EN ISO 10319:1996 E

Page 2 EN ISO 10319:1996

#### Foreword

The text of the International Standard from Technical Committee ISO/TC 38 "Textiles" of the International Organization for Standardization (ISO) has been taken over as a European Standard by Technical Committee CEN/TC 189 "Geotextiles and geotextile-related products", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1996, and conflicting national standards shall be withdrawn at the latest by November 1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

#### Endorsement notice

The text of the International Standard ISO 10319:1993 has been approved by CEN as a European Standard without any modification.

SIST EN ISO 10319:1999 https://standards.iteh.ai/catalog/standards/sist/dc0ab663-026f-4170-a5f9-001241fcdc5e/sist-en-iso-10319-1999



# INTERNATIONAL STANDARD

ISO 10319

> First edition 1993-04-15

# Geotextiles — Wide-width tensile test

Géotextiles — Essai de traction des bandes larges

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN ISO 10319:1999</u> https://standards.iteh.ai/catalog/standards/sist/dc0ab663-026f-4170-a5f9-001241fcdc5e/sist-en-iso-10319-1999



Reference number ISO 10319:1993(E)

# Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting VIEW a vote.

International Standard ISO 10319 was prepared by Technical Committee ) ISO/TC 38, *Textiles*, Sub-Committee SC 21, *Geotextiles*.

<u>SIST EN ISO 10319:1999</u> https://standards.iteh.ai/catalog/standards/sist/dc0ab663-026f-4170-a5f9-001241fcdc5e/sist-en-iso-10319-1999

© ISO 1993

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization Case Postale 56 • CH-1211 Genève 20 • Switzerland Printed in Switzerland

ii

# Geotextiles — Wide-width tensile test

### 1 Scope

This International Standard describes an index test method for determination of the tensile properties of geotextiles and related products, using a wide-width strip. The method is applicable to most geotextiles, including woven fabrics, nonwovens, geocomposites, knitted fabrics and felts. The method is also applicable to geogrids, but specimen dimensions may need to be altered.

This tensile test method covers the measurement of R load elongation characteristics and includes procedures for the calculation of secant stiffness, maximum load per unit width and strain at maximum load. Singular points on the load-extension curve are also

indicated. https://standards.iteh.ai/catalog/standards/s

Procedures for measuring the tensile properties of en-iso 3.2<sup>19</sup> extension at preload: Measured increase in both conditioned and wet specimens are included.

### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 554:1976, Standard atmospheres for conditioning and/or testing — Specifications.

ISO 3301:1975, Statistical interpretation of data — Comparison of two means in the case of paired observations.

ISO 3696:1987, Water for analytical laboratory use — Specification and test methods.

ISO 7500-1:1986, Metallic materials — Verification of static uniaxial testing machines — Part 1: Tensile testing machines.

ISO 9862:1990, Geotextiles — Sampling and preparation of test specimens.

### 3 Definitions

#### 3.1 nominal gauge length

(1) For measurement with an extensometer, the initial distance, normally 60 mm (30 mm on either side of the specimen's symmetrical centre), between two reference points located on the specimen parallel to the applied load.

(2) For measurement by jaw displacement, the initial jaw separation distance, normally 100 mm.

**3.2 Extension at preload:** Measured increase in gauge length, expressed in millimetres, corresponding to an applied load of 1 % of the maximum load (SA in figure 1).

**3.3 true gauge length:** Nominal gauge length plus the extension at preload.

**3.4 maximum load:** Maximum tensile force, expressed in kilonewtons, obtained during a test (see point D in figure 1).

**3.5 strain:** Increase in true gauge length of a specimen during a test, expressed as a percentage of the true gauge length.

**3.6 strain at maximum load:** Strain, expressed in percentage, exhibited by the specimen under maximum load.

**3.7 secant stiffness:** Ratio of load per unit width, in kilonewtons per metre, to a given value of strain. For example, at point B in figure 1, secant stiffness = BC/CA.

**3.8 tensile strength:** Maximum strength per unit width, in kilonewtons per metre, observed during a test in which the specimen is stretched until it breaks.

**3.9 strain rate:** Percentage increase in true gauge length at maximum load, divided by the duration of the test, i.e. the time to attainment of maximum load from preload level.

### 4 Principle

A test specimen is held across its entire width in the jaws of a tensile testing machine operated at a given rate of strain, and a longitudinal force applied to the test specimen until the specimen ruptures. The tensile properties of the test specimen are calculated from machine scales, dials, autographic recording charts, or an interfaced computer. The rate of strain is fixed at  $(20 \pm 5)$  % per minute for all geotextiles and related products.

Most geotextiles can be tested by this method. However, some modification of techniques may be necessary for particular geotextiles, e.g. strong geotextiles, meshes or geotextiles made from glass fibre, to prevent them from slipping in the jaws or being damaged as a result of being gripped in the jaws.

The basic distinction between the present method and and other methods for measuring tensile properties of fabrics is the width of the specimen. In the present method, the width is greater than the length of the specimen, as some geotextiles have a tendency to standard contract ("neck down") under load in the 2 gauge c/sist-ep

length area. The greater width reduces the contraction effect of such fabrics and provides a relationship closer to expected fabric behaviour in the field, as well as a standard for comparison of geotextiles.

The basic test, for all kinds of geotextiles and geogrids, uses test specimens of 200 mm width and of 100 mm length (see 6.3.3 for details on preparation of geogrid specimens). When information on strain is required, extension measurements are made by means of an extensometer which follows the movement of two reference points on the specimen. These reference points are situated on the specimen symmetry axis, which is parallel to the applied load, and are separated by a distance of 60 mm (30 mm on each side of the specimen symmetry centre). This distance can be adapted for geogrids in order to include at least one row of nodes (see 6.3.3).

Measurement of the extension of the test specimen is carried out by means of an extensometer. Alternatively, extension may be measured by jaw displacement if a calibration trial shows no significant difference between jaw displacement and extensometer results. The significance of the difference is determined by a Student *t*-distribution at significance level of 95 %, as defined in ISO 3301. In such a case, the nominal gauge length is the distance between the jaws and is fixed at 100 mm.

### 5 Apparatus and reagents

**5.1 Tensile testing machine** (constant rate of extension), complying with ISO 7500-1, in which the rate of increase of specimen length is uniform with time, fitted with jaws which are sufficiently wide to hold the entire width of the specimen and equipped with appropriate means to limit slippage or damage.

NOTE 1 Compressive jaws should be used for most materials, but for materials where the use of these grips gives rise to excessive jaw breaks or slippages, capstan grips may be used.

It is essential to choose jaw faces that limit slippage of the specimen, especially in stronger geotextiles. Examples of jaw faces that have been found satisfactory are shown in figure 2.

**5.2 Extensometer**, capable of measuring the distance between two reference points on the specimen without any damage to the specimen or slippage, care being taken to ensure that the measurement represents the true movement of the reference points. Examples of extensometers include mechanical, optical, infrared or electrical devices.

The accuracy of the extensioneter shall comply with ISO 7500-1 If any irregularity of the stress-strain curve due to the extensioneter is observed, this result shall be discarded and another specimen shall be tested.

**5.3 Distilled water**, for wet specimens only; see ISO 3696.

**5.4 Nonionic wetting agent**, for wet specimens only.

### 6 Test specimens

#### 6.1 Number

Cut a minimum of five test specimens in both the machine direction and the cross direction.

### 6.2 Selection

Select test specimens in accordance with ISO 9862.

### 6.3 Dimensions

**6.3.1** Prepare each finished test specimen to a nominal 200 mm  $\pm$  1 mm width (excluding fringes when applicable, see 6.3.2), and of sufficient length to ensure 100 mm between the jaws, with the length dimension being designated and parallel to the direction in which the tensile force is applied. Where appropriate and for monitoring any slippage, draw two lines running the full width of the test specimen jaw

faces, perpendicular to the length dimension and separated by 100 mm [except for capstan grips—see figure 2 c)].

**6.3.2** For woven geotextiles, cut each specimen approximately 220 mm wide and then make fringes by removing an equal number of threads from each side to obtain the 200 mm  $\pm$  1 mm nominal specimen width. This helps to maintain the specimen integrity during the test.

NOTE 2 When specimen integrity is not affected, the specimens may be initially cut to the finished width.

**6.3.3** For geogrids, prepare each specimen at least 200 mm wide and sufficiently long to ensure a length of at least 100 mm. The test specimen shall contain at least one row of nodes or cross-members, excluding the nodes or cross-members held in the jaws (see figure 3), and, for products of pitch less than 75 mm, at least five complete tensile elements in the width direction. Products of transverse pitch  $\ge$  75 mm shall contain at least two complete tensile elements in the width direction.

If the test is to be used as a reference test for the seam/joint strength test (see ISO 10321<sup>10</sup>), the speci-RD men width shall be a minimum of 200 mm and contain at least five complete tensile elements in cards.

The reference points for the extensioneter shall be wetting agent (5.4) to the marked on a central row of tensile elements that will 10319:1999 be subjected to test and shall be atcleast 60/mmlards/sis81c0Test procedure

be subjected to test and shall be narked at the en-iso-10319-199 centre point of a rib and shall be separated by at least one node or cross-member. Where necessary the two reference points may be separated by more than one row of nodes or cross-members in order to achieve the minimum separation of 60 mm. In this case, the requirement to mark the reference points at mid-rib shall be maintained and the gauge length shall then be an integral number of pitches of the grid. Measure the nominal gauge length to an accuracy of  $\pm 3$  mm.

**6.3.4** For knitted fabrics, geocomposites or others, preparation of the specimen by cutting with a knife or scissors can affect the fabric structure. In such cases, thermal cutting can be used and shall be reported in the test report (clause 10).

**6.3.5** When the values of both the wet maximum load and the dry maximum load are required, cut each test specimen at least twice as long as is usually required. Number each test specimen and then cut each specimen crosswise into two halves, one for determining the dry maximum load, and the other for determining the wet maximum load. Each portion shall be marked with the specimen number. Thus each paired break is performed on a test specimen containing the same threads.

For geotextiles which shrink excessively when wet, the tensile strength shall be determined from the maximum load, in wet conditions, and the initial width measured to an accuracy of  $\pm 1$  mm, after conditioning but before wetting (see clause 7).

# 7 Conditioning atmosphere

**7.1** The test specimens shall be conditioned and the test conducted in one of the atmospheres defined in ISO 554. The test specimens are considered to have been conditioned when the change in mass of the test specimen in successive weighings, made at intervals of not less than 2 h of conditioning, does not exceed 0,25 % of the mass of the test specimen.

NOTE 3 Conditioning and/or testing at a specified relative humidity may be omitted if it can be shown that the results are not affected by this omission.

**7.2** Specimens to be tested in the wet condition shall be immersed in water maintained at a temperature of  $(20 \pm 2)$  °C [or  $(23 \pm 2)$  °C, or  $(27 \pm 2)$  °C]. The time of immersion shall be at least 24 h and shall be sufficient to wet the test specimens thoroughly, as indicated by no significant change in maximum load or strain following a longer period of immersion. To obtain thorough wetting, it may be necessary to add up to a maximum of 0,05 % of a nonionic neutral wetting agent (5.4) to the water.

### 8.1 Setting up the machine

Adjust the distance between the jaws at the start of the test to give a test specimen length of 100 mm  $\pm$  3 mm, except for geogrids and for geotextiles mounted on capstan grips. Select the force range of the testing machine such that the break occurs between 30 % and 90 % of full-scale force. Set the machine so as to induce a strain rate of 20 %  $\pm$  5 % per min in the gauge length. Test conditioned specimens in an atmosphere as specified in clause 6. For wet specimens, carry out the test within 3 min of removal from the water.

If capstan grips are used, the separation between the centres of the capstans at the beginning of each test shall be kept to a minimum. The use of capstan grips shall be recorded in the test report.

### 8.2 Insertion of test specimen in the jaws

Mount the test specimen centrally in the jaws. Take care that in both the machine direction and cross direction tests the specimen length is parallel to the direction of application of force. Where appropriate, do this by having the two lines, which were previously

<sup>1)</sup> ISO 10321:1992, Geotextiles — Tensile test for joints/seams by wide-width method