



SLOVENSKI STANDARD
SIST ENV ISO 12960:1999
01-julij-1999

; YchY_gh]]Y]b [YchY_gh]]Ua `gcfcXb]]nXY_] !`DfYg_i gbUa YrcXUnUi [cHJ] `UbY
cXdcfbcgh] dfch]]Y_c]bUa `fGC#HF`%& *\$.%--Ł

Geotextiles and geotextile-related products - Screening test method for determining the resistance to liquids (ISO/TR 12960:1998)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: ^{SIST ENV ISO 12960:1999} **ENV ISO 12960:1998**
<https://standards.iteh.ai/catalog/standards/sist/74d29475-c679-446a-9d25-e08c31c6fc51/sist-env-iso-12960-1999>

ICS:

59.080.70 Geotekstilije Geotextiles

SIST ENV ISO 12960:1999 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ENV ISO 12960:1999](#)

<https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-e08c31c6fc51/sist-env-iso-12960-1999>

EUROPEAN PRESTANDARD
PRÉNORME EUROPÉENNE
EUROPÄISCHE VORNORM

ENV ISO 12960

November 1998

ICS 59.080.70

Descriptors: see ISO document

English version

Geotextiles and geotextile-related products - Screening test
method for determining the resistance to liquids (ISO/TR
12960:1998)

This European Prestandard (ENV) was approved by CEN on 19 July 1998 as a prospective standard for provisional application.

The period of validity of this ENV is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the ENV can be converted into a European Standard.

CEN members are required to announce the existence of this ENV in the same way as for an EN and to make the ENV available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the ENV) until the final decision about the possible conversion of the ENV into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

[SIST ENV ISO 12960:1999](https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-e08c311171/sist-env-iso-12960-1999)

<https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-e08c311171/sist-env-iso-12960-1999>



REPUBLIKA SLOVENIJA
MINISTRSTVO ZA ZNANOST IN TEHNOLOGIJO
Urad RS za standardizacijo in meroslovje
LJUBLJANA

SIST ENV ISO 12960

PREVZET PO METODI RAZGLASITVE

-00- 1999



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

Page 2
ENV ISO 12960:1998

Foreword

The text of ENV ISO 12960:1998 has been prepared by Technical Committee CEN/TC 189 "Geotextiles and geotextile-related products", the secretariat of which is held by IBN, in collaboration with Technical Committee ISO/TC 38 "Textiles".

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ENV ISO 12960:1999

<https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-e08c31c6fc51/sist-env-iso-12960-1999>



Introduction

In nearly all applications geotextiles and geotextile-related products (geotextile products) may be in contact with aqueous solutions of acids, bases or dissolved oxygen. The resistance of geotextile products to these chemicals depends on the one hand on polymer formulation, processing, textile structure and the presence of existing damage and on the other hand on the composition of the liquid and in situ conditions such as temperature, pressure and the presence of further mechanical stress.

It is the purpose of this prestandard to provide a method of screening (index testing) the resistance of geotextile products to these acids and bases.

Since an index test requires exposure times that are short compared to the expected lifetimes of geotextile products, it is necessary to accelerate the process. The data obtainable are suitable for screening but not for deriving performance data such as lifetime, unless supported by further evidence.

1 Scope

iTeh STANDARD PREVIEW

This standard specifies methods for screening the resistance of geotextile products to liquids while not subjecting them to external mechanical stress.

The standard is applicable to all geotextiles and geotextile related products.

NOTE: This standard only considers conditions where the specimens are fully immersed in the liquids. Though outside the scope of this standard, the test conditions may be modified to accommodate particular applications, eg gaseous media. This standard does not preclude use for test specimens that are pre-treated by some method, e.g. by weathering, aqueous extraction conditions or installation damage.

2 Normative references

This European prestandard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European prestandard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

ENV 12226	Geotextiles and geotextile-related products - General tests for evaluation following durability testing
ISO 3696	Water for analytical laboratory use - Specification and test methods

3 Principle

Test specimens are completely immersed in a test liquid for a given test duration at a fixed temperature. The properties of the test specimens are tested before and after immersion and if applicable after drying, and wherever possible, the test results are compared with those of control specimens stored under reference conditions.

4 General requirements and procedure

4.1 Apparatus

A container, e.g. a pneumatic vessel, is to be used, equipped with:

- a sealing lid or equivalent device and if necessary a reflux condenser or equivalent device to restrict evaporation of volatile components;
- a stirring or equivalent device to maintain homogeneity of the liquid and the exchange of matter between the liquid and the specimens;
- specimen holders to ensure correct placing of the specimens (see 4.6.2), the free distance between specimens being at least 10 mm;
- at least one closable aperture in the lid for access to control the composition of the liquid.

The container shall be large enough for the test liquid (see 4.6.1), which shall be held at constant temperature (see 4.3).

The material of the container and equipment shall be resistant to the test chemicals. Such materials are in general borosilicate glass or stainless steel.

4.2 Test liquids

Two types of test liquids are to be used:

- an inorganic acid: 0,025 M sulfuric acid (method A);
- an inorganic base: calcium hydroxide ($\text{Ca}(\text{OH})_2$), used as a saturated suspension, i.e. approximately 2,5 grams per litre (method B).

Chemicals of reagent or analytical grade should be used. Water shall comply with ISO 3696, grade 3.

National safety regulations for handling of chemicals and for disposal of test liquids shall be followed.

NOTE: For any test medium it is an important condition that its composition remains constant during the test exposure. This may be complicated if the concentration of any active component is low or if the liquid is not a stable one-phase system. In such cases the concentration should be monitored and if possible adjusted or replaced on a regular basis. Attention should be given also to possible catalytic or synergistic effects, including effects of simultaneous chemical and mechanical

stresses (eg environmental stress cracking in polyolefins). The choice of the concentration of the active species is governed by the aim to avoid significant changes of the concentration during the test and to accelerate the reaction but to avoid a change in the active mechanism by using too high a concentration.

4.3 Test temperatures

The test temperature shall be $(60 \pm 1) ^\circ\text{C}$ for each method.

4.4 Test duration

The test duration shall be 3 days for each method.

4.5 Specimens

Reference is made to ENV 12226.

The number of specimens shall be five test specimens and five control specimens.

NOTE 1: It is recommended that additional specimens be exposed. If a mechanical test is invalid, a further specimen should be tested in its place.

[SIST ENV ISO 12960:1999](https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-108731665100/sist-env-iso-12960-1999)

[https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-](https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-108731665100/sist-env-iso-12960-1999)

NOTE 2: If the products are sheathed by some coating, which could be penetrated during installation, the product should be tested with and without the coating. If not, the possibility of a change in chemical resistance in case of destruction or damage to the sheath should be noted in the report.

4.6 Procedure

4.6.1 Quantity of the test liquid

The quantity of test liquid shall be greater than 30 times the weight of the specimens and shall cover the specimens completely.

4.6.2 Positioning of specimens

The specimens shall be placed in the vessel free of any significant mechanical stress.

The mean distance between the specimens, between the specimens and the walls of the vessel, and between the specimens and the surface of the liquid, shall be at least 1 cm. No significant proportion of the surface of the specimens shall make contact with a material other than the test liquid itself.

Specimens of different materials shall not be tested in the same vessel. During the test the exchange of matter between liquid and geotextile shall not be hindered by poor convection of the test liquid.

Calcium hydroxide shall be stirred continuously; sulfuric acid at least once per day. The pH of the liquid shall be measured and recorded and, where necessary, liquid shall be replenished or replaced to maintain the original pH at least every seventh day. The liquid and the specimens shall be shielded from light.

4.6.3 Control specimens

The control specimens shall be immersed for one hour in water at the same temperature as the test specimens. Water shall be in accordance with Section 4.2.

4.6.4 Rinsing, wiping and drying

Rinsing shall be performed in water complying with 4.2., then in 0.01 M sodium carbonate solution, finally in water again. The quantities shall be sufficient to ensure thorough cleaning.

In exposing polyester geotextiles to calcium hydroxide it is necessary to remove adhering crystals of calcium terephthalate. This may be done by rinsing for 5 min with a 10% solution (by weight) of trisodiumnitrilotriacetate (NTA) in an agitating device, followed by rinsing in a 3% solution (by weight) of acetic acid and finally rinsing with water. <https://standards.iteh.ai/catalog/standards/sist/74f29475-eb79-446a-9d25-e08c31c6fc51/sist-env-iso-12960-1999>

Specimens shall be dried at room temperature or at elevated temperature up to 60°C. Specimens should not be subjected to undue stress during drying.

4.7 Determination of changes in properties.

The changes are determined in accordance with ENV 12226.

5 Test report

The test report shall contain particulars to the following items:

- reference to this prestandard;
- description of the material;
- results expressed in accordance with ENV 12226;
- date of test;
- any deviations from this standard and any factors likely to have influenced the results.