



Designation: **C1445 – 07 C1445 – 13**

Standard Test Method for Measuring Consistency of Castable Refractory Using a Flow Table¹

This standard is issued under the fixed designation C1445; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This test method covers the procedure for determining the consistency of castable refractory mixes by the flow table method.
- 1.2 This test method applies to regular weight castable refractories, insulating castable refractories, and castable refractories that require heavy vibration for forming, which are described in Classification C401. They also apply to such castables containing metal fibers.
- 1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*²
 - C71 Terminology Relating to Refractories
 - C230/C230M Specification for Flow Table for Use in Tests of Hydraulic Cement
 - C401 Classification of Alumina and Alumina-Silicate Castable Refractories
 - C860 Test Method for Determining the Consistency of Refractory Castable Using the Ball-In-Hand Test
 - D346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis

3. Significance and Use

- 3.1 The amount of water used in a castable mix for preparing test specimens has a significant influence on subsequent test results. This test method is used primarily to determine and reproduce the consistency required for the optimum casting of refractory castables in the preparation of test specimens and to express that consistency quantitatively. The correct water content is one of the major factors that must be controlled to obtain uniform test specimens. Excess water can reduce strength, increase volume shrinkage, and promote segregation of the castable ingredients. Insufficient water can produce “honeycombs” (air voids) in the castable because of poor consolidation during placement and prevent complete hydration of cement.
- 3.2 The flow table (see sketches in Specification C230/C230M) has been found to be an excellent tool for measuring the consistency of a castable and should be used in cases where a numerical result is required. Since castables differ somewhat in their “body” or plasticity, it has been found that a good casting range, expressed numerically, might vary from castable to castable. While one material may cast well between 40 and 60 % flow, another material may need to be in the 60 to 80 % flow range to properly flow. Because of this, it has been found that no arbitrary optimum range can be stated for all castables. The flow table then becomes a tool for measuring the flow and not determining it. It can allow the operator to follow the manufacturer’s recommendations or to reproduce the consistency of a particular castable between laboratories.
- 3.3 Total time of wet mixing must be closely controlled to obtain reproducible results.
- 3.4 This test method is not intended to be used to determine the proper water content for gunning applications, although it may provide information of value for interpretation by a skilled operator.

¹ This test method is under the jurisdiction of ASTM Committee C08 on Refractories and is the direct responsibility of Subcommittee C08.09 on Monolithics. Current edition approved March 1, 2007; Sept. 1, 2013. Published April 2007; October 2013. Originally approved in 1999. Last previous edition approved in 2005 as C1445 – 99C1445(2005) – 07. DOI: 10.1520/C1445-07; 10.1520/C1445-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.

4. Interferences (Factors Known to Affect Results)

4.1 A ruggedness test (Fig. 1) was performed using “C230 Calibration Mixture”³. All factors were found not to cause statistically significant effects on measured results. See ASTM Research Report No. C08 – 1016.

4.2 Factors which were found to be rugged during the test method evaluation were (1) tamper cross section – round versus rectangular, (2) tamper surface – polyurethane sealed versus unsealed, (3) mold filling procedure, (4) number of tamps – 36 versus 44, (5) table drop time – 7 s versus 11 s, and (6) operator.

5. Apparatus

5.1 *Balance*, 15-lb (6.8-kg) capacity, with sensitivity of 0.002 lb (1 g).

5.2 *Flow Table, Mold, and Calipers*, conforming to the requirements of Specification C230/C230M.

5.3 *Tamper*—A nonabsorbing, nonabrasive, non-brittle material such as a rubber compound having a Shore A durometer hardness of 80 ± 10 or hardwood dowel made nonabsorbing by coating with either solvent or water based polyurethane, and the tamper shall have a cross section of $\frac{1}{2}$ by 1 in. (13 by 25 mm) or an equivalent circular cross sectional area and a convenient length of 5 to 6 in. (127 to 152 mm). The tamping face shall be flat and at right angles to the length of the tamper.

5.4 *Trowel*, having a steel blade 4 to 6 in. (100 to 150 mm) in length, with straight edges.

5.5 *Castable Mixer*—Either a manually or electrically operated (see Fig. 2) mechanical mixer⁴ may be used to prepare batches for the consistency determination. Size the mixing bowl to contain 50 to 70 % volume loading with the dry batch.

NOTE 1—Castable-water requirement variation becomes more significant as dry volume loadings drop below 50 % of the capacity of the mixer bowl because the water required to wet the bowl surfaces changes more rapidly with decreasing volume loadings.

5.6 *Thermometer*, dial or digital-type, metal, with a range from 0 to 180°F (–18 to 80°C).

5.7 *Vibrating Table*—An electric vibrating table with 3600 Hz and at least a 1-ft² surface.

5.8 *Sample Splitter*, designed to reduce the castable to the desired weight and ensure that the grain size distribution is representative of the original batch.

NOTE 2—A Jones or riffle-type sample splitter is satisfactory, provided the openings are large enough to accommodate the largest aggregate particle. If a sample splitter is not available, hand reduction by the cone-and-quarter method may be used. Follow the applicable portions of this test method as described in Practice D346.

6. Sampling

6.1 At the time of use, the dry castable mix should be between 68 and 72°F (20 and 22°C). The temperature is measured by inserting the full length of the dial-thermometer stem into the material until the reading is constant.

6.2 Reduce the mass of the castable mix with a sample splitter to obtain the desired batch size in accordance with 6.3. Take precautions to prevent segregation. If additional batches are required, they should also be reduced to the desired batch size with a sample splitter.

6.3 Batch sizes for the flow table test normally consist of 10 lb (4.5 kg) for a regular weight or 5 lb (2.3 kg) for an insulating castable. Mixer size may dictate other sizes. (See 5.5).

7. Procedure

7.1 *Preparation of Castable Sample:*

7.1.1 Weigh the castable sample (see 6.3) to the nearest 0.02 lb (9 g). Place the batch in the mixer described in 5.5 (see Note 1), and dry mix for 1 min. While the mixer is operating at slow speed, add 90 % of the estimated water requirement having a temperature between 68 and 72°F (20 and 22°C), within $\frac{1}{2}$ min. Operate the mixer at 50 to 60 rpm, then add additional water in small amounts from a tared container, and mix until the batch appears to have the desired flow.

7.1.2 The total actual wet mixing time, including water additions, should be 3 min \pm 10 s for dense castables, 5 min \pm 10 s for insulating castables, and 4 to 6 min for mixes needing heavy vibration, unless specified differently by the manufacturer.

NOTE 3—Mixing times of less than 5 min for insulating castables may influence the results because lightweight aggregates usually soak up water during the initial stages of mixing and affect the consistency of the batch. Depending on the aggregate type, particle breakdown may occur with excessive mixing time. This was not observed in subcommittee round-robin tests with a 5-min mixing time using a variety of lightweight castables.

7.2 *Determination of Flow:*

³ Laboratory Flow Table Calibration Mixture available from Cement and Concrete Reference Laboratory; Building Research, 226-Room A365; National Institute of Standards and Technology; Gaithersburg, MD 208989.

⁴ The sole source of supply of mechanical mixers known to the committee at this time is Hobart Corporation, 701 S. Ridge Ave., Troy, OH 45374. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.

