



## Standard Specification for Carbon Steel Forgings for Piping Applications<sup>1</sup>

This standard is issued under the fixed designation A105/A105M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification<sup>2</sup> covers forged carbon steel piping components for ambient- and higher-temperature service in pressure systems. Included are flanges, fittings, valves, and similar parts ordered either to dimensions specified by the purchaser or to dimensional standards such as the MSS, ASME, and API specifications referenced in Section 2. Forgings made to this specification are limited to a maximum weight of 10 000 lb [4540 kg]. Larger forgings may be ordered to Specification **A266/A266M**. Tubesheets and hollow cylindrical forgings for pressure vessel shells are not included within the scope of this specification. Although this specification covers some piping components machined from rolled bar and seamless tubular products (see 5.2), it does not cover raw material produced in these product forms.

1.2 Supplementary requirements are provided for use when additional testing or inspection is desired. These shall apply only when specified individually by the purchaser in the order.

1.3 Specification **A266/A266M** covers other steel forgings and Specifications **A675/A675M** and **A696** cover other steel bars.

1.4 This specification is expressed in both inch-pound units and SI units. However, unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished to inch-pound units. The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.22** on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved Oct. 1, 2013. Published October 2013. Originally approved in 1926. Last previous edition approved in 2012 as A105/A105M-12. DOI: 10.1520/A0105\_A0105M-13.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-105 in Section II of that Code.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

### 2. Referenced Documents

2.1 In addition to those reference documents listed in Specification **A961/A961M**, the following list of standards apply to this specification:

#### 2.2 ASTM Standards:<sup>3</sup>

**A266/A266M** Specification for Carbon Steel Forgings for Pressure Vessel Components

**A675/A675M** Specification for Steel Bars, Carbon, Hot-Wrought, Special Quality, Mechanical Properties

**A696** Specification for Steel Bars, Carbon, Hot-Wrought or Cold-Finished, Special Quality, for Pressure Piping Components

**A788/A788M** Specification for Steel Forgings, General Requirements

**A961/A961M** Specification for Common Requirements for Steel Flanges, Forged Fittings, Valves, and Parts for Piping Applications

#### 2.3 MSS Standards:

**SP 44** Standard for Steel Pipe Line Flanges<sup>4</sup>

#### 2.4 ASME Standards:

**B16.5** Dimensional Standards for Steel Pipe Flanges and Flanged Fittings<sup>5</sup>

**B16.9** Wrought Steel Butt Welding Fittings<sup>5</sup>

**B16.10** Face-to-Face and End-to-End Dimensions of Ferrous Valves<sup>5</sup>

**B16.11** Forged Steel Fittings, Socket Weld, and Threaded<sup>5</sup>

**B16.34** Valves-Flanged, Threaded and Welding End<sup>5</sup>

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

<sup>4</sup> Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, http://www.mss-hq.com.

<sup>5</sup> Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, http://www.asme.org.

**\*A Summary of Changes section appears at the end of this standard**

**B16.47 Large Diameter Steel Flanges**<sup>5</sup>

2.5 *ASME Boiler and Pressure Vessel Code:*

**Section IX Welding Qualifications**<sup>5</sup>

2.6 *API Standards:*

**API-600 Flanged and Butt-Welding-End Steel Gate Valves**<sup>6</sup>

**API-602 Compact Design Carbon Steel Gate Valves for Refinery Use**<sup>6</sup>

**3. Terminology**

3.1 *Definitions*—For definitions of other terms used in this specification, refer to Specification **A961/A961M**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *heaviest cross-section, n*—maximum heat treated thickness of the production forging.

**4. Ordering Information**

4.1 See Specification **A961/A961M**.

4.1.1 Additional requirements (see **13.2**).

**5. General Requirements**

5.1 Product furnished to this specification shall conform to the requirements of Specification **A961/A961M**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the requirements of Specification **A961/A961M** constitutes nonconformance with this specification. In case of a conflict between the requirements of this specification and Specification **A961/A961M**, this specification shall prevail.

5.2 Except as permitted by Section 6 in Specification **A961/A961M**, the finished product shall be a forging as defined in the Terminology Section of Specification **A788/A788M**.

**6. Heat Treatment**

6.1 Heat treatment is not a mandatory requirement of this specification except for the following piping components:

6.1.1 Flanges above Class 300,<sup>7</sup>

6.1.2 Flanges of special design where the design pressure at the design temperature exceeds the pressure-temperature ratings of Class 300, Group 1.1,

6.1.3 Flanges of special design where the design pressure or design temperature are not known,

6.1.4 Piping components other than flanges which meet both of the following criteria: (1) over NPS 4 and (2) above Class 300, and

6.1.5 Piping components of Special Class<sup>8</sup> other than flanges which meet both of the following criteria: (1) over NPS 4 and (2) when the working pressure at the operating temperature exceeds the tabulated values for Special Class 300, Group 1.1.

6.2 Heat treatment, when required by **6.1** shall be annealing, normalizing, or normalizing and tempering or quenching and tempering in accordance with Specification **A961/A961M**.

<sup>6</sup> Available from American Petroleum Institute (API), 1220 L. St., NW, Washington, DC 20005-4070, <http://www.api.org>.

<sup>7</sup> For definition of Class 300, see ASME B16.5.

<sup>8</sup> For definition of special class, see ASME B16.34.

6.2.1 Quenching shall consist of either (1) fully austenitizing the forgings followed by quenching in a suitable liquid medium or (2) using a multiple stage procedure whereby the forgings are first fully austenitized and rapidly cooled, then reheated to partially reaustenitize, followed by quenching in a suitable liquid medium. All quenched forgings shall be tempered as prescribed in Specification **A961/A961M**.

**7. Chemical Composition**

7.1 The steel shall conform to the chemical requirements specified in **Table 1**.

7.2 Steels to which lead has been added shall not be used.

**8. Mechanical Properties**

8.1 The material shall conform to the mechanical property requirements prescribed in **Table 2** and **Table 3**.

8.2 For normalized, normalized and tempered, or quenched and tempered forgings, the central axis of the test specimen shall be taken at least  $\frac{1}{4} T$  from the nearest surface as-heat-treated, where  $T$  is the maximum heat-treated thickness of the represented forging. In addition, for quenched and tempered forgings, the midlength of the test specimen shall be at least  $T$  from all other surfaces as-heat-treated, exclusive of the  $T$  dimension surfaces. When section thickness does not permit this positioning, the test specimen shall be positioned as near as possible to the prescribed location.

8.3 *Tension Tests:*

8.3.1 One tension test shall be made for each heat of as-forged components.

8.3.2 One tension test shall be made from each heat-treating charge. If more than one heat is included in such a charge, each heat shall be tested.

8.3.2.1 When forgings of different shapes are included in the same heat-treating charge, the test specimen shall be obtained from the heaviest cross-section of the thickest forging, except for hubbed flanges (see **8.3.3**). The test specimen shall represent all forgings from the same heat and heat-treating charge whose maximum thicknesses do not exceed the thickness of the test forging.

**TABLE 1 Chemical Requirements**

NOTE 1—For each reduction of 0.01 % below the specified carbon maximum (0.35 %), an increase of 0.06 % manganese above the specified maximum (1.05 %) will be permitted up to a maximum of 1.65 %.

Element	Composition, %
Carbon	0.35 max
Manganese	0.60–1.05
Phosphorus	0.035 max
Sulfur	0.040 max
Silicon	0.10–0.35
Copper	0.40 max <sup>A</sup>
Nickel	0.40 max <sup>A</sup>
Chromium	0.30 max <sup>A,B</sup>
Molybdenum	0.12 max <sup>A,B</sup>
Vanadium	0.08 max

<sup>A</sup> The sum of copper, nickel, chromium, molybdenum and vanadium shall not exceed 1.00 %.

<sup>B</sup> The sum of chromium and molybdenum shall not exceed 0.32 %.