



FINAL DRAFT International Standard

ISO/FDIS 115

Unalloyed aluminium ingots for remelting — Classification and composition

*Aluminium non allié en lingots pour refusion — Classification et
composition*

ISO/TC 79/SC 4

Secretariat: JISC

Voting begins on:
2024-10-04

Voting terminates on:
2024-11-29

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/FDIS 115

<https://standards.iteh.ai/catalog/standards/iso/5db22989-face-48d8-a2c8-072cdadf4f98/iso-fdis-115>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO/FDIS 115

<https://standards.iteh.ai/catalog/standards/iso/5db22989-face-48d8-a2c8-072cdadf4f98/iso-fdis-115>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....iv

1 Scope.....1

2 Normative references.....1

3 Terms and definitions.....1

4 Order.....1

5 Requirements.....1

5.1 Production and manufacturing processes.....1

5.2 Quality control.....2

5.3 Chemical composition.....2

5.4 Freedom from contamination and hazardous materials.....3

5.5 Form of products.....3

6 Product inspection and testing methods.....4

6.1 General.....4

6.2 Chemical analysis of main impurities.....4

6.3 Chemical analysis of trace impurities.....4

6.4 Sampling from ingots.....4

7 Inspection documents.....4

8 Marking of products.....5

9 Packaging.....5

10 Delivery documents.....5

11 Complaints.....5

Annex A (normative) Rules for writing the designation and the chemical composition of unalloyed aluminium.....7

Bibliography.....9

<https://standards.iteh.ai/catalog/standards/iso/5db22989-face-48d8-a2c8-072cdadf4f98/iso-fdis-115>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 4, *Unalloyed (refined) aluminium ingots*.

This second edition cancels and replaces the first edition (ISO 115:2003), which has been technically revised.

The main changes are as follows:

— five grades were added to [Table 2](#).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Unalloyed aluminium ingots for remelting — Classification and composition

1 Scope

This document defines the requirements for grades of unalloyed aluminium ingots intended for remelting. It specifies the classification and designation applicable to these grades, the conditions in which they are produced, their properties and the marks by which they are identified.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Order

The order, in the form agreed upon between the supplier and the purchaser, shall contain the following information:

- a) designation of the unalloyed aluminium in accordance with this document or the customer code after agreement between the supplier and the purchaser;
- b) specification of the form of the products, including the mass and dimensions of individual ingots and bundles;
- c) quantity: mass, in tonnes (quantity tolerances if required);
- d) any requirements for certificates of conformity, test and/or analysis reports or inspection certificates;
- e) any additional requirements agreed between the supplier and the purchaser.

5 Requirements

5.1 Production and manufacturing processes

The production and manufacturing processes shall be left to the discretion of the manufacturer.

No obligation shall be placed on the manufacturer to use the same processes for subsequent and similar orders.

5.2 Quality control

The supplier shall be responsible for carrying out all inspection and tests required by this document prior to shipment of the product. If the purchaser wishes to inspect the product at the supplier's works, the purchaser shall stipulate this at the time of placing the order.

5.3 Chemical composition

Each grade of unalloyed aluminium, including refined aluminium, with a specified minimum aluminium content shall be in accordance with the designations and chemical composition given in [Table 1](#).

Each grade of unalloyed aluminium without a specified minimum aluminium content shall be in accordance with the designations and chemical compositions given in [Table 2](#).

The compositions, except that for aluminium, shown in [Table 1](#) and [Table 2](#) are given in maximum mass fractions, in per cent.

For the interpretation of the results of chemical analysis, the number representing the result of the determination of an element content shall be rounded to the same number of decimal places as the corresponding number in this document.

The writing rules for designations and chemical compositions shall be applied in accordance with [Annex A](#).

If the purchaser requires content limits for elements not specified in this document, these limits shall be stated on the order, after agreement between the supplier and the purchaser.

Table 1 — Unalloyed aluminium with specified minimum aluminium content — Chemical composition in maximum mass fractions

Designation	Si	Fe	Cu	Mn	Mg	Zn	Ti	Ga	V	Others each	Al min.
Al 99,995 ^a	0,002 0	0,002 0	0,002 0	0,001	0,003 0	0,001	0,001	0,002	0,001	0,001	99,995
Al 99,990 ^a	0,003 0	0,003 0	0,004 0	0,001	0,003 0	0,001	0,001	0,002	0,001	0,001	99,990
Al 99,99 ^a	0,004 0	0,003 0	0,002 0	0,001	0,001 0	0,004	0,002	0,003 0	0,001	0,001	99,99
Al 99,98 ^a	0,006	0,006	0,002 0	0,002	0,002	0,004	0,002	0,003	0,001	0,001	99,98
Al 99,97 ^a	0,008	0,008	0,004	0,003	0,002	0,005	0,002	0,004	0,001	0,001	99,97
Al 99,94 ^a	0,030	0,030	0,005	0,010	0,010	0,010	0,005	0,02	—	0,010	99,94
Al 99,70 ^a	0,10	0,20	0,01	—	0,02	0,03	0,02	0,03	0,03	0,03	99,70
Al 99,7E ^{a, b}	0,07	0,20	0,01	0,005	0,02	0,04	—	—	—	0,03	99,70
Al 99,6E ^{a, c}	0,10	0,30	0,01	0,007	0,02	0,04	—	—	—	0,03	99,60

^a Cd + Hg + Pb max. 0,009 5; As max. 0,009.

^b B max. 0,04; Cr max. 0,004; Mn + Ti + Cr + V max. 0,020.

^c B max. 0,04; Cr max. 0,005; Mn + Ti + Cr + V max. 0,030.