



# FINAL DRAFT International Standard

## ISO/FDIS 3451-5

### Plastics — Determination of ash — Part 5: Poly(vinyl chloride)

*Plastiques — Détermination du taux de cendres —*

*Partie 5: Poly(chlorure de vinyle)*

ISO/TC 61/SC 5

Secretariat: **DIN**

Voting begins on:  
**2025-02-05**

Voting terminates on:  
**2025-04-02**

iTeh Standards  
(<https://standards.itih.ai>)  
Document Preview

<https://standards.itih.ai>  
ISO/FDIS 3451-5

<https://standards.itih.ai/catalog/standards/iso/93f0acb7-2c65-4594-993a-a70551589228/iso-fdis-3451-5>

**ISO/CEN PARALLEL PROCESSING**

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO/FDIS 3451-5](https://standards.iteh.ai/catalog/standards/iso/93f0acb7-2c65-4594-993a-a70551589228/iso-fdis-3451-5)

<https://standards.iteh.ai/catalog/standards/iso/93f0acb7-2c65-4594-993a-a70551589228/iso-fdis-3451-5>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2025

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
4.1 Method A (direct calcination).....	1
4.2 Method B (calcination, with sulfuric acid treatment after combustion).....	2
4.3 Method C (calcination, with sulfuric acid treatment before combustion).....	2
<b>5 Reagents (for methods B and C only)</b> .....	<b>2</b>
<b>6 Apparatus</b> .....	<b>2</b>
<b>7 Safety precautions</b> .....	<b>3</b>
<b>8 Procedure</b> .....	<b>3</b>
8.1 Test portion.....	3
8.2 Method A (determination of unsulfated ash).....	4
8.3 Method B (determination of sulfated ash).....	4
8.4 Method C (determination of sulfated ash).....	5
<b>9 Number of determinations</b> .....	<b>5</b>
<b>10 Expression of results</b> .....	<b>5</b>
<b>11 Accuracy and precision</b> .....	<b>6</b>
<b>12 Test report</b> .....	<b>6</b>
<b>Annex A (informative) Summary of test results for PVC compounds filled with chalk (CaCO<sub>3</sub>)</b> .....	<b>7</b>

iTeh Standards  
<https://standards.itih.ai>  
 Document Preview

[ISO/FDIS 3451-5](https://standards.itih.ai)

<https://standards.itih.ai/catalog/standards/iso/93f0acb7-2c65-4594-993a-a70551589228/iso-fdis-3451-5>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 249, *Plastics*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 3451-5:2002), which has been technically revised.

The main changes are as follows:

- the test conditions have been adapted to relevant fillers;
- the thermobalance has been added as alternative method;
- the results of an interlaboratory comparison have been added to justify the changed test conditions for PVC compounds filled with chalk (CaCO<sub>3</sub>).

A list of all parts in the ISO 3451 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Plastics — Determination of ash —

## Part 5: Poly(vinyl chloride)

**WARNING** — The use of this document may involve hazardous chemicals, materials, operations or equipment. This document does not purport to address the safety problems associated with its use. It is the responsibility of the user of this document to establish proper safety and health practices, and determine the application of regulatory limitations prior to use. Poly(vinyl chloride) evolves hydrogen chloride on thermal decomposition and precautions should be taken to avoid inhalation of these or other fumes.

### 1 Scope

This document specifies three methods for the determination of the ash of poly(vinyl chloride).

The general procedures given in ISO 3451-1 are followed. For ash, method A is used. For sulfated ash, methods B and C are used. All three methods are applicable to resins, compounds and finished products. Methods B and C are applicable when lead-containing compounds are present.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3451-1, *Plastics — Determination of ash — Part 1: General methods*

ISO 11358-1, *Plastics — Thermogravimetry (TG) of polymers — Part 1: General principles*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 4 Principle

#### 4.1 Method A (direct calcination)

The organic matter in a test portion is burnt off and the residue is heated at a specific temperature given in [Table 1](#) until constant mass is reached. This method may be used with a muffle or microwave furnace ([6.3](#)).

Table 1 — Calcination temperatures for method A

Filler system	Temperature <sup>c</sup> °C
Unfilled	950 ± 50 °C
Glass fibres/Glass bubbles <sup>a</sup>	600 ± 25 °C
Talc powder <sup>a</sup> and other fillers except calcium carbonate	950 ± 50 °C
Calcium carbonate <sup>b</sup>	1 100 ± 50 °C
Mixtures with calcium carbonate <sup>b</sup>	1 100 ± 50 °C

<sup>a</sup> The test temperature shall allow for further investigations according to filler structure.

<sup>b</sup> The test temperature of 1 100 °C is required for formulations containing calcium carbonate only.

<sup>c</sup> The specified temperature tolerances apply to the muffle or microwave furnace. For the thermobalance, the applicable temperature tolerance is ±5 °C.

#### 4.2 Method B (calcination, with sulfuric acid treatment after combustion)

The organic matter in a test portion is burnt off, the residue is converted into sulfates using concentrated sulfuric acid and, finally, the residue is heated at 950 °C until constant mass is reached.

#### 4.3 Method C (calcination, with sulfuric acid treatment before combustion)

The organic matter in a test portion is burnt off after adding concentrated sulfuric acid and the residue is heated at 950 °C until constant mass is reached. This method is recommended over method B because of the better reproducibility of the results.

Method B or method C should be used if lead-containing compounds are present. They are not recommended to be used with a thermobalance.

### 5 Reagents (for methods B and C only)

5.1 **Sulfuric acid**, 100 %, density 1,84 g/ml, analytical grade.

<https://standards.iteh.ai/catalog/standards/iso/93f0acb7-2c65-4594-993a-a70551589228/iso-fdis-3451-5>

5.2 **Acetic acid**, 100 %, analytical grade.

**WARNING — Care should be taken in handling sulfuric acid and acetic acid.**

### 6 Apparatus

Apparatus as specified in ISO 3451-1 and, in particular, the following.

6.1 **Crucible of aluminium oxide, silica, platinum or porcelain**, diameter of upper part 35 mm to 75 mm. The size shall be such that the crucible is not more than half-filled by the test portion. The crucibles shall be stable in the temperature range required for measurements.

Optionally, a suitable lid may be used to cover the crucible.

For use with a thermobalance, crucibles consistent with the type of thermobalance shall be used. Aluminium oxide crucibles are normally used.

6.2 **Heating device**, such as Bunsen burner, with silica triangle and tripod, or other suitable heating device (not required for use with a thermobalance).

6.3 **Muffle furnace or microwave furnace**, capable of being controlled thermostatically at applicable temperatures given in [Table 1](#).