ISO/FDIS-14635-1:2023(E)

ISO-<u>/</u>TC-<u>6</u>0/SC-<u>2</u>

Secretariat: DIN

1

Date: 2023-01-2503-08

Gears — FZG test procedures —

Part 1: FZG test method A/8,3/90 for relative scuffing load-carrying capacity of oils

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>Engrenages — Méthodes d'essai FZG —</u> <u>Partie 1: Méthode FZG A/8.3/90 pour évaluer la capacité de charge au grippage des huiles</u>

FDIS stage

© ISO-2023-- All rights reserved

ISO/FDIS-14635-1:2023(E)

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +_41 22 749 01 11 EmailE-mail: copyright@iso.org Website: www.iso.orgwww.iso.org

Published in Switzerland

ii

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 14635-1

https://standards.iteh.ai/catalog/standards/sist/924f1a3e-50ef-47a4-888a-6fccc46a5a9a/isofdis-14635-1

© ISO-2023- – All rights reserved

	ISO/FDIS14635-1:2023(E)	
Con	itents	
Fore	word	r
Intro	viductionvi	i
Part	1: FZG test method A/8.3/90 for relative scuffing load-carrying capacity of oils	
1	<u>Scope</u>	
2	Normative references	
3	Terms and definitions	
4	Brief description of method	
<u>4.1</u>	General principle	
<u>4.2</u>	Precision	
5	Test materials	1
<u>5.1</u>	Test gears	1
<u>5.2</u>	Cleaning fluid	1
6	Apparatus	1
<u>6.1</u>	FZG spur-gear test rig	1
<u>6.2</u>	Heating device10	1
<u>6.3</u>	Revolution counter	
7	Preparation of apparatus11	
8	Test procedure11	
9	Reporting of results	
<u>Anne</u>	ex A (informative) Typical FZG test report sheet	
Anne	ex B (informative) Checklist for maintenance of FZG gear test rig	,
<u>Bibli</u>	ography	-888a-6fccc46a5a9a/j
	fdis-14635-1	
Fore	word v	
Intre	duction vii	
1	Scope 1	
2	Normative references 1	
3	Terms and definitions 1	
4	Brief description of method 2	
4.1	General principle 2	
4.2	Precision 4	
5	Test materials 4	
5.1	Test gears 4	
<u>5.2</u>	Cleaning fluid 4	
6	Apparatus 7	
6.1	FZG spur-gear test rig 7	
6.2	Heating device 8	
6.3	Revolution counter 8	
6.3 7	Revolution counter 8 Preparation of apparatus 8	

ISO/FDIS-14635-1:2023(E) 9 Reporting of results 9
Annex A (informative) Typical FZG test report sheet 11
Annex B (informative) Checklist for maintenance of FZG gear test rig12
B.1 How to recognize malfunction 12
B.1.1 — Distribution of scuffing marks 12
B.1.2 Tooth contact pattern 12
B.1.3 Tests with reference oil 12
B.1.4 Other indications 12
B.2 Parts that need maintenance 12
B.2.1 — Test-gear box 12
B.2.1.1 Shafts 12
B.2.1.2 Bearings 13
B.2.1.3 Keys 13
B.2.1.4 Spacer rings 13
B.2.1.5 Gear box and front cover 13
B.2.1.6 Seals 13
B.2.2 Connecting shafts and flanges 13
B.2.2.1 Load coupling 13 iTeh STANDARD PREVIEW
B.2.2.2 Torque measuring device 13
B.2.2.3 Load coupling support bearing 13 (standards.iteh.ai)
B.2.2.4 Torsion shaft 14
B.2.2.5-Flanges14
B.2.3 Slave-gear box 14 ISO/FDIS 14635-1
B.2.3.1 Slave gears // 514 dards.iteh.ai/catalog/standards/sist/924f1a3e-50ef-47a4-888a-6fccc46a5a9a/iso-
B.2.3.2 Lubrication 14 fdis-14635-1
B.2.4 Other parts 14
B.2.4.1 Heating 14
B.2.4.2-Flexible coupling blocks 14
B.2.4.3 Motor 14
B.3 Approximate time intervals 14
Bibliography 16

© ISO-2023 – All rights reserved

iv

_ISO/FDIS_14635-1:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directiveswwww.iso.org/directiveswww.iso.org/directiveswww.iso.org/directiveswww.iso.org/directiveswwww.iso.org/directiveswww.iso.org/directiv

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patentswww.iso.org/patents.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.htmlwww.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 60, *Gears*, Subcommittee SC 2, *Gear capacity calculation*.

This second edition cancels and replaces the first edition (ISO 14635<u>-1</u>:2000), <u>of</u> which <u>it</u> constitutes a minor revision in accordance with ISO Directives, Part 1., The changes are as follows:

The main changes are as follows:

fdis-14635-

- ISO 1328-1:1995, Cylindrical gears ISO system of accuracy Part 1: Definitions and allowable values of deviations relevant to corresponding flanks of gear teeth¹ has been dated as this document still refers to accuracy grade;
- replacement of ISO 4287, Geometrical Product Specifications (GPS) Surface texture: Profile method Terms, definitions and surface texture parameters which has been withdrawn and replaced by ISO 21920-2, Geometrical product specifications (GPS) Surface texture: Profile Part 2: Terms, definitions and surface texture parameters;
- replacement of ISO 4964, <u>Steel</u> <u>Hardness conversions</u> which has been withdrawn and similar information can be found in ISO 18265, <u>Metallic materials</u> <u>Conversion of hardness values</u>;
- <u>updatingreplacement</u> of <u>some</u> bibliography entries <u>which were withdrawn</u>, and changes from dated to undated references where no specific reason requires the dated reference (see Bibliography footnotes);
- <u>Clause 5.2, subclause 5.2</u>, wording harmonized within with the ISO 14635 series;
- <u>Table 1, Table 1</u>, description <u>"pitch line circumferential speed</u> (v_w) has been replaced by <u>"circumferential velocity at the pitch line"</u> to harmonize the wording with <u>the ISO 6336-series</u>.

v

ISO/FDIS-14635-1:2023(E)

 <u>Table 4, Table 4, insertion of lines "Direction of rotation and Test lubrication volume" to conform</u> to <u>be compliant with giventhe</u> information <u>withinin the</u> ISO 14635 series.

A list of all parts in the ISO 14635 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 14635-1

https://standards.iteh.ai/catalog/standards/sist/924f1a3e-50ef-47a4-888a-6fccc46a5a9a/isofdis-14635-1

© ISO_2023 - All rights reserved

vi

_ISO/FDIS-_14635-1:2023(E)

Introduction

The types of gear failures which can be influenced by the lubricant in use are scuffing, low-speed wear and the gear-surface fatigue phenomena known as micro- and macropitting. In the gear design process, these gear damages are taken into consideration by the use of specific lubricant and service-related characteristic values. For an accurate, field-related selection of these values, adequate lubricant test procedures are required. The FZG² test procedures described in this <u>document</u> and <u>other parts of</u> ISO 14635-2 and ISO 14635-3, can be regarded as tools for the determination of the lubricant-related characteristic values to be introduced into the load-carrying capacity calculation of gears.

FZG test method A/8,3/90 for the relative scuffing load-carrying capacity of oils described in this part of ISO 14635document is typical for the majority of applications in industrial and marine gears. ISO 14635-2 is related to the relative scuffing load-carrying capacity of oils of very high EP properties, as used for the lubrication of automotive driveline components. Other FZG test procedures for the determination of low-speed wear, micro- and macropitting load-carrying capacity of gears are already in a late state of development. They can intended to be added later to the ISO 14635 series as further parts.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>ISO/FDIS 14635-1</u>

https://standards.iteh.ai/catalog/standards/sist/924f1a3e-50ef-47a4-888a-6fccc46a5a9a/isofdis-14635-1

<u>FZG = Forschungsstelle f
ür Zahnr
äder und Getriebebau, Technische Universit
ät M
ünchen (Gear Research Centre</u>
 © ISO-2023- – All rights reserved

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 14635-

https://standards.iteh.ai/catalog/standards/sist/924f1a3e-50ef-47a4-888a-6fccc46a5a9a/isofdis-14635-1 ISO/FDIS 14635-1:2023(E)

Gears — FZG test procedures —

Part 1: FZG test method A/8,3/90 for relative scuffing load-carrying capacity of oils

1 Scope

This document specifies a test method based on a FZG³ four-square test machine to determine the relative load-carrying capacity of lubricating oils defined by the gear-surface damage known as scuffing. High surface temperatures due to high surface pressures and sliding velocities can initiate the breakdown of the lubricant films. This test method can be used to assess such lubricant breakdown under defined conditions of temperature, high sliding velocity and stepwise increased load.

This method is technically equivalent to ASTM D 5182-974, DIN 51354-1 and DIN 51354-24; NOTE IP 334/90619 and CEC L-07-A-95.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1328-1:1995^z, Cylindrical gears — ISO system of accuracy — Part -: Definitions and allowable values of deviations relevant to flanks of gear teeth

1SO 5725-2, Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method

ISO 18265, Metallic materials- - Conversion of hardness values

ISO 21920-2, Geometrical product specifications (GPS)-_ Surface texture: Profile-_ Part-_2: Terms, definitions and surface texture parameters

ASTM D 235, Specification for Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

. datah - C-. 100 1.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:	
 ISO Online browsing platform: available at <u>https://www.iso.org/obp</u> 	Field Code Changed
 IEC Electropedia: available at <u>https://www.electropedia.org/</u> 	Field Code Changed
3.1 scuffing load-carrying capacity (of a lubricant) maximum load which can be sustained under a defined set of conditions	
Note 1-to entry:-For examples of failure see Figure 1.Figure 1.	
3 770 – Foreshurgestelle für Zehrräder und Catrickelen. Technische Heinersität München (Coor Desserch Centre	
³ FZG = Forschungsstelle f ür Zahnr äder und Getriebebau, Technische Universit ät M ünchen (Gear Research Centre Technical University, Munich), Boltzmannstra ße 15, D-85748 Garching, Germany. ⁴ ASTM D 5182-97 has been replaced by ASTM D 5182-19.	
⁵ -DIN 51354-1 and DIN 51354 ⁻ 2 have been replaced by DIN ISO 14635-1. ⁶ -IP 334/90 has been withdrawn.	
7 Cancelled and replaced by ISO 1328-1:2013. © ISO-2023 All rights reserved 1	

ISO/FDIS 14635-1:2023(E)

Note 2-to entry:-_Scuffing is a particularly severe form of damage to the gear-tooth surface in which seizure or welding together of areas of tooth surface occur, due to absence or breakdown of a lubricant film between the contacting tooth flanks of mating gears, typically caused by high temperature and high pressure. Scuffing is most likely when surface velocities are high. Scuffing can also occur at relatively low sliding velocities when tooth-surface pressures are high enough either generally or, because of uneven surface geometry and loading, in discrete areas.

Note 3-to entry:-Risk of scuffing damage varies with the properties of gear materials, the lubricant used, the surface roughness of tooth flanks, the sliding velocities and the load. Consequences of scuffing of high-speed gears include a tendency to high levels of dynamic loading due to increase of vibrations, which usually leads to further damage by scuffing, pitting or tooth breakage.

3.2

FZG test condition A/8,3/90

test condition where A is the particular tooth form of the test gears, according to Table 1;Table 1, 8,3 is the speed at the pitch circle, in metres per second, and 90 is the initial oil temperature, in degrees Celsius, from load stage 5 and onward in the oil sump

Note 1-_to-_entry:-_The direction of the rotation of the gears is shown in Figure 3. Figure 3.

3.3

failure load stage

load stage in which the summed total width of scuffing damage on the active flank area of the 16 pinion teeth exceeds one gear-tooth width, i.e. 20 mm

Note 1-to-entry:-Examples of flank damages for the purpose of the test method are shown in Figure 1.Figure 1.

4 Brief description of method

4.1 General principle

A set of test gears as defined in <u>Clause 5, Tables 1Clause 5, Tables 1</u> and <u>2,2</u>, is run with the test lubricant at constant speed for a fixed number of revolutions using dip-lubrication mode. Loading of the gear teeth is increased in steps outlined in <u>Table 3. Table 3</u>. Beginning with load stage 5, the initial oil temperature is controlled between (90 ± 3) °C. During the test run of each load stage, the oil temperature is allowed to rise freely. After load stage 4, the pinion tooth flanks are inspected for surface damage at the end of each load stage and any changes in appearance are noted. A test is considered complete when either the failure criteria has been met or when load stage 12 is run without meeting the failure criteria.

It is the responsibility of the operator to ensure that all local legislative and statutory requirements are met.

NOTE It has been assumed by the compilers of this test method that anyone using the method will either be fully trained and familiar with all normal engineering and laboratory practice, or will be under the direct supervision of such a person.

WARNING — When the rig is running, there are long loaded shafts and highly stressed test gears turning at high speed and precautions shall be taken to protect personnel.

Protection from noise is also highly recommended.

88a-6fccc46a5a9a/iso-

2



3

ISO/FDIS 14635-1:2023(E)



g) Approx. 6 mm failure marks

h) 20 mm failure marks

NOTE This figure describes the typical pinion tooth flank changes occurring in FZG tests. Changes in the original surface condition (criss-cross grinding) can be described by their physical appearance. One and the same type of flank damage can be described in different places in the world by using different terminology (e.g. "scuffing", "scoring" and "severe wear"). In order to avoid misinterpretation of the pinion tooth flank changes occurring during the test, typical examples of non-failure and failure are given.

PRODUCTION NOTE The colours represented in the electronic file of this part of ISO 14635document can be neither viewed nor printed as true representations. Only copies of this part of ISO 14635document printed by ISO can be guaranteed to represent the true colours.

Figure 1 — FZG A-type gear-tooth face changes (flank damages)