



Designation: D3530M – 97 (Reapproved 2008)<sup>ε1</sup>

## Standard Test Method for Volatiles Content of Composite Material Prepreg<sup>1</sup>

This standard is issued under the fixed designation D3530M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

<sup>ε1</sup> NOTE—This standard was corrected to a single-designation standard editorially in October 2013.

### 1. Scope

1.1 This test method covers the determination of the volatiles content, in weight percent of composite material prepregs. This standard focuses on composites with thermosetting resins that tend to lose a few percent of the matrix mass when heated due to loss of both retained water and low molecular weight matrix constituents that volatilize during heating.

1.2 Use of this test method is limited to maximum temperature of circulating air ovens (approximately 300°C).

1.3 Use of this test method is limited to temperatures below which the matrix flows from the reinforcement.

1.4 The values stated in SI units are to be regarded as standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* Specific precautionary statements are given in Section 8.

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D3878 Terminology for Composite Materials

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

E1309 Guide for Identification of Fiber-Reinforced Polymer-Matrix Composite Materials in Databases

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.03 on Constituent/Precursor Properties.

Current edition approved April 1, 2008. Published April 2008. Originally approved in 1976. Last previous edition approved in 2008 as D3530M/D3530M – 97(2008). DOI: 10.1520/D3530M-97R08E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *NFPA Standard:*

NFPA 86 Standard for Ovens and Furnaces<sup>3</sup>

### 3. Terminology

3.1 *Definitions*—Terminology D3878 defines terms relating to composite materials. Terminology D883 defines terms relating to plastics. Practice E177 defines terms relating to statistics. In the event of a conflict between terms, Terminology D3878 shall have precedence over other documents.

3.1.1 *prepreg, n*—the admixture of fibrous reinforcement and polymeric matrix used to fabricate composite materials. Its form may be sheet, tape, or tow. See Terminology D3878.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *Volatiles Content, n*—the amount of volatiles present in a prepreg expressed as a weight percent.

3.3 *Symbols:*

3.3.1  $M_i$ —the initial mass of the sample.

3.3.2  $M_f$ —the mass of the sample after oven exposure.

3.3.3  $V_c$ —the weight percent volatiles content.

### 4. Summary of Test Method

4.1 Specimens of prepreg are weighed and then exposed to elevated temperature, equal to the nominal cure or consolidation temperature of the material, in an air circulating oven to remove the volatiles. The exposed samples are reweighed and the percent change in weight expressed as volatiles content.

### 5. Significance and Use

5.1 This test method is used to obtain the volatiles content of composite material prepreg. Knowledge of the volatiles content is useful in developing optimum manufacturing processes.

5.2 The volatiles content is determined after exposure to the nominal cure or consolidation temperature.

<sup>3</sup> Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02269-9101.