



Designation: ~~D4725 – 11~~ D4725 – 13

## Standard Terminology for Engine Coolants and Related Fluids<sup>1</sup>

This standard is issued under the fixed designation D4725; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This document covers terminology relating to engine coolants. It is intended to provide a reference for anyone seeking information on engine coolants, and also to provide a uniform set of definitions for use in preparing ASTM specifications, test methods and other standard documents.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

[D1193 Specification for Reagent Water](#)

[D3306 Specification for Glycol Base Engine Coolant for Automobile and Light-Duty Service](#)

[D3585 Specification for ASTM Reference Fluid for Coolant Tests](#)

[D4985 Specification for Low Silicate Ethylene Glycol Base Engine Coolant for Heavy Duty Engines Requiring a Pre-Charge of Supplemental Coolant Additive \(SCA\)](#)

[D6210 Specification for Fully-Formulated Glycol Base Engine Coolant for Heavy-Duty Engines](#)

[D6471 Specification for Recycled Prediluted Aqueous Glycol Base Engine Coolant \(50 Volume % Minimum\) for Automobile and Light-Duty Service](#)

[D6472 Specification for Recycled Glycol Base Engine Coolant Concentrate for Automobile and Light-Duty Service](#)

[E1177 Specification for Engine Coolant Grade Glycol](#)

#### 2.2 ISO Standard:

[ISO 22241 Diesel engines - NOx reduction agent AUS 32](#)

### 3. Terminology

**antifoam**, *n*—a substance added to engine coolant concentrate, corrosion inhibitor packages, or supplemental coolant additives to prevent or suppress foam.

<sup>1</sup> This terminology is under the jurisdiction of ASTM Committee [D15](#) on Engine Coolants and Related Fluids and is the direct responsibility of Subcommittee [D15.92](#) on Terminology.

Current edition approved ~~June 1, 2011~~ Oct. 1, 2013. Published ~~August 2011~~ October 2013. Originally approved in 1987. Last previous edition approved in ~~2008~~ 2011 as ~~D4725 – 08a~~ [D4725 – 11](#). DOI: ~~10.1520/D4725-11~~ 10.1520/D4725-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

#### DISCUSSION—

Eliminating foam improves heat transfer.

**antifreeze**, *n*—a term frequently used in the marketplace for engine coolant concentrate. (See **engine coolant concentrate**.)

**antirust**, *n*—an inhibitor package, solid or liquid, intended to be diluted with water or glycol for use in an engine cooling system to mitigate rust and corrosion.

**ash content**, *n*—the residue from an engine coolant concentrate, antirust, or engine coolant that remains after evaporation, charring, and ignition at strong heat.

**boiling point**, *n*—the temperature at which the vapor pressure of an engine coolant reaches atmospheric pressure under equilibrium boiling conditions.

**cavitation corrosion**, *n*—a form of localized, accelerated corrosion characterized by deep pitting and caused by high mechanical forces resulting from coolant vapor bubble collapse at the surface of the metal.

**cavitation erosion corrosion**, *n*—the mechanical removal of protective films on metal by the formation and collapse of vapor bubbles in a liquid, and the abrasive action of a liquid, which may contain suspended solids, moving at high velocity.

DISCUSSION—

The mechanical removal of the protective films exposes fresh metal to corrosive attack.

**coolant additive package**, *n*—the combination of inhibitors added to an engine coolant to mitigate cooling system degradation, corrosion, scaling, and foaming, or to provide other desirable properties.

**corrosion inhibitor package**, *n*—the combination of inhibitors added to an engine coolant to mitigate cooling system corrosion.

**corrosive water**, *n*—a standard solution containing 100 ppm each of sulfate, chloride, and bicarbonate ions introduced as the sodium salts to distilled water.

**diesel exhaust fluid (DEF)**, *n*—preparation of aqueous urea [(NH<sub>2</sub>)<sub>2</sub>CO], containing 32.5 % by weight of technically pure urea in high-purity water with quality characteristics defined by ISO 22241.

**dye**, *n*—a colorant added to an engine coolant to give it a distinctive color.

**engine coolant**, *n*—a fluid used to transfer heat from an engine to the radiator, usually containing specific amounts of glycols, water, corrosion inhibitors, and a foam suppressor.

DISCUSSION—

Engine coolants may also contain supplemental coolant additives.

**engine coolant concentrate**, *n*—a formulated liquid product intended to be diluted with water for use in engine cooling systems.

DISCUSSION—

Functionally, the product provides a lower freeze point and mitigates corrosion and foaming.

**engine dynamometer test**, *n*—a laboratory full-scale engine test designed to evaluate corrosion protection and inhibitor stability of engine coolants under simulated operational conditions.

**erosion corrosion**, *n*—nonuniform, accelerated corrosion characterized by a smooth appearance and caused by high velocity coolant.

DISCUSSION—

The corrosive attack may be aggravated by suspended solids.

**extended life coolant**, *n*—an engine coolant for light-duty service vehicles with recommended change-out of the coolant after 160 000 km (100 000 miles), 5 years, or 4000 operating hours.

**foaming tendencies**, *n*—a laboratory test conducted in glassware to evaluate the tendency of an engine coolant to foam under standard conditions of aeration and temperature.

**freezing point**, *n*—the temperature at which crystallization begins in the absence of supercooling, or the maximum temperature reached immediately after initial crystal formation in the case of supercooling, or the temperature at which solid crystals, formed on cooling, disappear when the temperature of the specimen is allowed to rise.

**glassware corrosion test**, *n*—a laboratory screening test for evaluating the corrosion protection properties of engine coolants on metal test specimens under controlled conditions of aeration and temperature.

**glycol bottoms**, *n*—the residue in the still after final distillation of most of the glycol and dimers, trimers and tetramers from the output stream of a glycol reactor.

DISCUSSION—