



Designation: **B888—12 B888/B888M – 13**

Standard Specification for Copper Alloy Strip for Use in Manufacture of Electrical Connectors or Spring Contacts¹

This standard is issued under the fixed designation ~~B888~~**B888/B888M**; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes the requirements for copper alloy strip for use in the manufacture of electrical connectors or spring contacts produced from one of the following Copper Alloy UNS Nos.²: C14530, C15100, C15500, C17000, C17200, C17410, C17450, C17460, C17500, C17510, C19002, C19010, C19015, C19025, C19210, C19400, C19500, C19700, C23000, C26000, C40810, C40850, C40860, C42200, C42500, C42520, C42600, C50580, C50780, C51000, C51080, C51100, C51180, C51980, C52100, C52180, C52480, C63800, C64725, C65400, C68800, C70250, C70260, C70265, C70310, C75200, and C76200.

1.2 The requirements for the other copper alloys such as copper-nickel-tin spinodal, UNS C72650, C72700, and C72900, shall be as prescribed in the current edition of Specification **B740**.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:³

B193 Test Method for Resistivity of Electrical Conductor Materials

B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar

B248M Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)

B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

B740 Specification for Copper-Nickel-Tin Spinodal Alloy Strip

B820 Test Method for Bend Test for Determining the Formability of Copper and Copper Alloy Strip

B846 Terminology for Copper and Copper Alloys

E8E8/E8M Test Methods for Tension Testing of Metallic Materials

~~**E8M** Test Methods for Tension Testing of Metallic Materials [Metric] (Withdrawn 2008)⁴~~

E54 Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)⁴

E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)⁴

E75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)⁴

E478 Test Methods for Chemical Analysis of Copper Alloys

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 ISO Standards:⁵

ISO 4744 Copper and Copper Alloys—Determination of Chromium Content—Flame Atomic Absorption Spectrometric Method

ISO 7602 Copper and Copper Alloys—Determination of Tellurium Content

¹ This specification is under the jurisdiction of Committee **B05** on Copper and Copper Alloys and is the direct responsibility of Subcommittee **B05.01** on Plate, Sheet, and Strip.

Current edition approved Oct. 1, 2012/Oct. 1, 2013. Published November 2012/November 2013. Originally approved in 1998. Last previous edition approved in 2010/2012 as ~~B888—10~~**B888—12**. DOI: ~~10.1520/B0888-12~~**10.1520/B0888_B0888M-13**.

² The UNS system for copper and copper alloys (see Practice **E527**) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “c” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

*A Summary of Changes section appears at the end of this standard



3. Terminology

3.1 *Definitions*—For definition of terms used in this specification, refer to Terminology B846.

4. General Requirements

4.1 For product furnished under this specification in English units, the following sections of Specification B248 must constitute a part of this specification. For product furnished under this specification in the SI units, the following sections of Specification B248M must constitute a part of this specification.

- 4.1.1 Terminology,
- 4.1.2 Materials and Manufacture,
- 4.1.3 Dimensions, Weights, and Permissible Variations,
- 4.1.4 Workmanship, Finish, and Appearance,
- 4.1.5 Sampling,
- 4.1.6 Number of Tests and Retests,
- 4.1.7 Specimen Preparation,
- 4.1.8 Test Methods,
- 4.1.9 Significance of Numerical Limits,
- 4.1.10 Certification,
- 4.1.11 Test Reports, and
- 4.1.12 Packaging and Package Marking.

4.2 In the event of a conflict between this specification and Specification B248 or B248M, the requirements of this specification shall take precedence.

5. Classification

5.1 Product produced to this specification is classified as strip material to be used for spring contact or electrical and electronic connector applications only.

6. Ordering Information

6.1 Contract or purchase orders for product under this specification should include the following information:

- 6.1.1 ASTM designation and year of issue,
- 6.1.2 UNS alloy designation,
- 6.1.3 Dimensions, for example, thickness, width,
- 6.1.4 Quantity, and
- 6.1.5 Temper (Section 8).

6.2 The following options are available under this specification and shall be specified in the contract or purchase order when required:

- 6.2.1 Type of edge: slit, sheared, sawed, square corners, rounded corners, rounded edges, or full-rounded edges (Section 11),
- 6.2.2 Width and straightness tolerances, slit-metal tolerances, square-sheared metal tolerances, sawed metal tolerances, straightened or edge-rolled metal tolerances (Section 11),
- 6.2.3 Identification marking (Section 22),
- 6.2.4 Certification (Section 20),
- 6.2.5 Mill test report (Section 21), and
- 6.2.6 How packaged: coil wound in traverse or pancake style (Section 22).
 - 6.2.6.1 Number of strip lengths per coil,
 - 6.2.6.2 Size and weight of each coil, and
 - 6.2.7 The electrical resistivity or any other physical and electrical properties (See Table X1.1).

7. Materials and Manufacture

7.1 *Material*—The material of manufacture shall be a cast bar, slab, cake, billet, or other form of the composition given in Table 1 for the specified alloy, suitable for processing into the product prescribed in this specification.

7.2 *Manufacture*—The product shall be produced by either hot- or cold-working operation. It shall be finished, unless otherwise specified, by such hot working, cold working, annealing, or heat treatment as may be necessary to meet the properties specified in Table 2.

7.3 *Edges*—The edges shall be slit or rolled edges as specified by the buyer. Slit edges shall be furnished unless otherwise specified or agreed upon between the purchaser and supplier or manufacturer.

TABLE 1 Chemical Requirements

Elements Composition, %																		
Copper Alloy UNS No.	Copper	Alum-inum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C14530	99.90 ^A min									0.001– 0.010	0.003– 0.023						0.003– 0.023	
E15100 ^B	99.80 ^C min													0.05– 0.15				
E15500	99.75 ^C min						0.08– 0.13			0.040– 0.080						0.027– 0.10		
E17000 ^D	remainder ^C	0.20 —max	1.60– 1.70	0.20 ^E min											0.20 —max			
E17200 ^D	remainder ^C	0.20 —max	1.80– 2.00	0.20 ^E min											0.20 —max			
E17410 ^D	remainder ^C	0.20 —max	0.15– 0.50	0.35– 0.6	0.20 — max										0.20 —max			
E17450 ^D	remainder ^C	0.20 —max	0.15– 0.50		0.20 —m ax				0.50– 1.0		0.25 —max		0.50-% —max		0.20 —max			
E17460 ^D	remainder ^C	0.20 —max	0.15– 0.50		0.20 max				1.0– 1.4		0.25 —max		0.50-% —max		0.20 max			
E17500 ^D	remainder ^C	0.20 —max	0.4– 0.7	2.4– 2.7	0.10 — max										0.20 — max			
E17510 ^D	remainder ^C	0.20 —max	0.2– 0.6	0.3 — max	0.10 — max				1.4– 2.2						0.20 —max			
E19002 ^D	remainder ^C				0.10	0.05	0.01		1.4–1.7 ^E	0.05	0.02–0.30	0.04–0.35		0.005– 0.05	0.20– 0.35	0.02– 0.50		
E19010 ^D	remainder ^C								0.8– 1.8	0.01– 0.05					0.15– 0.35			
E19015 ^G	remainder ^C						0.02–0.15		0.50–2.4	0.02–0.20					0.10– .40			
E19025 ^H	remainder ^C				0.10 — max				0.8– 1.2	0.03– 0.07	0.7– 1.1	0.20 —max						
E19210 ^G	remainder				0.05– 0.15					0.025– 0.04								
E19400 ^G	97.0-min				2.1– 2.6	0.03 —max				0.015– 0.15		0.05– 0.20						
E19500 ^G	96.0-min	0.02 —max		0.30– 1.3	1.0– 2.0	0.02 max				0.01– 0.35	0.10– 1.0	0.20 — max						
E19700 ^G	remainder			0.05 —max	0.30– 1.2	0.05 —max	0.01– 0.20	0.05 —max	0.05 — max	0.10– 0.40	0.20 —max	0.20 —max						
E23000 ^G	84.0-86.0				0.05 — max	0.05 —max						remainder						
E26000 ^H	68.5-71.5				0.05 — max	0.07 —max						remainder						
E40810 ^H	94.5-96.5				0.08– 0.12	0.05 —max			0.11– 0.20	0.028– 0.04	1.8– 2.2	remainder						

iTeh Standards
[tps://standards.itih.com](https://standards.itih.com)
 Document Preview

ASTM B888/B888M
<https://standards.itih.com/catalog/standards/sstdoc/3ea1c42d6-b39d-ec095c467228c/astm-b888-b888m>

TABLE 1 Continued

Elements Composition, %

Copper Alloy UNS No.	Copper	Aluminum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C40850 ^H	94.5-96.5				0.05-0.20	0.05-max			0.05-0.20	0.01-0.20	2.6-4.0	remainder						
C40860 ^H	94.0-96.0				0.01-0.05	0.05-max			0.05-0.20	0.02-0.04	1.7-2.3	remainder						
C42200 ^H	86.0-89.0				0.05-max	0.05-max				0.35-max	0.8-1.4	remainder						
C42500 ^H	87.0-90.0				0.05-max	0.05-max				0.35-max	1.5-3.0	remainder						
C42520 ^H	88.0-91.0				0.05-0.20	0.05-max			0.05-0.20	0.01-0.20	1.5-3.0	remainder						
C42600 ^H	87.0-90.0 ^C				0.05-0.20	0.05-max			0.05-0.20 ^E	0.01-0.20	2.5-4.0	remainder						
C50580 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	1.0-1.7	0.30-max						
C50780 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	1.7-2.3	0.30-max						
C51000 ^D	remainder				0.10-max	0.05-max			0.05-0.35	0.03-0.35	4.2-5.8	0.30-max						
C51080 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	4.8-5.8	0.30-max						
C51100 ^D	remainder				0.10-max	0.05-max			0.05-0.35	0.03-0.35	3.5-4.9	0.30-max						
C51180 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	3.5-4.9	0.30-max						
C51980 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	5.5-7.0	0.30-max						
C52100 ^D	remainder				0.10-max	0.05-max			0.05-0.35	0.03-0.35	7.0-9.0	0.20-max						
C52180 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	7.0-9.0	0.30-max						
C52480 ^D	remainder				0.05-0.20	0.05-max			0.05-0.20	0.01-0.35	9.0-11.0	0.30-max						
C63800 ^D	remainder ^C	2.5-3.1		0.25-0.55	0.20-max	0.05-max		0.10-max	0.20-max			0.8-max			1.5-2.1			
C64725 ^D	95.0 min ^C				0.25	0.01	0.20		1.3-2.7 ^E		0.20-0.8	0.50-1.5	0.09		0.20-0.8			0.01 Calcium
C65400 ^D	remainder ^C					0.05-max					1.2-1.9	0.50-max	0.01-0.12		2.7-3.4			
C68800 ^D	remainder ^C	3.0-3.8 ^I		0.25-0.55	0.20-max	0.05-max					21.3-24.1 ^I							
C70250 ^D	remainder ^C				0.20-max	0.05-max	0.05-0.30	0.10-max	2.2-4.2 ^E			1.0-max			0.25-1.2			
C70260 ^D	remainder ^C								1.0-3.0 ^E	0.01-max				0.20-0.7				
C70265 ^D	remainder ^C					0.05-max			1.0-3.0 ^E	0.01-max	0.05-0.8	0.30-max		0.20-0.7				
C70310 ^D	remainder ^C				0.10	0.05	0.01		1.0-4.0 ^E	0.05	1.0	2.0		0.005-0.05	0.08-1.0	0.02-0.50		

TABLE 1 Continued

Elements Composition, %																		
Copper Alloy UNS No.	Copper	Alum-inum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C75200 ^D	63.0-66.5 ^C				0.25 max	0.05 max		0.50 max	16.5- 19.5 ^E									remainder
C76200 ^D	57.0-61.0 ^C				0.25 max	0.09 max		0.50 max	11.0- 13.5 ^E									remainder

TABLE 1 Chemical Requirements

Elements Composition, %																		
Copper Alloy UNS No.	Copper	Alum-inum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C14530	99.90 ^A min	0.001- 0.010	0.003- 0.023	0.003- 0.023 ^B	...
C15100 ^C	99.80 ^D min	0.05- 0.15
C15500	99.75 ^D min	0.08- 0.13	0.040- 0.080	0.027- 0.10
C17000 ^E	remainder ^D	0.20 max	1.60- 1.79	0.20 ^F min	0.20 max
C17200 ^E	remainder ^D	0.20 max	1.80- 2.00	0.20 ^F min	0.20 max
C17410 ^E	remainder ^D	0.20 max	0.15- 0.50	0.35- 0.6	0.20 max	0.20 max
C17450 ^E	remainder ^D	0.20 max	0.15- 0.50	...	0.20 max	0.50- 1.0	...	0.25 max	0.50 % max	0.20 max
C17460 ^E	remainder ^D	0.20 max	0.15- 0.50	...	0.20 max	1.0- 1.4	...	0.25 max	0.50 % max	0.20 max
C17500 ^E	remainder ^D	0.20 max	0.4- 0.7	2.4- 2.7	0.10 max	0.20 max
C17510 ^E	remainder ^D	0.20 max	0.2- 0.6	0.3 max	0.10 max	1.4- 2.2	0.20 max
C19002 ^E	remainder ^D	0.10	0.05	0.01	...	1.4-1.7 ^G	0.05	0.02-0.30	0.04-0.35	...	0.005- 0.05	0.20- 0.35	0.02- 0.50
C19010 ^E	remainder ^D	0.8- 1.8	0.01- 0.05	0.15- 0.35
C19015 ^H	remainder ^D	0.02-0.15	...	0.50-2.4	0.02-0.20	0.10- 0.40
C19025 ^I	remainder ^D	0.10	0.8- 1.2	0.03- 0.07	0.7- 1.1	0.20 max
C19210 ^H	remainder	0.05- 0.15	0.025- 0.04
C19400 ^H	97.0 min	2.1- 2.6	0.03 max	0.015- 0.15	...	0.05- 0.20
C19500 ^H	96.0 min	0.02 max	...	0.30- 1.3	1.0- 2.0	0.02 max	0.01- 0.35	0.10- 1.0	0.20 max

TABLE 1 Continued

Elements Composition, %

Copper Alloy UNS No.	Copper	Aluminum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C19700 ^H	remainder	0.05 max	0.30–1.2	0.05 max	0.01–0.20	0.05 max	0.05 max	0.10–0.40	0.20 max	0.20 max
C23000 ^H	84.0-86.0	0.05 max	0.05 max	remainder
C26000 ^I	68.5-71.5	0.05 max	0.07 max	remainder
C40810 ^I	94.5-96.5	0.08–0.12	0.05 max	0.11–0.20	0.028–0.04	1.8–2.2	remainder
C40850 ^I	94.5-96.5	0.05–0.20	0.05 max	0.05–0.20	0.01–0.20	2.6–4.0	remainder
C40860 ^I	94.0-96.0	0.01–0.05	0.05 max	0.05–0.20	0.02–0.04	1.7–2.3	remainder
C42200 ^I	86.0-89.0	0.05 max	0.05 max	0.35 max	0.8–1.4	remainder
C42500 ^I	87.0-90.0	0.05 max	0.05 max	0.35 max	1.5–3.0	remainder
C42520 ^I	88.0-91.0	0.05–0.20	0.05 max	0.05–0.20	0.01–0.20	1.5–3.0	remainder
C42600 ^I	87.0-90.0 ^D	0.05–0.20	0.05 max	0.05–0.20 ^G	0.01–0.20	2.5–4.0	remainder
C50580 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	1.0–1.7	0.30 max
C50780 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	1.7–2.3	0.30 max
C51000 ^E	remainder	0.10 max	0.05 max	0.03–0.35	0.03–0.35	4.2–5.8	0.30 max
C51080 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	4.8–5.8	0.30 max
C51100 ^E	remainder	0.10 max	0.05 max	0.03–0.35	3.5–4.9	0.30 max
C51180 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	3.5–4.9	0.30 max
C51980 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	5.5–7.0	0.30 max
C52100 ^E	remainder	0.10 max	0.05 max	0.03–0.35	7.0–9.0	0.20 max
C52180 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	7.0–9.0	0.30 max
C52480 ^E	remainder	0.05–0.20	0.05 max	0.05–0.20	0.01–0.35	9.0–11.0	0.30 max
C63800 ^E	remainder ^D	2.5–3.1	...	0.25–0.55	0.20 max	0.05 max	...	0.10 max	0.20 max	0.8 max	1.5–2.1
C64725 ^E	95.0 min ^D	0.25	0.01	0.20	...	1.3–2.7 ^G	...	0.20–0.8	0.50–1.5	0.09	...	0.20–0.8	0.01 Calcium
C65400 ^E	remainder ^D	0.05 max	1.2–1.9	0.50 max	0.01–0.12	...	2.7–3.4