



Designation: **F138–13 F138 – 13a**

## Standard Specification for Wrought 18Chromium-14Nickel-2.5Molybdenum Stainless Steel Bar and Wire for Surgical Implants (UNS S31673)<sup>1</sup>

This standard is issued under the fixed designation F138; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers the chemical, mechanical, and metallurgical requirements for wrought 18chromium-14nickel-2.5molybdenum stainless steel bar and wire used for the manufacture of surgical implants.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

[A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels](#)

[A484/A484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings](#)

[A555/A555M Specification for General Requirements for Stainless Steel Wire and Wire Rods](#)

[A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)

[E8/E8M Test Methods for Tension Testing of Metallic Materials](#)

[E10 Test Method for Brinell Hardness of Metallic Materials](#)

[E18 Test Methods for Rockwell Hardness of Metallic Materials](#)

[E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications](#)

[E45 Test Methods for Determining the Inclusion Content of Steel](#)

[E112 Test Methods for Determining Average Grain Size](#)

[E354 Test Methods for Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys](#)

[E407 Practice for Microetching Metals and Alloys](#)

[F981 Practice for Assessment of Compatibility of Biomaterials for Surgical Implants with Respect to Effect of Materials on Muscle and Bone](#)

[F1350 Specification for Wrought 18Chromium-14Nickel-2.5Molybdenum Stainless Steel Surgical Fixation Wire \(UNS S31673\)](#)

[IEEE/ASTM SI 10 American National Standard for Metric Practice](#)

#### 2.2 Aerospace Material Standard:<sup>3</sup>

[AMS 2630 Inspection, Ultrasonic Product Over 0.5 inch \(12.7 mm\) Thick](#)

[AMS 2632 Ultrasonic Inspection of Thin Materials](#)

#### 2.3 ISO Standards:<sup>4</sup>

[ISO 5832–1 Implants for Surgery—Metallic Materials—Part 1:Wrought Stainless Steel](#)

[ISO 6892 Metallic Materials—Tensile Testing](#)

[ISO 9001 Quality Management Systems—Requirements](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee F04 on Medical and Surgical Materials and Devices and is the direct responsibility of Subcommittee F04.12 on Metallurgical Materials.

Current edition approved April 1, 2013. Oct. 1, 2013. Published April 2013. November 2013. Originally approved in 1971. Last previous edition approved in 2008 as F138–08. F138 – 13. DOI: 10.1520/F0138-13.10.1520/F0138-13A.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://aerospace.sae.org>.

<sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

\*A Summary of Changes section appears at the end of this standard

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bar, n*—rounds, flats, or other shapes from 0.1875 in. [4.76 mm] to 4 in. [101.60 mm] in diameter or thickness. (Other sizes and shapes by special order.)

3.1.2 *fine wire, n*—wire as described in 3.1.5, less than 0.063 in. [1.60 mm] in diameter or thickness.

3.1.3 *forging bar, n*—bar as described in 3.1.1, used for the production of forgings, may be furnished in the hot worked condition.

3.1.4 *lot, n*—the total number of mill products produced from the same melt heat under the same conditions at essentially the same time.

3.1.5 *wire, n*—rounds, flats or other shapes less than 0.1875 in. [4.76 mm] in diameter or thickness.

### 4. General Requirements for Delivery

4.1 In addition to the requirements of this specification, all requirements of the current editions of Specifications **A484/A484M** and **A555/A555M** shall apply.

4.2 In the case where a conflict exists between this specification and those listed in 2.1 and 2.3, this specification shall take precedence.

### 5. Ordering Information

5.1 Inquiries and orders for material under this specification shall include the following information:

5.1.1 Quantity (weight or number of pieces);

5.1.2 ASTM designation and date of issue;

5.1.3 Form (bar, wire, fine wire);

5.1.4 Condition (see 6.1);

5.1.5 Mechanical properties (if applicable, for special conditions);

5.1.6 Finish (see 6.2);

5.1.7 Applicable dimensions including size, thickness, width, and length (exact, random or multiples) or drawing number;

5.1.8 Special tests, if any; and

5.1.9 Other requirements.

### 6. Materials and Manufacture

#### 6.1 Condition:

6.1.1 Bar and wire shall be furnished, as specified, in the hot worked, annealed, cold worked, or extra hard condition (see **Table 1**).

6.1.2 Fine wire shall be furnished, as specified, in the cold drawn condition (see **Table 2**).

#### 6.2 Finish:

6.2.1 Types of finish available for bar and wire products are cold drawn, pickled, ground, ground and polished, or as specified in the purchase order.

6.2.2 Types of finish available for fine wire products are descaled or pickled, abrasive-blasted, cold drawn, ground, ground and polished, or as specified in the purchase order.

### 7. Chemical Requirements

7.1 The heat analysis shall conform to the requirements as to chemical composition specified in **Table 3**.

7.1.1 The compositional requirement shall meet the following:

$$\% \text{Cr} + 3.3 \times \% \text{Mo} \geq 26.0 \quad (1)$$

**TABLE 1 Mechanical Requirements, Bar and Wire**

Condition	Diameter or Thickness, in. [mm]	Ultimate Tensile Strength, min, psi [MPa]	Yield Strength (0.2 % offset), min, psi [MPa]	Elongation <sup>A</sup> in 4D or 4W, min, %	Brinell <sup>B</sup> Hardness, max, HB
Hot worked <sup>C</sup>	all	.....	.....	.....	250
Annealed	0.063 and over [1.60]	71 000 [490]	27 500 [190]	40	...
Cold worked	0.063 to 1.500 [1.60 to 38.1]	125 000 [860]	100 000 [690]	12	...
Extra-hard	0.063 to 0.250 [1.60 to 6.35]	196 000 [1350]	...	...	...

<sup>A</sup> The gage length must be reported with the test results. 4D = 4 × diameter; 4W = 4 × width. Alternatively, a gage length corresponding to Test Methods **E8/E8M** or ISO 6892 may be used when agreed upon between supplier and purchaser. (5.65 times the square root of So, where So is the original cross sectional area).

<sup>B</sup> 29-kN [3000-kgf] load.

<sup>C</sup> Typically supplied as hot rolled bar for forging applications.

**TABLE 2 Mechanical Requirements, Fine Wire<sup>A</sup>**

Condition <sup>B</sup>	Diameter, in. [mm]	Ultimate <sup>C</sup> Tensile Strength, psi [MPa]	Elongation in 10 in. [254 mm], min, %
Cold drawn	under 0.063 [1.60]	125 000 to 150 000 [860 to 1035]	5

<sup>A</sup> Annealed fine wire requirements are covered in Specification **F1350**.

<sup>B</sup> Recommended crosshead speed for cold drawn fine wire is 5 in./min [2.0 mm/s].

<sup>C</sup> Cold drawn wire may be ordered to tensile strengths up to 300 000 psi [2070 MPa] with lower elongation as determined by the purchaser and supplier.

**TABLE 3 Chemical Requirements, Heat Analysis**

Element	Composition, % (mass/mass)
Carbon	0.030 max
Manganese	2.00 max
Phosphorous	0.025 max
Sulfur	0.010 max
Silicon	0.75 max
Chromium <sup>A</sup>	17.00 to 19.00
Nickel	13.00 to 15.00
Molybdenum <sup>A</sup>	2.25 to 3.00
Nitrogen	0.10 max
Copper	0.50 max
Iron <sup>B</sup>	balance

<sup>A</sup> The compositional requirement shall meet the following:

$$\% \text{Cr} + 3.3 \times \% \text{Mo} \geq 26.0.$$

<sup>B</sup> The percentage of iron content by difference is not required to be determined or certified.

7.1.2 Requirements for the major and minor elemental constituents are listed in **Table 3**. Also listed are important residual elements. Analysis for elements not listed in **Table 3** is not required to certify compliance with this specification.

7.1.3 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology **A751**.

7.2 *Product Analysis*—Product analysis tolerances do not broaden the specified heat analysis requirements, but cover variations between laboratories in the measurement of chemical content. The supplier shall not ship material that is outside the limits specified in **Table 3**. Product analysis limits shall be as specified in **Table 4**.

7.2.1 The product analysis is either for the purpose of verifying the composition of a heat or manufacturing lot or to determine variations in the composition within the heat.

7.2.2 Acceptance or rejection of a heat or lot of material may be made by the purchaser on the basis of this product analysis.

7.2.3 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods **E354**.

## 8. Metallurgical Requirements

8.1 The material shall exhibit no delta ferrite, chi, or sigma phases when it is examined metallographically at 100× magnification when etched in accordance with Practice **E407**.

**TABLE 4 Product Analysis Tolerance<sup>A</sup>**

Element	Tolerance Under the Minimum or Over the Maximum Limit, % (mass/mass) <sup>B</sup>
Carbon	0.005
Manganese	0.04
Phosphorous	0.005
Sulfur	0.005
Silicon	0.05
Chromium	0.20
Nickel	0.15
Molybdenum	0.10
Nitrogen	0.01
Copper	0.03

<sup>A</sup> Refer to Specification **A555/A555M**.

<sup>B</sup> Under minimum limit not applicable for elements where only a maximum percentage is indicated.