



Designation: **D6979—08 D6979 – 13**

Standard Test Method for Polyurethane Raw Materials: Determination of Basicity in Polyols, Expressed as Percent Nitrogen¹

This standard is issued under the fixed designation D6979; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method measures the basic constituents in polyols that are soluble in glacial acetic acid and reactive with perchloric acid. Samples containing 0.3 – 10 % nitrogen have been evaluated by this method. This test method is applicable to polyether polyols and polyether polyol blends that are used in urethane reactions. (See [Note 1.](#))

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—This standard is equivalent to ISO 25761:08

2. Referenced Documents

2.1 *ASTM Standards:*²

[D883 Terminology Relating to Plastics](#)

[E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals](#)
(Withdrawn 2009)³

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

3. Terminology

3.1 *Definitions*—For definitions of terms used in this test method see Terminology [D883](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *percent nitrogen*—the quantity of perchloric acid-titratable base, expressed as a weight percentage of nitrogen in a sample.

4. Summary of Test Method

4.1 The sample is dissolved in glacial acetic acid. The resulting single-phase solution is titrated at room temperature to a potentiometric end point with a standardized solution of perchloric acid in acetic acid. Results are reported as percent nitrogen.

5. Significance and Use

5.1 This test method is suitable for quality control, as a specification test, and for research. The results are measures of batch-to-batch uniformity and may be useful in estimating reactivity.

5.1.1 The percent nitrogen can be used to characterize a polyol or indicate amounts of certain components in a polyol blend.

5.1.2 It is permissible to also express the results in equivalents of base per gram of sample, if desired.

6. Apparatus

6.1 *Potentiometric Automatic Titrator*

6.2 *Autotitrator Buret with Dosing Device, 20-mL*

¹ This test method is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.22](#) on Cellular Materials - Plastics and Elastomers.

Current edition approved ~~Aug. 1, 2008~~ Nov. 1, 2013. Published ~~September 2008~~ November 2013. Originally approved in 2003. Last previous edition approved in 2003 ~~2008~~ as ~~D6979-03~~ [D6979-08](#). DOI: ~~10.1520/D6979-08~~ [10.1520/D6979-13](#).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

6.3 *pH Glass Electrode and Reference Electrode or a Combination Glass Electrode*

6.4 *Analytical Balances, capable of weighing to the nearest 0.01g and 0.0001 g*

6.5 *Magnetic Stirrer/Hotplate*

7. Reagents and Materials

7.1 *Purity of Reagents*—Use reagent-grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.⁴ It is permissible to use other grades provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

7.2 *Acetic Acid, Glacial*

7.3 *Acetic Anhydride*

7.4 *Perchloric Acid, (70 % nominal)*

7.5 *Perchloric acid in Acetic Acid (0.10 N)*—Prepare 0.10 N perchloric acid in acetic acid. For example, in a 1000-mL volumetric flask dissolve 8.7 mL of perchloric acid in 500 mL of glacial acetic acid; add 25 mL of acetic anhydride and dilute to volume with glacial acetic acid.

NOTE 2—Perchloric Acid—is extremely irritating to the skin, eyes and mucous membrane; highly toxic via oral and inhalation routes; and can form explosive mixtures when mixed with carbonaceous material or allowed to dry. Concentrated material shall only be used in a hood approved for perchloric acid use. Skin contact—wash with soap and water. Eye contact—flush with copious amounts of water for 15 minutes. Inhalation - move victim to an uncontaminated area. Ingestion—do not induce vomiting. For all exposures seek professional medical advice.

8. Procedure

8.1 Weigh the appropriate amount of sample, W' into a suitable container. Calculate the target weight of sample to be analyzed as follows:

$$W' = 2/P \quad (1)$$

where:

W' = the target weight of the sample to be analyzed in grams, and

P = the expected percent nitrogen content of the sample.

NOTE 3—For sample weights below 10.0 g, record the weight to the nearest 0.1 mg; for sample weights greater than 10.0 g, record the weight to the nearest 0.01g.

8.2 Add 100 mL of glacial acetic acid and gently stir until the sample dissolves completely.

NOTE 4—If necessary, the mixture can be heated gently until the sample is completely dissolved.

8.3 Titrate the sample solution potentiometrically with 0.10 N perchloric acid through the end point which occurs at ca. 600 mV.

9. Calculation

9.1 Calculate the basicity in the sample, as percent nitrogen as follows:

$$\%N = \frac{S \times N \times 14.00}{W \times 1000} \times 100 \% \quad (2)$$

where:

S = the volume of titrant used to reach the end point of the sample solution titration in millilitres,

N = the normality of the 0.10 N perchloric acid solution in milliequivalents per millilitre,

W = the weight of the sample in grams,

14.00 = the equivalent weight of nitrogen in milligrams per milliequivalent, and

1000 = the factor for converting milligrams to grams

NOTE 5—It is permissible to also report the results as alkalinity in milligrams of potassium hydroxide per gram of sample as follows:

$$\text{Alkalinity, (mg KOH/g)} = \frac{S \times N \times 56.10}{W}$$

where:

the variables have the same meaning as in 9.1 above and 56.10 is the equivalent weight of KOH in mg per meq.

⁴ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.