



Designation: **B98/B98M—08 B98/B98M – 13**

## Standard Specification for Copper-Silicon Alloy Rod, Bar and Shapes<sup>1</sup>

This standard is issued under the fixed designation B98/B98M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification establishes requirements for copper-silicon rod, bar, and shapes for UNS Copper Alloys C65100, C65500, and C66100.

NOTE 1—Material for hot forging is covered by Specification **B124/B124M**.

NOTE 2—For ASME Boiler and Pressure Vessel Code applications, see Specification SB-98 in Section II of that code.

1.2 Units—The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

### 2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.1 *ASTM Standards:*<sup>2</sup>

**B124/B124M** Specification for Copper and Copper Alloy Forging Rod, Bar, and Shapes

**B249/B249M** Specification for General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, Shapes and Forgings

**B950** Guide for Editorial Procedures and Form of Product Specifications for Copper and Copper Alloys

**B601** Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast

**E8E8/E8M** Test Methods for Tension Testing of Metallic Materials

**E8M** Test Methods for Tension Testing of Metallic Materials [Metric] (Withdrawn 2008)<sup>3</sup>

**E18** Test Methods for Rockwell Hardness of Metallic Materials

**E62** Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)<sup>3</sup>

**E478** Test Methods for Chemical Analysis of Copper Alloys

### 3. General Requirements

3.1 The following sections of Specification **B249/B249M** constitute a part of this specification:

3.1.1 Terminology,

3.1.2 Materials and Manufacture,

3.1.3 Workmanship, Finish, and Appearance,

3.1.4 Sampling,

3.1.5 Number of Tests and Retests,

3.1.6 Specimen Preparation,

3.1.7 Test Methods,

3.1.8 Significance of Numerical Limits,

3.1.9 Inspection,

3.1.10 Rejection and Reheating,

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **B05** on Copper and Copper Alloys and is the direct responsibility of Subcommittee **B05.02** on Rod, Bar, Wire, Shapes and Forgings.

Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1934. Last previous edition approved in 2003 as **B98/B98M—03**; **B98/B98M—08**. DOI: 10.1520/B0098\_B0098M-08. 10.1520/B0098\_B0098M-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

- 3.1.11 Certification,
- 3.1.12 Test Report (Mill) Reports,
- 3.1.13 Packaging and Package Marking, and
- 3.1.14 Supplemental Supplementary Requirements.

3.2 In addition, when a section with a title identical to one of those referenced in 3.1 appears in this specification, it contains additional requirements that supplement those which appear in Specification B249/B249M.

#### 4. Ordering Information

4.1 Include the following information in specified choices when placing orders for product under this specification: specification, as applicable:

- 4.1.1 ASTM Designation and year of issue,
- 4.1.2 Copper Alloy UNS No. designation,
- 4.1.3 Temper designation, designation (see Temper Section 7),
- 4.1.4 Quantity; total weight or length, or number of pieces of each temper, form, or alloy,
- 4.1.5 Dimensions; diameter or distance between parallel surfaces,
- 4.1.6 Type of edge; edge contours,
- 4.1.7 How furnished; specific lengths with or without ends, and
- 4.1.8 When material is purchased for agencies of the U.S. Government (see Specification Intended application B249/B249M).

4.2 The following options are available under this specification and should be specified in the contract or purchase but may not be included unless specified at the time of placing of the order when required:

- 4.2.1 Certification (Specification B249/B249M), and
- 4.2.2 Mill Test Report (Specification B249/B249M).
- 4.2.3 Tensile test required for alloys in Table 4 or Table 5 (see 8.1.1.1),
- 4.2.4 If product is purchased for agencies of the U.S. Government (see Supplementary Requirements in B249/B249M).

#### 5. Material and Manufacture

5.1 *Materials*—The starting material shall be cast billets or rods of Copper Alloy UNS Nos. C65100, C65500, or C66100, and shall be of such soundness and structure as to enable them to be processed into the product specified in the contract or purchase order.

5.2 *Manufacture*—The product shall be manufactured by such hot-working, cold-working, straightening, and annealing processing as to produce a uniform wrought structure and obtain the required finish properties.

#### 6. Chemical Composition

6.1 The product material shall conform to the chemical requirements specified in Table 1 for the Copper Alloy UNS No. designated in the ordering information.

6.1.1 For alloys in which copper is listed as “remainder,” copper is the difference between the sum of the results of all elements determined and 100 %.

6.1.2 When all elements listed in Table 1 are determined for the designated alloy, the sum of results shall be 99.5 % min.

6.2 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer and the purchaser.

**TABLE 1 Chemical Requirements**

	Composition, % Maximum (Unless Shown as a Range or Minimum)		
	Copper Alloy UNS No.		
	C65100	C65500	C66100
Copper (Includes silver)	remainder	remainder	remainder
Lead	0.05	0.05	0.20–0.8
Iron	0.8	0.8	0.25
Zinc	1.5	1.5	1.5
Manganese	0.7	0.50–1.3	1.5
Silicon	0.8–2.0	2.8–3.8	2.8–3.5
Nickel (includes cobalt)	...	0.6	...
Nickel (includes cobalt)	...	0.6	...

**TABLE 2 Tensile Requirements, Inch-pound/Inch-Pound (see Table 3 for SI)**

Temper Designation	Diameter or Distance Between Parallel Surfaces, <sup>A</sup> in.	Tensile Strength min, ksi	Yield Strength at 0.5 % Extension Under Load, min, ksi	Elongation in 4 × Diameter or Thickness of Specimen, min, % <sup>B</sup>	
Code	Name				
<b>Copper Alloy UNS No. C65100 Rods, Bars, and Shapes</b>					
O60	Soft anneal	All forms, all sizes	40	12	30
H02	Half-hard	Rods:			
		Up to ½, incl	55	20	11
		Over ½ to 2, incl	55	20	12
		Bars and shapes	c	c	c
H04	Hard	Rods:			
		Up to ½, incl	65	35	8
		Over ½ to 2, incl	65	35	10
		Bars and shapes	c	c	c
H06	Extra-hard	Rods:			
		Up to ½, incl	85	55	6
		Over ½ to 1, incl	75	45	8
		Over 1 to 1½, incl	75	40	8
<b>Copper Alloy UNS Nos. C65500 and C66100 Rectangular Bars</b>					
O60	Soft anneal	All sizes	52	15	35
H04	Hard	Up to 1, incl	65	38	20
		Over 1 to 1½, incl	60	30	25
		Over 1½ to 3, incl	55	24	27
<b>Copper Alloy UNS Nos. C65500 and C66100 Rods, Square Bars, and Shapes</b>					
O60	Soft anneal	All forms, all sizes	52	15	35
H01	Quarter-hard	All forms, all sizes	55	24	25
H02	Half-hard	Rods and square bars:			
		Up to 2, incl	70	38	20
		Shapes	c	c	c
H04	Hard	Rods and square bars:			
		Up to ¼, incl	90	55	8
		Over ¼ to 1, incl	90	52	13
		Over 1 to 1½, incl	80	43	15
		Over 1½ to 3, incl	70	38	17
		Over 3	c	c	c
		Shapes	c	c	c
H06	Extra-hard	Rods: up to ½, incl	100	55	7

<sup>A</sup> For rectangular bar, the Distance Between Parallel Surfaces refers to thickness.

<sup>B</sup> In any case a minimum gage length of 1 in. shall be used.

<sup>C</sup> As agreed upon between manufacturer and purchaser.

## ASTM B98/B98M-13

### 7. Temper

7.1 The standard tempers, as defined in Classification B601, for products described in this specification are given in Tables 2-5.

7.1.1 Soft annealed O60,

7.1.2 ¼-hard H01,

7.1.3 ½-hard H02,

7.1.4 Hard H04,

7.1.5 Extra-hard H06,

7.1.6 As hot rolled M20, and

7.1.7 As hot extruded M30.

7.2 Product of bars and shapes in the temper H06 is normally not produced.

### 8. Mechanical Property Requirements

8.1 ~~The product~~ Product furnished under this specification shall conform to the ~~mechanical property requirements given~~ tensile and hardness requirements prescribed in Tables 2-5 for the Copper Alloy UNS No. designation specified in the ordering information.

8.1.1 ~~Rockwell Hardness—Hardness Requirement—~~For the alloys and tempers listed, product 0.5 in. (12 mm) [12 mm] and over in diameter or distance between parallel surfaces shall conform with the requirements given in Table 4 and Table 5, when tested in accordance with Test Methods E18.

8.1.1.1 For the alloys and tempers listed in Table 4 and Table 5, Rockwell hardness shall be the basis of acceptance or rejection for mechanical properties except when the tensile test is specified in the contract or purchase order.

8.1.2 ~~Tensile Strength—Strength Requirements—~~The product shall conform with the requirements of Table 2 and Table 3 when tested in accordance with Test Methods E8E8/E8M or E8M.

8.1.2.1 The tensile requirements for all alloys and forms of M20 and M30 tempers shall be as agreed upon between the manufacturer and purchaser at time of order.