



Designation: **A283/A283M – 12a** A283/A283M – 13

Standard Specification for Low and Intermediate Tensile Strength Carbon Steel Plates¹

This standard is issued under the fixed designation A283/A283M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

- 1.1 This specification² covers two grades (C and D) of carbon steel plates of structural quality for general application.
- 1.2 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification **A6/A6M** for information on weldability.
- 1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exactly equivalents; therefore, each system is to be used independently of the other, without combining values in any way.
- 1.4 For plate produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification **A6/A6M** apply.
- 1.5 This specification contains notes or footnotes, or both, that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

2. Referenced Documents

- 2.1 *ASTM Standards*:³
A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

3. General Requirements for Delivery

- 3.1 Plates furnished under this specification shall conform to the requirements of the current edition of Specification **A6/A6M**, for the specific date ordered, unless a conflict exists, in which case this specification shall prevail.
- 3.2 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding plate produced from coil are described in Specification **A6/A6M**.

4. Process

- 4.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace.
- 4.2 The steel shall be killed.

5. Chemical Requirements

- 5.1 The heat analysis shall conform to the requirements prescribed in **Table 1**.

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.02** on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved Nov. 1, 2012/Nov. 15, 2013. Published March 2013/November 2013. Originally approved in 1946. Last previous edition approved in 2012 as **A283/A283M – 12-A283/A283M – 12a**. DOI: 10.1520/A0283_A0283M-12A-10.1520/A0283_A0283M-13.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-283/SA 283M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard