



Designation: **E2651—10 E2651 – 13**

Standard Guide for Powder Particle Size Analysis¹

This standard is issued under the fixed designation E2651; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This guide covers the use of many available techniques for particle size measurement and particle size distribution analysis of solid particulate (powder) materials. It does not apply to analysis of liquid droplets or liquid aerosols. The guide is intended to serve as a resource for powder/particle technologists in characterizing their materials.

1.2 This guide provides more detail regarding the particle size analysis methods listed in Guide E1919, which is a compilation of worldwide published standards relating to particle and spray characterization. Although Guide E1919 and this guide are both extensive, neither is all inclusive.

1.3 The principle of operation, range of applicability, specific requirements (if any), and limitations of each of the included particle size analysis techniques are listed and described, so that users of this guide may choose the most useful and most efficient technique for characterizing the particle size distribution of their particular material(s).

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[B215 Practices for Sampling Metal Powders](#)

[B330 Test Methods for Estimating Average Particle Size of Metal Powders and Related Compounds Using Air Permeability](#)

[B821 Guide for Liquid Dispersion of Metal Powders and Related Compounds for Particle Size Analysis](#)

[B859 Practice for De-Agglomeration of Refractory Metal Powders and Their Compounds Prior to Particle Size Analysis](#)

[C322 Practice for Sampling Ceramic Whiteware Clays](#)

[E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves](#)

[E1617 Practice for Reporting Particle Size Characterization Data](#)

[E1638 Terminology Relating to Sieves, Sieving Methods, and Screening Media](#)

[E1919 Guide for Worldwide Published Standards Relating to Particle and Spray Characterization](#)

[E2589 Terminology Relating to Nonsieving Methods of Powder Characterization](#)

3. Terminology

3.1 *Definitions:*

3.1.1 For definitions of terms used in this guide, refer to Terminologies E1638 and E2589.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *powder, n*—a collection of solid particles that are usually less than 1000 μm (1 mm) in size.

4. Significance and Use

4.1 The myriad array of particle size analysis techniques available to the modern-day powder technologist is both daunting and confusing. Many of the techniques are applicable only to certain types of materials, and all have limited ranges of applicability

¹ This guide is under the jurisdiction of ASTM Committee E29 on Particle and Spray Characterization and is the direct responsibility of Subcommittee E29.02 on Non-Sieving Methods.

Current edition approved May 1, 2010/Nov. 1, 2013. Published October 2010/November 2013. Originally approved in 2008. Last previous edition approved in 2008/2010 as E2651—08/E2651 – 10. DOI: 10.1520/E2651-10.1520/E2651-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

with respect to powder particle size. This guide is an attempt to describe and define the applicability of each of the available techniques, so that powder technologists, and others interested in powders, may make informed and appropriate choices in characterizing their materials.

4.2 This guide is intended to be used to determine the best and most efficient way of characterizing the particle size distribution of a particular powder material. It may also be used to determine whether a reported powder particle size, or size distribution, was obtained in an appropriate and meaningful way.

4.3 Most particle size analysis techniques report particle size in terms of an “equivalent spherical diameter”—diameter:” the diameter of an ideal spherical particle of the material of interest that would be detected in the same manner during analysis as the (usually irregular-shaped) actual particle under the same conditions. The different techniques must necessarily use different definitions of the equivalent spherical diameter, based on their different operating principles. However, when analyzing elongated particles, the size parameter most relevant to the intended application should be measured; for example, length (maximum dimension).

4.4 Reported particle size measurement is a function of both the actual dimension ~~and/or shape factor~~ or shape factor, or both, as well as the particular physical or chemical properties of the particle being measured. Caution is required when comparing data from instruments operating on different physical or chemical parameters or with different particle size measurement ranges. Sample acquisition, handling, and preparation can also affect reported particle size results.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals should be used in all tests. Unless otherwise indicated, it is intended that all reagents should conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Surfactants*—Suitable surfactants are listed in references **(1-3)**.⁴

6. Sampling

6.1 The first step in performing a powder particle size analysis is obtaining a sample of the powder that is intended to be representative of the entire amount. There are two conditions necessary for obtaining an accurate sample of a powder **(4)**: The first is that the sampling must be probabilistic; that is, every increment of the powder must have *some* probability of being selected in the sampling process. The sampling must not only be probabilistic, it must also be correct. That means that *every* sample increment must have an equal probability of being chosen. No method of sampling can *guarantee* a representative sample, but adherence to certain “Golden Rules of Sampling” **(1)** will satisfy these two conditions and ensure a sample as close to representative as possible. These rules are:

6.1.1 Always sample a powder in motion (for example, pouring from a blender, or off the end of a conveyor).

6.1.2 Take small portions for many short increments of time from the *whole* stream of powder.

6.1.3 *Never* scoop a sample from a heap or container of powder.

6.2 The preferred method of sampling is to use a spinning (rotary) riffler; however, this is not always possible. Devices that adhere to these rules, such as chute rifflers, spinning rifflers, and stream samplers, are available commercially. Examples of good powder sampling practices may be found in Practices **B215** and **C322**.

7. Dispersion

7.1 The method of powder dispersion has a significant effect on the results of a particle size distribution analysis. The analysis will show a too-coarse, unstable, or non-repeatable distribution if the powder has not been dispersed adequately. It is therefore important that parties wishing to compare their analyses use the same dispersion technique.

7.2 Many particle size analysis instruments are capable of, or require, dispersing powders in a liquid medium. Guide **B821** contains recommended liquid dispersion procedures for certain metal powders and related compounds. That guide also contains general procedures for dispersing powders in liquids, and assessing dispersion. Those general procedures are repeated here:

7.3 The general procedure for determining and achieving proper dispersion is outlined in **Fig. 1 (5)** and described in detail below:

7.3.1 Place a test portion of the powder to be analyzed in a beaker containing the carrier liquid, selected according to **7.3.2**.

7.3.2 *Selection of Carrier Liquid*:

NOTE 1—The selected carrier liquid must be compatible with the components of the instrument used for the particle size analysis.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC, www.chemistry.org. For suggestions on the testing of reagents not listed by the American Chemical Society, see the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD, http://www.usp.org.

⁴ The boldface numbers in parentheses refer to the list of references at the end of this standard.