

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
18692-5

ISO/TC 38

Secretariat: SAC

Voting begins on:
2023-12-08

Voting terminates on:
2024-02-02

Fibre ropes for offshore stationkeeping —

Part 5: Aramid

*Cordages en fibres pour le maintien en position des structures
marines —*

Partie 5: Aramide

iteh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/FDIS 18692-5](https://standards.iteh.ai/catalog/standards/sist/525b7c95-f10c-4157-87a4-320a80d06683/iso-fdis-18692-5)

<https://standards.iteh.ai/catalog/standards/sist/525b7c95-f10c-4157-87a4-320a80d06683/iso-fdis-18692-5>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 18692-5:2023(E)

© ISO 2023

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO/FDIS 18692-5](https://standards.iteh.ai/catalog/standards/sist/525b7c95-f10c-4157-87a4-320a80d06683/iso-fdis-18692-5)

<https://standards.iteh.ai/catalog/standards/sist/525b7c95-f10c-4157-87a4-320a80d06683/iso-fdis-18692-5>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Materials.....	1
5 Requirements — Rope properties.....	2
5.1 Minimum breaking strength.....	2
5.2 Minimum core tenacity.....	2
5.3 Axial compression fatigue properties.....	2
5.4 Cyclic loading performance.....	2
5.5 Particle ingress protection.....	2
6 Requirements — Rope layout and construction.....	3
7 Rope testing.....	3
7.1 Type testing.....	3
7.1.1 General.....	3
7.1.2 Sampling.....	3
7.1.3 Breaking strength, core tenacity, and stiffness tests.....	3
7.1.4 Axial compression fatigue properties test.....	3
7.1.5 Torque properties tests.....	3
7.1.6 Linear density test.....	4
7.1.7 Cyclic loading (endurance) test.....	4
7.1.8 Protective cover thickness.....	4
7.1.9 Particle ingress protection.....	4
7.2 Testing of current production.....	4
8 Report.....	4
9 Certification.....	4
10 Marking, labelling and packaging.....	4
Annex A (normative) Fibre qualification and testing.....	5
Annex B (normative) Axial compression fatigue properties test.....	6
Annex C (informative) Additional information and guidance.....	8
Bibliography.....	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

This first edition of ISO 18692-5 cancels and replaces ISO/TS 17920:2015, which has been technically revised.

The main changes are as follows:

- the document previously, published as a Technical Specification, has been reorganized as the new ISO 18692-5, taking into account the content of ISO 18692-1.

A list of all parts in the ISO 18692 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Fibre ropes for offshore stationkeeping —

Part 5: Aramid

1 Scope

This document specifies the main characteristics and test methods of new aramid fibre ropes used for offshore stationkeeping.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1968, *Fibre ropes and cordage — Vocabulary*

ISO 18692-1, *Fibre ropes for offshore stationkeeping — Part 1: General specification*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1968, ISO 18692-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

3.1

aramid

long-chain synthetic polyamide in which at least 85 % of the amide linkages are attached directly to two aromatic rings

Note 1 to entry: Adapted from ISO 2076:2021, 5.9.

3.2

axial compression fatigue

failure mode for fibre rope such as *aramid* (3.1) under low tension or compression

4 Materials

The fibre used in the core of the rope shall be aramid fibre, with an average tenacity of not less than 1,8 N/tex, and shall be qualified and tested in accordance with [Annex A](#).

Rope cover material and other materials employed in rope assembly shall be in accordance with ISO 18692-1.

5 Requirements — Rope properties

5.1 Minimum breaking strength

The minimum breaking strength (MBS) of the rope (spliced), when tested according to ISO 18692-1, shall conform to [Table 1](#).

Table 1 — Minimum breaking strength (MBS)

Reference number(RN) ^a	Minimum breaking strength kN
80	2 500
90	3 100
100	3 900
106	4 400
112	5 000
118	5 600
125	6 300
132	7 000
140	7 800
150	8 700
160	10 000
170	11 200
180	12 500
190	14 000
200	15 500
212	17 500
224	19 500

^a The reference number corresponds to the approximate outer diameter of the rope, in millimetres (mm). Actual diameters may vary for a given reference number.

5.2 Minimum core tenacity

The minimum tenacity of the aramid rope core shall be 0,90 N/tex, measured according to ISO 18692-1. All samples tested shall comply with this minimum value.

5.3 Axial compression fatigue properties

The rope shall have demonstrated a residual strength not less than 95 % of MBS, following the axial compression fatigue test method in [Annex B](#). Additional information is given in [Annex C](#).

Torque properties, torque-neutral rope or torque-matched rope shall be defined according to ISO 18692-1.

5.4 Cyclic loading performance

The rope shall have demonstrated performance under cycling loading following the requirements of ISO 18692-1.

5.5 Particle ingress protection

Unless otherwise specified, the rope shall be constructed with a protection of the core against the ingress of particles in accordance with ISO 18692-1.