



Designation: ~~D6878/D6878M – 11a~~ D6878/D6878M – 13

Standard Specification for Thermoplastic Polyolefin Based Sheet Roofing¹

This standard is issued under the fixed designation D6878/D6878M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers flexible sheet made from thermoplastic polyolefin (TPO) as the principal polymer, intended for use in single-ply roofing membranes exposed to the weather. The sheet shall contain reinforcing fabrics or scrim.

1.2 The tests and property limits used to characterize the sheet are values intended to ensure minimum quality for the intended purpose. In-place roof system design criteria, such as fire resistance, field seaming strength, material compatibility, and uplift resistance, among others, are factors which should be considered but are beyond the scope of this specification.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory requirements prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D471 Test Method for Rubber Property—Effect of Liquids](#)

[D573 Test Method for Rubber—Deterioration in an Air Oven](#)

[D751 Test Methods for Coated Fabrics](#)

[D1149 Test Methods for Rubber Deterioration—Cracking in an Ozone Controlled Environment](#)

[D1204 Test Method for Linear Dimensional Changes of Nonrigid Thermoplastic Sheet or Film at Elevated Temperature](#)

[D2137 Test Methods for Rubber Property—Brittleness Point of Flexible Polymers and Coated Fabrics](#)

[D5538 Practice for Thermoplastic Elastomers—Terminology and Abbreviations](#)

[D7635/D7635M Test Method for Measurement of Thickness of Coatings Over Fabric Reinforcement](#)

[G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources](#)

[G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials](#)

3. Materials and Manufacture

3.1 The sheet shall be formulated from ethylene and higher alpha-olefin polymers, copolymers, and mixtures thereof, in amounts greater than 50 %, by weight of the total polymer content suitably compounded to satisfy the physical requirements in the specification (see Practice [D5538](#)).

3.2 The sheet shall be capable of being heat welded, fused, or adhesively bonded to itself for making watertight field splices and repairs, and the supplier or fabricator shall recommend suitable methods and materials.

3.3 Sheet shall be reinforced with fabric or scrim.

4. Physical Properties and Tolerances

4.1 Each sheet specimen shall meet or exceed the physical requirements prescribed in [Table 1](#).

¹ This specification is under the jurisdiction of ASTM Committee [D08](#) on Roofing and Waterproofing and is the direct responsibility of Subcommittee [D08.18](#) on Nonbituminous Organic Roof Coverings.

Current edition approved ~~June 1, 2011~~ Dec. 15, 2013. Published ~~June 2011~~ December 2013. Originally approved in 2003. Last previous edition approved in 2011 as ~~D6878 – 11~~ [D6878/D6878M – 11a](#). DOI: ~~10.1520/D6878-D6878M-11a~~ [10.1520/D6878_D6878M-13](#).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



TABLE 1 Physical Requirements for TPO Sheet

| | |
|--|-------------------|
| Thickness, min, mm [in.] | |
| — Sheet overall | 1.0 [0.039] |
| — Coating over fabric or scrim, weathering side only | 0.38 [0.015] |
| Breaking strength, min, N [lbf] | 976 [220] |
| Elongation at reinforcement break, min, % | 15 |
| Tearing strength, min, N [lbf] | 245 [55] |
| Brittleness point, max, °C [°F] | -40 [-40] |
| Ozone resistance, no cracks | Pass |
| Properties after heat aging: (retained values) | |
| — Breaking strength, % min | 90 |
| — Elongation at reinforcement break, % min | 90 |
| — Tearing strength, % min | 60 |
| — Weight change (mass), max % | ±1 |
| Linear dimensional change, max, % | ±1 |
| Water absorption, max, mass % | ±3.0 ^A |
| Factory seam strength, min, N [lbf] | 290 [66] |
| Weather resistance: | |
| — Visual inspection | Pass |

TABLE 1 Physical Requirements for TPO Sheet

| | |
|--|-------------------|
| Thickness, min, mm [in.] | |
| — Sheet overall | 1.0 [0.039] |
| — Coating over fabric or scrim, weathering side only | 0.38 [0.015] |
| Breaking strength, min, N [lbf] | 976 [220] |
| Elongation at reinforcement break, min, % | 15 |
| Tearing strength, min, N [lbf] | 245 [55] |
| Brittleness point, max, °C [°F] | -40 [-40] |
| Ozone resistance, no cracks | Pass |
| Properties after heat aging: (retained values) | |
| — Breaking strength, % min | 90 |
| — Elongation at reinforcement break, % min | 90 |
| — Tearing strength, % min | 60 |
| — Weight change (mass), max % | ±1 |
| Linear dimensional change, max, % | ±1 |
| Water absorption, max, mass % | ±3.0 ^A |
| Factory seam strength, min, N [lbf] | 290 [66] |
| Weather resistance: | |
| — Visual inspection | Pass |

^A Test performed on top coating material only. (Use Test Method D471, Procedure for Change in Mass.)

ASTM D6878/D6878M-13

<https://standards.iteh.ai/catalog/standards/sist/09ade5fd-744f-4982-be21-730372d37768/astm-d6878-d6878m-13>

4.2 The tolerance for time conditions (aging, weathering, and so forth) is ± 15 min or ± 1 % of the period, whichever is greater, unless otherwise specified.

4.3 The tolerance for temperature conditions (aging, weathering, and so forth) is $\pm 2^{\circ}\text{C}$ [$\pm 4^{\circ}\text{F}$] of the specified temperature, unless otherwise specified.

5. Dimensions and Permissible Variations

5.1 The width and length of the sheet shall be agreed upon between the purchaser and the supplier.

5.1.1 The width and length tolerance shall be +3 %, -0 %.

5.1.2 The thickness tolerance shall be +15 %, -10 % of thickness agreed upon by the purchaser and supplier, but in no case shall it be less than the minimum in Table 1.

5.1.3 The thickness of coating over scrim (reinforcing fabric) of the weathering side shall be at least 30 % of the overall thickness as agreed upon by the purchaser and supplier, but in no case shall it be less than the minimum in Table 1. The table below can be used as a reference for commonly used thicknesses.

| Overall Thickness, mm [in.] | Thickness of Coating Over Scrim, min, mm [in.] |
|-----------------------------|--|
| 1.1 [0.045] | 0.38 [0.015] |
| 1.5 [0.060] | 0.48 [0.018] |
| 2.0 [0.080] | 0.60 [0.024] |

6. Workmanship, Finish, and Appearance

6.1 The sheet, including factory seams, if present, shall be watertight and free of pinholes, particles of foreign matter, protruding fibers or reinforcement, undispersed raw material, nicks and cuts, voids, thin areas, delaminations or other manufacturing defects that might adversely affect serviceability.

6.2 Edges of the sheets shall be capable of being seamed to one another without fishmouthing.