
International Standard



3383

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Rubber — General directions for achieving elevated or subnormal temperatures for test purposes

Caoutchouc — Directives générales pour l'obtention de températures élevées ou de températures inférieures à la température normale lors des essais

Second edition — 1985-12-15

ITh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3383:1985](https://standards.iteh.ai/catalog/standards/sist/bd8cc8dc-2f36-4ee7-9de3-67ad4f04bdf/iso-3383-1985)

<https://standards.iteh.ai/catalog/standards/sist/bd8cc8dc-2f36-4ee7-9de3-67ad4f04bdf/iso-3383-1985>

UDC 678.4 : 620.1 : 536

Ref. No. ISO 3383-1985 (E)

Descriptors : rubber, tests, high temperature tests, low temperature tests, conditioning.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 3383 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*.

This second edition cancels and replaces the first edition (ISO 3383-1976), of which it constitutes a technical revision. <https://standards.iteh.ai/catalog/standards/sist/bd8cc8dc-2f36-4ee7-9de3-67adf4f04bdf/iso-3383-1985>

Users should note that all International Standards undergo revision from time to time and that any reference made herein to any other International Standard implies its latest edition, unless otherwise stated.

Rubber — General directions for achieving elevated or subnormal temperatures for test purposes

1 Scope and field of application

This International Standard specifies general requirements for achieving elevated or subnormal temperatures in the testing of rubber and other elastomeric materials. It specifies general principles of the construction and operation of temperature-controlled chambers for conditioning and/or testing. For some tests — for example ageing tests — special procedures, conditions or equipment which differ from those specified in this International Standard may be required. In such cases, the requirements should be included in the method of test and supersede the requirements of this International Standard.

2 Purpose of conditioning

The purpose of conditioning procedures is to ensure that the test piece is substantially at a uniform temperature throughout its mass and in equilibrium with its environment.

3 Heat transfer media

For the control of temperature in the conditioning and/or test chambers, various temperature-control media may be employed, the most common being gaseous or liquid. Liquid media offer the most rapid heat transfer but may have deleterious effects on the rubber if the immersion is prolonged. Fluidized beds using glass ballotini have many of the advantages of liquid heat transfer combined with chemical inertness.

4 General requirements for temperature-controlled chambers

4.1 The immersion medium in the chamber shall be without significant effects on the rubber properties. Water, ethanol and ethylene glycol are examples of fluids that have been found to have insignificant effects on most solid rubbers, provided that the immersion period is kept to the absolute minimum required in the testing.

4.2 The portion of the chamber in which test pieces may be located shall be controlled within the specified tolerances of the relevant method of test.

4.3 The immersion medium shall be circulated thoroughly in the chamber. A fan or stirrer suitably located in the chamber may be used for this purpose.

4.4 Automatic temperature control is preferred.

4.5 Recovery to the set temperatures after the introduction of test pieces or test apparatus shall be as rapid as possible consistent with minimal overshoot or undershoot, but in any case shall not exceed 15 min, particular care being required for gaseous media.

4.6 The size of the chamber is optional, provided that uniform temperature is maintained throughout the space occupied by the test pieces.

4.7 The chamber shall be thermally insulated to prevent condensation on exterior surfaces when testing at subnormal temperatures and to prevent discomfort to the touch when testing at elevated temperatures.

The thermal insulation should be stable at the maximum design temperature, shall be protected from condensation at subnormal temperatures and shall ensure the maximum attainable uniformity of temperature. If a window is needed to observe test equipment indicators, it shall be constructed so as to ensure adequate thermal insulation and to prevent condensation. For example for a chamber operating at $-100\text{ }^{\circ}\text{C}$, five layers of glass, suitably spaced, with dehydrated air between layers, has been found to be suitable.

4.8 The construction of the chamber depends on the type of immersion medium. For gaseous media, a side entrance for introducing test pieces is convenient, and is necessary where the test equipment is operated from the side. However, the chamber shall be designed to minimize the loss of gaseous media where the test pieces or equipment are introduced. The interior walls surrounding the chamber shall be made of a good thermal conductor, preferably aluminium or tinned copper, to ensure uniform temperature and minimum radiant effects. When manual operation of equipment (except for mounting and demounting of test pieces) inside the chamber is necessary, handholes equipped with gloves and insulated sleeves shall be installed in the walls of the chamber. The temperature shall not be controlled by cooling and heating elements within the chamber mounted in such a way that they can affect the temperature of test equipment or test pieces by radiation.

For liquid media, the temperature may be controlled by elements immersed in the medium or by circulating the medium to a heat-exchange system outside the chamber.

5 Chambers operating at elevated temperatures

5.1 Chambers with gaseous heat transfer media

Such chambers should normally conform to the requirements of clause 4. The gaseous medium, usually air, is heated by means of electric elements, a fan or blower being provided to ensure adequate air circulation. The electric elements shall be shielded to avoid direct radiation on to the test pieces. To obtain the necessary precision of temperature control, the heating system shall :

- a) use a recirculating gas system;
- b) be designed so that most of the heat required is supplied continuously and the remainder intermittently for temperature control or with proportionating devices on the heat supply that prevent large cyclic variations in temperature.

NOTE — In the case of recirculating gas systems, care should be taken at higher temperatures to avoid the possibility of cross-contamination by volatile constituents of rubber samples.

5.2 Chambers with liquid heat transfer media

Such chambers should conform to the requirements of clause 4 and follow the same principles as in 5.1, using an immersion heater in place of the electric elements and a stirrer or pump in place of a fan or blower.

5.3 Fluidized beds

Such chambers should conform to the requirements of clause 4 by utilizing a bed of inert material, such as glass ballotini, which may be "fluidized" (i.e. given the properties of a fluid) by passing a suitable gas through the bed at a suitable velocity. Heaters may be embedded in the bed, or the gas stream itself may be heated.

6 Chambers operating at subnormal temperatures

Several types of such chambers are available, the chief of which are described in 6.1 to 6.5.

6.1 Mechanically refrigerated units

In general, a mechanically refrigerated low-temperature chamber consists of a multi-stage compressor and suitable cooling coils which surround the test chamber. Suitable insulation is provided between the test piece compartment and the outside walls of the chamber. Automatic temperature control is obtained either by a thermostatic control located in the test piece compartment, which turns the compressor on or off, or by a suitable pressure control which regulates the refrigerant temperature. Air is used as the heat transfer medium in the test piece compartment. This type of equipment is well adapted to continuous operation at a fixed temperature. Except for rather high maintenance and initial costs, this type of equipment is less expensive to operate continuously from a power standpoint than are solid carbon dioxide units. Another advantage of

mechanical refrigeration is that lower temperatures are available. By the installation of electric strip heaters and suitable automatic controls, temperatures up to room temperature and above can be obtained.

6.2 Solid carbon dioxide units (direct type)

In the direct type of solid carbon dioxide low-temperature chamber, a suitable fan or blower, located in the solid carbon dioxide compartment, circulates the carbon dioxide vapour from the solid carbon dioxide compartment into the test piece compartment and back. By means of a preset damper between the solid carbon dioxide compartment and the test piece compartment, the inlet and outlet openings may be adjusted for maximum efficiency. A bimetallic thermoregulator, located in the test piece compartment, controls the "on" and "off" operation of the fan in the solid carbon dioxide compartment, thus providing automatic temperature control.

Alternatively, the test piece compartment may consist of a suitably insulated vessel containing a liquid medium which does not affect the rubber and which remains liquid at the required temperature of test. The temperature of the liquid is adjusted by the addition of small portions of the coolant. In the case of solid carbon dioxide, care is needed to prevent the boiling over of liquid from the vessel. To ensure uniformity of temperature in the test piece compartment, a fan or stirrer is provided. More accurate temperature control may be obtained by the addition of thermostatically controlled heaters inside the test piece compartments.

6.3 Solid carbon dioxide units (indirect type)

In the indirect type of solid carbon dioxide low-temperature chambers, air is used as the heat transfer medium and no carbon dioxide from the solid carbon dioxide comes into contact with the test pieces. The test piece compartment is cooled by circulating the carbon dioxide vapour completely around the outside of the test piece compartment, which, in turn, is insulated from the outside of the cold box. In general, this type is of more costly construction than the direct type and is not quite as efficient. The time required to cool the test piece compartment to a low temperature is somewhat greater and is more comparable in this respect to the mechanically refrigerated units.

Alternatively, the test piece compartment may consist of a suitably insulated vessel containing a liquid medium which does not affect the rubber and which remains liquid at the temperature of test. The temperature of the liquid is adjusted by circulating the liquid through a suitable heat-exchanger located externally to the vessel, where the temperature of the liquid is lowered by packing the outside of the heat-exchanger with solid carbon dioxide contained in a suitably insulated compartment.

6.4 Packaged-air units

It is frequently desirable to enclose a piece of test equipment in a separate chamber and circulate temperature-regulated cold air or carbon dioxide from a separate unit through insulated ducts or pipes. This type of unit is somewhat similar to the direct type of solid carbon dioxide unit (see 6.2), but contains an auxiliary blower to force the cold air through the pipes to the

separate chamber. It has the advantage of being portable, and can be connected to different pieces of equipment.

In some cases the temperature is controlled by a motor-driven damper which bypasses the cold chamber or test chamber, rather than by control of the fan motor itself. Motor or solenoid driven dampers which operate in the compartment for temperature control may cause trouble due to frosting of the machine. No entirely satisfactory method has yet been devised for removing sufficient moisture from the heat transfer medium to eliminate frosting completely. Desiccants such as calcium chloride and calcium sulfate have been used.

6.5 Liquid nitrogen

Liquid nitrogen is an effective means of maintaining chambers at subnormal temperatures. The liquid nitrogen may be injected into the chamber as required to control the temperature or the gas in the chamber may be circulated to a liquid nitrogen vessel outside the chamber in such volume as is required for temperature control. When liquid nitrogen is injected, it shall be completely vaporized and the nitrogen gas shall be at test temperature before contacting the test equipment or test pieces.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3383:1985](https://standards.iteh.ai/catalog/standards/sist/bd8cc8dc-2f36-4ee7-9de3-67ad4f04bdf/iso-3383-1985)

<https://standards.iteh.ai/catalog/standards/sist/bd8cc8dc-2f36-4ee7-9de3-67ad4f04bdf/iso-3383-1985>

Annex

Conditioning times for rubber test pieces

(This annex forms an integral part of the Standard.)

Tables 1 to 3 give the calculated times for the test piece centres to reach 1 °C of the set temperature starting from an initial temperature of 20 °C. The time will depend on the geometry, the material, and the type of heating medium.

To make individual calculations for every test piece in current use would be impractical. Fortunately nearly all test pieces fall into three geometries : cylinders, flat sheets, and flat strips. Dumb-bell test pieces used in tensile tests may be considered as flat strips.

The heating times depend on the thermal properties of the sample material. For rubber thermal diffusivity may be taken as 0,1 mm²/s, and thermal conductivity as 0,2 W/(m.K).

The majority of temperature controlled cabinets use either air or a liquid as the heat transfer medium. To generate the tables a heat transfer coefficient in air of 20 W/(m².K) was used. Different liquids will have different values for the heat transfer coefficient, but for most purposes a single value of 750 W/(m².K) is adequate.

The conditioning time is not critical to the nearest minute, although it is essential that the test piece is given sufficient time to reach equilibrium. All times in the table have been rounded up to the next highest multiple of 5 min.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Table 1 - Cylinders

Medium	Temperature (° C)	Time to 1 °C off equilibrium (min)											
		Diameter (mm)											
		64	40	37	32	29	29	25	25	25	13	13	9,5
Height (mm)													
		38	30	10,2	16,5	25	12,5	20	10	6,3	12,6	6,3	9,5
Air	-50	130	75	35	45	50	35	40	25	20	20	15	15
	0	95	55	25	35	40	25	30	20	15	15	10	10
	50	105	60	30	35	45	30	35	20	20	20	15	15
	100	130	75	35	45	55	35	45	25	20	20	15	15
	150	145	65	40	50	60	40	45	30	25	25	20	20
	200	155	90	40	55	65	45	50	30	25	25	20	20
	250	160	95	45	55	65	45	50	30	25	25	25	20
Liquid	-50	75	35	10	15	20	10	15	5	5	5	5	5
	0	60	30	10	15	15	10	15	5	5	5	5	5
	50	65	30	10	15	20	10	15	5	5	5	5	5
	100	00	35	10	20	25	15	15	5	5	5	5	5
	150	85	40	10	20	25	15	20	10	5	10	5	5
	200	90	45	10	20	25	15	20	10	5	10	5	5
	250	90	45	15	20	25	15	20	10	5	10	5	5

Table 2 — Flat sheets

Medium	Temperature (°C)	Time to 1 °C off equilibrium (min)								
		Thickness (mm)								
		25	15	10	8	5	3	2	1	0,2
Air	-50	135	70	45	35	20	15	10	5	5
	0	95	50	30	25	15	10	10	5	5
	50	110	60	35	30	20	10	10	5	5
	100	140	75	45	35	20	15	10	5	5
	150	155	80	50	40	25	15	10	5	5
	200	160	85	55	40	25	15	10	5	5
	250	170	90	55	45	25	15	10	5	5
Liquid	-50	90	35	15	10	5	5	5	5	5
	0	75	30	15	10	5	5	5	5	5
	50	00	30	15	10	5	5	5	5	5
	100	90	35	20	10	5	5	5	5	5
	150	95	40	20	10	5	5	5	5	5
	200	100	40	20	15	5	5	5	5	5
	250	105	40	20	15	5	5	5	5	5

iTeh STANDARD PREVIEW Table 3 — Flat strips

Medium	Temperature (°C)	Time to 1 °C off equilibrium (min)																																
		Width (mm)																																
		25,4			15,0			12,7			6,35			4,0																				
		Thickness (mm)																																
12,7			10,0			9,5			6,5			5,0			3,0			2,0			1,0													
Air	-50	45	35	35	25	20	15	10	5	35	30	25	25	20	15	15	10	10	5	20	20	15	15	10	10	5	5	15	15	10	10	10	5	5
	0	30	25	25	20	15	10	10	5	30	25	20	20	15	15	10	10	5	5	15	15	10	10	10	5	5	5	10	10	10	10	5	5	5
	50	35	30	30	20	15	10	10	5	30	25	20	20	15	15	10	10	10	5	15	15	15	10	10	5	5	5	10	10	10	10	10	5	5
	100	45	35	35	25	20	15	10	5	40	30	30	25	20	20	15	10	10	5	20	20	15	15	10	10	5	5	15	15	10	10	10	10	5
	150	50	40	40	30	20	15	10	5	40	35	30	30	25	20	15	15	10	5	25	20	15	15	10	10	10	5	15	15	15	10	10	10	5
	200	50	40	40	30	25	15	10	5	45	35	30	30	25	20	15	15	10	5	25	20	20	15	10	10	10	5	15	15	15	15	10	10	5
	250	55	45	40	30	25	15	10	5	45	40	35	35	25	20	15	15	10	5	25	25	20	15	10	10	10	5	20	15	15	15	10	10	5
Liquid	-50	15	10	10	5	5	5	5	5	10	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
	0	10	10	10	5	5	5	5	5	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
	50	10	10	10	5	5	5	5	5	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
	100	15	10	10	5	5	5	5	5	10	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
	150	15	10	10	5	5	5	5	5	15	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
	200	15	10	10	5	5	5	5	5	15	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5
	250	15	10	10	5	5	5	5	5	15	10	10	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

[ISO 3383:1985](#)

<https://standards.iteh.ai/catalog/standards/sist/bd8cc8dc-2f36-4ee7-9de3-67adf4f04bdf/iso-3383-1985>